SI International System of Units

Post-Installed Reinforcing Bar Systems in Concrete—Qualification Requirements and Commentary

Reported by ACI Committee 355

ACI CODE-355.5-24

American Concrete Institute
Always advancing

American Concrete Institute
Always advancing

First Printing: June 2025
ISBN: 978-1-64195-319-1

Post-Installed Reinforcing Bar Systems in Concrete—Qualification Requirements and Commentary

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. Despite these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at http://concrete.org/Publications/DocumentErrata.aspx. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations regarding health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

ACI documents are written via a consensus-based process. The characteristics of ACI technical committee operations include:
(a) Open committee membership
(b) Balance/lack of dominance
(c) Coordination and harmonization of information
(d) Transparency of committee activities to public
(e) Consideration of views and objections
(f) Resolution through consensus process

The technical committee documents of the American Concrete Institute represent the consensus of the committee and ACI. Technical committee members are individuals who volunteer their services to ACI and specific technical committees.

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: **+1.248.848.3700**
Fax: **+1.248.848.3701**

www.concrete.org

ACI CODE-355.5-24

(SI Units)

Post-Installed Reinforcing Bar Systems in Concrete—Qualification Requirements and Commentary

An ACI Standard

Reported by ACI Committee 355

Andra Hoermann-Gast, Chair

Jay Dorst, Vice Chair

John F. Silva, Vice Chair

Neal S. Anderson
Jacques A. Bertrand
T. J. Bland
Rachel Chicchi Cross
Rolf Eligehausen
Werner A. F. Fuchs
Brian C. Gerber
Jan Erich Hofmann
Chiwan Wayne Hsieh
Amy S. Kolczak
Thomas A. Kolden
Anthony J. Lamanna
Giovanni Muciaccia
Daniel T. Mullins
John E. Pearson
Marlou B. Rodriguez
Milton Rodriguez
Peter C. Schillinger
Howard Silverman
Luke Tavernit
Jason H. Wagner
Roman Wan-Wendner

Consulting Members

Peter J. Carrato
Ronald A. Cook
Branko Galunic
Neil M. Hawkins
Christopher La Vine
Nam-Ho Lee
Lee W. Mattis
Robert R. McGlohn
Donald F. Meinheit
Conrad Paulson
Dan R. Stoppenhagen

Note: Special acknowledgment given to K. McBride for his contribution to this Code.

This Code prescribes testing programs and evaluation requirements for post-installed reinforcing bars intended for use in concrete under the straight-bar development and splice length design provisions of ACI CODE-318. Testing and assessment criteria are provided for various conditions of use, including seismic loading, sustained loading, aggressive environments, and reduced and elevated temperatures. Criteria are provided for establishing the required characteristic bond strength, reductions for adverse conditions, and associated job-site quality control requirements.

Keywords: post-installed reinforcing bars; qualification procedures.

CONTENTS

CHAPTER 1—INTRODUCTION, p. 4
1.1—Introduction, p. 4
1.2—Scope, p. 4
1.3—Units of measurement, p. 5

CHAPTER 2—NOTATION AND DEFINITIONS, p. 6
2.1—Notation, p. 6
2.2—Definitions, p. 8

CHAPTER 3—GENERAL REQUIREMENTS, p. 13
3.1—Test organization and basic requirements, p. 13
3.2—Variables and options, p. 13
3.3—Required tests for qualification of Type A grouts, p. 14

ACI CODE-355.5-24 was approved by the ACI Standards Board for publication May 2024, and published November 2024. The SI unit version was published in June 2025.

Copyright © 2024, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

3.4—Required tests for qualification of Type B grouts, p. 16
3.5—Assessment for alternative drilling methods, p. 18

CHAPTER 4—REQUIREMENTS FOR TEST SPECIMENS, REINFORCING BAR INSTALLATION, AND TESTING, p. 20
4.1—Testing by ITEA and manufacturer, p. 20
4.2—Test samples, p. 20
4.3—Concrete for test members, p. 20
4.4—Requirements for test members and reinforcing bars, p. 21
4.5—Installation, p. 23
4.6—Drill bit requirements, p. 23
4.7—Test methods, p. 23
4.8—Changes to products, p. 25

CHAPTER 5—REQUIREMENTS FOR GROUT IDENTIFICATION, p. 26
5.1—Basic requirements, p. 26
5.2—Verification, p. 26
5.3—Fingerprinting grouts, p. 26
5.4—Packaging, p. 27
5.5—Classification of grout as Type A or Type B, p. 27

CHAPTER 6—REFERENCE TESTS, p. 28
6.1—Purpose, p. 28
6.2—Required tests, p. 28
6.3—Conduct of tests, p. 28

CHAPTER 7—RELIABILITY TESTS, p. 30
7.1—Purpose, p. 30
7.2—Required tests, p. 30
7.3—Conduct of tests, p. 30
7.4—Limitations of reliability tests, p. 30
7.5—Sensitivity to hole cleaning: dry concrete, p. 31
7.6—Sensitivity to hole cleaning: saturated concrete, p. 33
7.7—Sensitivity to hole cleaning: water-filled hole, p. 34
7.8—Sensitivity to hole cleaning: submerged concrete, p. 35
7.9—Sensitivity to mixing effort, p. 36
7.10—Tension tests with sustained load at maximum long-term temperature, p. 36
7.11—Sensitivity to installation direction, p. 38

CHAPTER 8—SERVICE-CONDITION TESTS, p. 41
8.1—Purpose, p. 41
8.2—Required tests, p. 41
8.3—Conduct of tests, p. 41
8.4—Bond/splitting behavior at deep embedment, p. 41
8.5—Tension tests with decreased installation temperature, p. 42
8.6—Establishment of curing time, p. 44

CHAPTER 9—INSTALLATION PROCEDURE VERIFICATION TESTS, p. 45
9.1—Purpose, p. 45
9.2—Required tests, p. 45
9.3—Conduct of tests, p. 45
9.4—Injection at deep embedment, p. 45
9.5—Injection verification, p. 46

CHAPTER 10—DURABILITY TESTS, p. 48
10.1—Purpose, p. 48
10.2—Required tests, p. 48
10.3—Conduct of tests, p. 48
10.4—Sensitivity to freezing-and-thawing conditions, p. 48
10.5—Sensitivity to installation in low-moisture concrete, p. 50
10.6—Resistance to alkalinity and sulfur, p. 52
10.7—Resistance to corrosion, p. 55
10.8—Resistance to accelerated aging conditions, p. 57

CHAPTER 11—TESTS FOR SPECIAL CONDITIONS, p. 59
11.1—Purpose, p. 59
11.2—Required tests, p. 59
11.3—Conduct of tests, p. 59
11.4—Seismic tests, p. 59
11.5—Round-robin tests for regional concrete variation, p. 61
11.6—Tests to assess fire resistance, p. 63

CHAPTER 12—ASSESSMENT, p. 68
12.1—Analysis of data, p. 68
12.2—Normalization of capacities for measured concrete bond and steel strengths, p. 68
12.3—General requirements, p. 68
12.4—Bond strength requirements, p. 70
12.5—Assessment of sustained load behavior at maximum long-term temperature (7.10), p. 73
12.6—Assessment of performance associated with installation direction (7.11), p. 74
12.7—Assessment of bond and splitting behavior at deep embedment (8.4), p. 75
12.8—Assessment of performance with decreased installation temperature (8.5), p. 76
12.9—Assessment for installation in low-moisture concrete (10.5), p. 77
12.10—Assessment for establishment of curing time (8.6), p. 77
12.11—Assessment of installation procedure verification tests, p. 77
12.12—Assessment of freezing and thawing behavior (10.4), p. 77
12.13—Assessment of slice tests to assess durability, p. 78
12.14—Assessment of corrosion tests (10.7), p. 79
12.15—Assessment of performance under seismic tension (11.4), p. 79
12.16—Adjustment for regional variations in concrete (11.5), p. 79
12.17—Assessment of tests for determining fire resistance (11.6), p. 80
12.18—Establishment of hole-cleaning procedures, p. 82

American Concrete Institute Copyrighted Material—www.concrete.org

CHAPTER 13—DATA PRESENTATION, p. 84
13.1—General requirements, p. 84
13.2—Contents of reports, p. 84

CHAPTER 14—INDEPENDENT TESTING AND EVALUATION AGENCY REQUIREMENTS, p. 85
14.1—General requirements, p. 85
14.2—Certification, p. 85

CHAPTER 15—QUALITY CONTROL REQUIREMENTS, p. 86
15.1—Quality assurance program, p. 86
15.2—Quality control manuals, p. 86
15.3—Inspection, p. 86
15.4—Proof loading, p. 87

CHAPTER 16—REFERENCES, p. 88
Referenced standards and reports, p. 88
Commentary references, p. 88

American Concrete Institute Copyrighted Material—www.concrete.org

CODE

CHAPTER 1—INTRODUCTION

1.1—Introduction

This Code prescribes testing and evaluation requirements for post-installed reinforcing bar systems intended for use in structural concrete under the provisions of ACI CODE-318. Inspection is required during reinforcing bar installation as noted in 15.3.

1.2—Scope

This Code applies only to post-installed reinforcing bars as defined herein.

1.2.1 This Code applies to reinforcing bar diameters No. 10 through No. 43 installed in drilled holes with flowable grout.

1.2.2 Grouts shall be classified as either Type A or Type B as defined in 5.5 and evaluated in accordance with Tables 3.3 and 3.4, respectively.

1.2.3 This Code does not address the following systems and use conditions:

1. Grouts used to adhere reinforcing elements to concrete surfaces outside of a drilled hole

COMMENTARY

CHAPTER R1—INTRODUCTION

R1.1—Introduction

This Code prescribes the testing programs required to qualify post-installed reinforcing bar systems for design in accordance with the reinforcing bar provisions of ACI CODE-318. For a discussion of issues associated with the qualification and design of systems for post-installed reinforcing bars, refer to Mahrenholtz et al. (2020).

The use of post-installed reinforcing bar systems qualified in accordance with this Code may also be used in conjunction with other documents and standards addressing the modification, repair, or strengthening of structures, provided that the provisions for development and splicing of reinforcing bars are compatible with the provisions of ACI CODE-318.

R1.2—Scope

Post-installed reinforcing bars resist tension loads through mechanical bond (micro-interlock) and, to a lesser degree, chemical adhesion. Organic binders and hydraulic cements used for securing reinforcing bars in drilled holes (herein referred to as "grouts") may exhibit a range of performance characteristics associated with the drilling method, hole diameter, and hole cleaning procedures. The criteria provided in this Code evaluate the ability of the grout to be installed and to perform reliably at the embedment depths associated with the development and splice length provisions of ACI CODE-318. Design of post-installed reinforcing bars in existing structures using ACI CODE-562 and other design standards should be based on equivalent nominal strength in place of specified concrete strength, defined according to the target reliability level, and use development and splice length equations from the design-basis code.

R1.2.1 Use of the term "flowable" is intended to refer to grouts that are placed into holes before the reinforcing bar is installed and subsequently flow around the reinforcing bar once it is installed into the hole. This differentiation is made to set flowable grouts apart from dry-pack grouts, which are specifically excluded from this Code in 1.2.3. Flowable grouts may also be formulated to have properties that allow them to both flow around the reinforcing bar during installation and possess a high viscosity once the installation is complete such that the grout does not run out of a horizontal or upwardly inclined hole.

R1.2.2 Grouts used for post-installed reinforcing bars include organic (polymer) binders, hydraulically activated binders (cements), and combinations of polymers and hydraulically activated binders.

R1.2.3 Correct proportioning (metering) and mixing of grout components are important to good performance. For hydraulically activated grouts mixed in open containers and poured or injected into drilled holes, control of the water-cement ratio (w/c) is critical and, therefore, enhanced levels

American Concrete Institute Copyrighted Material—www.concrete.org