ANSI/AWWA **B506-25**

(Revision of ANSI/AWWA B506-18)

AWWA Standard

Zinc Orthophosphate

Effective date: July 1, 2025.
First edition approved by Board of Directors Feb. 12, 2006.
This edition approved Jan. 23, 2025.
Approved by American National Standards Institute Jan. 7, 2025.

American Water Works Association

Approved American National Standard ANSI

STANDARD Since 1881

AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or code of any governmental authority. AWWA standards are intended to represent a consensus of the water industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed in the Official Notice section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

Caution Notice: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of ANSI approval. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 1180 Avenue of the Americas, 10th Floor, New York, NY 10036; 212.642.4900, or e-mailing info@ansi.org.

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including scanning, recording, or any information or retrieval system. Reproduction and commercial use of this material is prohibited, except with written permission from the publisher. Please send any requests or questions to permissions@awwa.org.

ISBN-13, print: 978-1-64717-254-1

ISBN-13, electronic: 978-1-61300-777-8

DOI: http://dx.doi.org/10.12999/AWWA.B506.25

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including scanning, recording, or any information or retrieval system. Reproduction and commercial use of this material is prohibited, except with written permission from the publisher.

Copyright © 2025 by American Water Works Association
Printed in USA

Copyright © 2025 by American Water Works Association. All Rights Reserved

Committee Personnel

The AWWA Standards Committee on Scale and Corrosion-Control Chemicals, which reviewed and approved this standard, had the following personnel at the time of approval:

Milton D. Larsen, *Chair*

General Interest Members

M. Aghababaei, Arcadis, San Antonio, Tex.
N.J. Edman (*liaison, nonvoting*), Standards Group Liaison, AWWA, Denver, Colo.
M.D. Larsen, Kennedy Jenks Consultants, Gig Harbor, Wash.
N.E. McTigue, Cornwell Engineering Group, Newport News, Va.
D. Orozco, Consultant, Safety Harbor, Fla.
T. Phelan (*liaison, nonvoting*), Standards Council Liaison, Kelowna, B.C.
R.D. Vaidya, PCL Construction, Tampa, Fla.

Producer Members

H.T. Belcher Jr., Corrtrac Systems Corporation, Currituck, N.C.
D. Linville, Aqua Smart Inc., Atlanta, Ga.
C.P. Principi, Carus Corporation, Belmont, N.C.

User Members

D.M. LaFalam, Town of Lincoln, Lincoln, Mass.
R.M. Powell, Pinellas County Utilities, Spring Hill, Fla.

Copyright © 2025 by American Water Works Association. All Rights Reserved

This page intentionally blank.

Copyright © 2025 by American Water Works Association. All Rights Reserved

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.		PAGE
Foreword		
I	Introduction	vii
I.A	Background	vii
I.B	History	x
I.C	Acceptance	x
II	Special Issues	xi
II.A	Storage and Handling Precautions	xi
III	Use of This Standard	xi
III.A	Purchaser Options and Alternatives	xi
III.B	Modification to Standard	xii
IV	Major Revisions	xii
V	Comments	xii
Standard		
1	**General**	
1.1	Scope	1
1.2	Purpose	1
1.3	Application	1
2	**References**	2
3	**Definitions**	2
4	**Requirements**	
4.1	Physical Requirements	3
4.2	Chemical Requirements	3
4.3	Impurities	4
5	**Verification**	
5.1	Sampling	4
5.2	Test Procedures	5
5.3	Notice of Nonconformance	7
6	**Delivery**	
6.1	Marking	8
6.2	Packaging and Shipping	8
6.3	Affidavit of Compliance or Certified Analysis	9
Table		
1	Sample Size Determination for Orthophosphate Analysis	7

Copyright © 2025 by American Water Works Association. All Rights Reserved

This page intentionally blank.

Copyright © 2025 by American Water Works Association. All Rights Reserved

Foreword

This foreword is for information only and is not a part of ANSI/AWWA B506.*

I. Introduction

I.A. *Background.* Phosphate chemicals are among the few substances that can be safely and effectively used in potable water for corrosion control and/or inhibition. There are several types of phosphate inhibitors available, including zinc orthophosphate (ZOP), which was originally found to suppress iron corrosion by the Long Beach, Calif., Water Department in the 1940s.† Since that time, various formulations of ZOP have been used as corrosion inhibitors in potable water supplies.

ZOP can be an effective chemical inhibitor of electrolytic corrosion in iron, steel, copper, and lead, which occurs in aggressive water (with low to moderate hardness and alkalinity). ZOP was originally used to suppress colored water caused by leaching of tuberculation of iron pipe.† This treatment technology can be effective in waters without elevated concentrations of iron and manganese to sequester and where calcium precipitation and scaling are of minimal concern.

ZOP can also reduce asbestos fiber counts and provide protection for asbestos-cement and concrete pipe. It prevents concrete pipe deterioration in aggressive waters because the zinc interacts with cement and forms a protective zinc carbonate barrier on the surface at zinc concentrations as low as 0.2 mg/L.‡

ZOP formulations consist of zinc salts (sulfate and chloride) combined with orthophosphate formulated in a wide variety of zinc-to-phosphate ratios, ranging from 15:1 to 1:16.

Typically, as the zinc-to-phosphate ratio and dosage are decreased, it is necessary to increase the phosphate portion and dosage. The reverse also often occurs. The zinc proportion is provided by dissolving zinc in sulfonic, sulfuric, or hydrochloric acid and mixing that solution with sodium orthophosphate or phosphoric acid. Until the mid-1980s, the zinc proportion was more economical than the phosphate, and higher

* American National Standards Institute, 1180 Avenue of the Americas, 10th Floor, New York, NY 10036.

† Murray, W.B. 1970. "A Corrosion Inhibitor Process for Domestic Water." *Journal AWWA*. 62(10):659–662.

‡ Leroy, P. et al. 1996 (2nd ed.). Ch. 7, "Cement Based Materials," p. 354; and Vik, E.A. et al. 1996 (2nd ed.). Ch. 8, "Mitigation of Corrosion Effects," p. 426. In *Internal Corrosion of Water Distribution Systems* (AwwaRF and DVGW-TZW). Denver, Colo.: AwwaRF and AWWA.

Copyright © 2025 by American Water Works Association. All Rights Reserved

zinc-to-phosphate ratios were used. Chemical costs change relatively rapidly, and the cost value of the ratio may change.

ZOP solutions are usually acidic, have a pH of less than 2, and are a hazardous chemical. Double containment of large storage vessels and piping as well as other chemical handling safety measures are appropriate and required.

ZOP in metal-corrosion suppression functions by two direct mechanisms: film formation and electrochemical passivation. In metal-corrosion protection, the orthophosphate provides an anodic inhibitor, and zinc films form at the cathode and provide a cathodic inhibitor. The blockage of both anodic and cathodic corrosion sites provides a double interruption of the electrochemical-corrosion reaction; that can be more effective than a single-acting inhibitor, which is typical for other phosphate or silicate chemicals.

Asbestos-cement pipe, concrete pipe, or cement linings can be protected by zinc carbonate film, which inhibits aggressive water (with a Langelier Index of less than zero) from leaching calcium and deteriorating the cement surface. There is no apparent benefit from the orthophosphate in cement protection, and other zinc formulations, including zinc chloride, can be used. However, ZOP can be a wide-ranging corrosion inhibitor for multiple types of pipe and reservoir materials of water distribution and consumer plumbing systems.

Typically, maximum ZOP dosages are limited to 5–30 mg/L, depending on supplier qualifications in testing to NSF[§]/ANSI/CAN[¶] 60, Drinking Water Treatment Chemicals—Health Effects, in the United States. The supplier can provide operators appropriate information on certification and dosage limit of the product for use in potable water. German and other European potable water standards do not allow the use of zinc in chemicals added to potable water, and the possible use of ZOP as a corrosion inhibitor must be evaluated in each country for its intended use.

The zinc concentration is frequently limited to 0.2–2 mg/L to avoid water system secondary-contaminant limits and wastewater and effluent-discharge toxicity limits. However, as is typical for most corrosion inhibitors, it is desirable to use a passivating dose of three to five times the maintenance inhibitor dose for a month or more to reach all portions of the distribution system and initially more rapidly passivate the metal to provide the protective films.

Phosphate concentrations should typically be in the range of 0.5–2 mg/L as phosphorus (P). Sometimes, phosphate may stimulate bacteria and bioslime growths,

[§] NSF International, 789 North Dixboro Road, Ann Arbor, MI 48105.

[¶] Standards Council of Canada, 55 Metcalfe Street, Suite 600, Ottawa, ON K1P 6L5 Canada.

Copyright © 2025 by American Water Works Association. All Rights Reserved

particularly in warmer water and where chloramination disinfection is practiced. There have been instances in warmer waters in Hawaii and the southeastern United States where elevated heterotrophic bacteria counts and other microbiological organisms have caused skin rashes in people bathing.** This possibility should always be considered when evaluating a phosphate corrosion inhibitor.

It is highly desirable to test and evaluate the effectiveness of various combinations of zinc-to-phosphate ratios and at various dosages with both instrumentation and pipe-coupon pilot plant tests.†† Control tests of no inhibitor, orthophosphate without zinc, and at various pH and alkalinity values should be evaluated to select the optimum corrosion-inhibitor concentration for iron, steel, copper, lead, and cement protection. It is also quite likely that type, strategy, and temperature effects will result in use of a larger inhibitor dose in summer (warm-water temperature conditions) than in winter. Either in situ metal coupon, real-time linear polarization, or electrochemical noise measurements can optimize inhibitor dosage for changing water conditions. Inhibitor dosage control may be automated by techniques such as linear polarization or electrochemical noise sensors using programmable logic controllers (PLCs).

Alternatively, prospective vendors should be asked for initial opinions based on water quality characteristics, piping types, and conditions for zinc-to-phosphate ratios to initially try, as well as dosage recommendations. These can be changed later for more optimum conditions based on observed results after an extended period of use.

The water characteristics that are most important when applying ZOP in corrosion protection are pH, alkalinity, hardness, and temperature. The optimum pH for use of ZOP is 7.2–7.8, and ZOP optimum dosage rates are typically lower in elevated pH and colder waters. There are concerns for ZOP dosing into water exhibiting a pH above 8.1 in order to avoid possible precipitation of the zinc and undesirable turbidity or particulates in the distributed water. There have been successful applications of ZOP in medium and hard waters with pH ranges from 8.3 to 9.0. Much of the success with ZOP as a corrosion inhibitor has been obtained in waters exhibiting low-to-moderate hardness and alkalinity.

A recognized limitation of using a ZOP corrosion inhibitor is contribution of the zinc loading at the wastewater treatment plant and in the effluent discharged to surface

** Edwards, M., B. Marshall, Y. Zhang, and Y.-J., Lee. 2005. "Unintended Consequences of Chloramination Hit Home." Proc. Disinfection 2005, Feb. 6–9, 2005, Mesa, Ariz. Alexandria, Va.: Water Environment Federation.

†† Reiber, S., R.A. Ryder, and I. Wagner. 1996 (2nd ed.). Ch. 9, "Corrosion Assessment Technologies." In *Internal Corrosion of Water Distribution Systems* (AwwaRF and DVGW-TZW). Denver, Colo.: AwwaRF and AWWA.

Copyright © 2025 by American Water Works Association. All Rights Reserved

waters. This is sometimes regulated to be as low as 0.5 mg/L or lower, and effluent toxicity limits may be lower than 0.1 mg/L of zinc. Another recognized effect of using a ZOP corrosion inhibitor is consumption of alkalinity and possible reduction in water pH, typically by 0.1–0.2 units. Formulations with low zinc content may provide effective corrosion suppression while meeting wastewater regulations. Many different ratios are available from suppliers.

Typically, zinc is measured in the water at the end of distribution systems to provide an indication that the inhibitor dosage is sufficient to reach all portions of the piping system. Because of the corrosion inhibitor's filming effect, it is possible to have the dosage interrupted for several days to perhaps a week and not seriously compromise corrosion protection if the maintenance dose is resumed.

I.B. *History*. The first edition of ANSI/AWWA B506, Zinc Orthophosphate, was approved by the AWWA Board of Directors on Feb. 12, 2006. The last edition was approved on June 11, 2018. This edition was approved on Jan. 23, 2025.

I.C. *Acceptance*. In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the original consortium included the Water Research Foundation (formerly AwwaRF) and the Conference of State Health and Environmental Managers (COSHEM). The American Water Works Association (AWWA) and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.[‡‡] Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including four standards developed under the direction of NSF: NSF/ANSI/CAN 60, Drinking Water Treatment Chemicals—Health Effects; NSF/ANSI/CAN 61, Drinking Water System Components—Health Effects; NSF/ANSI 372, Drinking Water System Components—Lead Content; and NSF/ANSI/CAN 600, Health Effects Evaluation and Criteria for Chemicals in Drinking Water.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI/CAN 60. Individual states or local agencies have

[‡‡] Persons outside the United States should contact the appropriate authority having jurisdiction.

Copyright © 2025 by American Water Works Association. All Rights Reserved

authority to accept or accredit certification organizations within their jurisdictions. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

NSF/ANSI/CAN 600 (which formerly appeared in NSF/ANSI/CAN 60 and 61 as Annex A, "Toxicology Review and Evaluation Procedures") does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of "unregulated contaminants" are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of NSF/ANSI/CAN 600 procedures may not always be identical, depending on the certifier.

ANSI/AWWA B506 addresses additives requirements in Sec. 4.3.2 of the standard. The transfer of contaminants from chemicals to processed water or to residual solids is becoming a problem of greater concern. The language in Sec. 4.3.2 is a recommendation only for direct additives used in the treatment of potable water to be certified by an accredited certification organization in accordance with NSF/ANSI/CAN 60, Drinking Water Treatment Chemicals—Health Effects. However, users of the standard may opt to make this certification a requirement for the product. Users of this standard should consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

II. Special Issues

II.A. *Storage and Handling Precautions*. ZOP that is a dry solid should be stored in closed containers in a cool, dry area on concrete floors and should be protected from physical damage. Dry ZOP has an affinity for water and can easily absorb moisture, which can result in severe caking and lumping.

Liquid ZOP is generally manufactured with phosphoric acid and zinc salts. Therefore, ZOP products should be stored and handled as any typical strong acid and should be considered hazardous.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. *Purchaser Options and Alternatives*. The following information should be provided by the purchaser:

1. Standard used—that is, ANSI/AWWA B506, Zinc Orthophosphate, of latest revision.

Copyright © 2025 by American Water Works Association. All Rights Reserved

2. Quantity required.

3. Whether compliance with NSF/ANSI/CAN 60, Drinking Water Treatment Chemicals—Health Effects, is required.

4. Zinc-to-phosphate ratio (Zn:PO_4^{3-}) desired.

5. Details of federal, state, provincial, territorial, and local requirements (Section 4).

6. Type of material—dry or liquid (Sec. 4.2).

7. Whether the purchaser will reject product from containers or packaging with missing or damaged seals. The purchaser may reject product from bulk containers or packages with missing or damaged seals unless the purchaser's tests of representative samples, conducted in accordance with Sec. 5.2, demonstrate that the product meets the standard. Failure to meet the standard or the absence of, or irregularities in, seals may be sufficient cause to reject a shipment.

8. Whether alternative security measures have been adopted to replace or augment the security measures set out in Sec. 6.2.3 and Sec. 6.2.4.

9. Form of shipment—bulk or package and the type and size of container (Sec. 6.2).

10. Affidavit of compliance or certified analysis, if required (Sec. 6.3).

III.B. *Modification to Standard*. Any modification of the provisions, definitions, or terminology in this standard must be provided by the purchaser.

IV. Major Revisions. Major changes made to the standard in this revision include the following:

Updates to boilerplate language in the following sections:

1. Minor boilerplate updates to the following sections:
    - I.A Background
    - I.C Acceptance
    - III.A Purchaser Options and Alternatives
    - Section 2 References
    - Section 4 Requirements
    - Sec. 4.3.2 Product Certifications

V. Comments. If you have any comments or questions about this standard, please call AWWA Engineering and Technical Services at 303.794.7711, write to the department at 6666 West Quincy Avenue, Denver, CO 80235-3098, or e-mail at standards@awwa.org.

Copyright © 2025 by American Water Works Association. All Rights Reserved

American Water Works Association

ANSI/AWWA B506-25
(Revision of ANSI/AWWA B506-18)

AWWA Standard

Zinc Orthophosphate

SECTION 1: GENERAL

Sec. 1.1 Scope

This standard describes zinc orthophosphate (ZOP) corrosion inhibitor in dry and liquid forms for use in the treatment of potable water, wastewater, or reclaimed water.

Sec. 1.2 Purpose

The purpose of this standard is to provide the minimum requirements for ZOP, including physical, chemical, sampling, packaging, shipping, and testing requirements.

Sec. 1.3 Application

This standard can be referenced in documents for purchasing and receiving ZOP and can be used as a guide for testing the physical and chemical properties of ZOP samples. The stipulations of this standard apply when this document has been referenced and then only to ZOP used in the treatment of potable water, wastewater, or reclaimed water.

Copyright © 2025 by American Water Works Association. All Rights Reserved