ANSI/AWWA **C216-22**

(Revision of ANSI/AWWA C216-15)

AWWA Standard

Heat-Shrinkable Cross-Linked Polyolefin Coatings for Steel Water Pipe and Fittings

Effective date: Feb. 1, 2023.
First edition approved by Board of Directors Jan. 29, 1989.
This edition approved Oct. 24, 2022.
Approved by American National Standards Institute Sept. 15, 2022.

American Water Works Association

Approved American National Standard ANSI

STANDARD Since 1881


AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or code of any governmental authority. AWWA standards are intended to represent a consensus of the water industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed in the Official Notice section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

Caution Notice: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of ANSI approval. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; 212.642.4900, or emailing info@ansi.org.



All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including scanning, recording, or any information or retrieval system. Reproduction and commercial use of this material is prohibited, except with written permission from the publisher. Please send any requests or questions to permissions@awwa.org.

ISBN-13, print: 978-1-64717-118-6

ISBN-13, electronic: 978-1-61300-649-8

DOI: http://dx.doi.org/10.12999/AWWA.C216.22

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopy, recording, or any information or retrieval system, except in the form of brief excerpts or quotations for review purposes, without the written permission of the publisher.

Copyright © 2022 by American Water Works Association
Printed in USA

Copyright © 2022 by American Water Works Association. All Rights Reserved

Committee Personnel

The Steel Water Pipe Manufacturers Technical Advisory Committee (SWPMTAC) Task Group for ANSI/AWWA C216, which updated this standard, had the following personnel at the time:

Jeff Bertsche, *Chair*
Cindy Patton, *Vice-Chair*

J. Bertsche, Seal for Life, Sandy Hook, Conn.
J. Buratto, Seal For Life, Pflugerville, Tex.
D. D'Ambrosio, Polyguard Products Inc., Lancaster, Tex.
G.A. Davidenko, Northwest Pipe Co., Saginaw Facility, Saginaw, Tex.
A. Geiger, Canusa-SFL, Nisku, Alberta.
A. Fletcher, Pentair Water Solutions Pty. Ltd., Melbourne, Vic., Australia
B.D. Keil, Northwest Pipe Company, South Jordan, Utah
D. Libby, Chase Corporation, Westwood, Mass.
R.D. Mielke, Northwest Pipe Company, Raleigh, N.C.
C. Patton, Seal for Life, Houston, Tex.
B.P. Simpson, American SpiralWeld Pipe Company, Birmingham, Ala.
C. Smith, TexStar Products LLC, Houston, Tex.
T. Tatem, Canusa-SFL, Houston, Tex.
S.J. Thomas, Liberty Coatings Company, Morrisville, Penn.

The AWWA Standards Committee on Steel Pipe, which reviewed and approved this standard, had the following personnel at the time of approval:

John H. Bambei Jr., *Chair*
Bob J. Card, *Vice-Chair*
John L. Luka, *Secretary*

General Interest Members

S.A. Arnaout (*alternate*), Stantec, Dallas, Tex.
J.H. Bambei Jr., Bambei Engineering Services, Arvada, Colo.
R.J. Card, Lockwood, Andrews & Newnam Inc., Suwanee, Ga.
R.L. Coffey, Consultant, Bend, Ore.
R.L. Gibson, Freese and Nichols Inc., Fort Worth, Tex.

Copyright © 2022 by American Water Works Association. All Rights Reserved

M.D. Gossett, HDR, Denver, Colo.
M.B. Horsley (*alternate*), Horsley Engineering LLC, Overland Park, Kans.
R. Issa, AECOM, McKinney, Tex.
C.H. Kirby (*alternate*), Lockwood, Andrews & Newnam Inc., Houston, Tex.
R.A. Kufaas, Norske Corrosion & Inspection Service Ltd., Abbotsford, B.C.
J.L. Mattson, Corrosion Control Technologies, Sandy, Utah
D.L. McPherson (*alternate*), HDR, Charlotte, N.C.
A. Murdock, Jacobs, Salt Lake City, Utah
R. Ortega, Aurora Technical Services, Houston, Tex.
E.S. Ralph (*liaison, nonvoting*), Standards Engineer Liaison, AWWA, Denver, Colo.
A.E. Romer (*alternate*), AECOM, Orange, Calif.
J.R. Snow, Stantec, Denver, Colo.
A.M. Stanton, Black & Veatch, Pasadena, Calif.
W.R. Whidden, Woolpert, Orlando, Fla.

Producer Members

H.H. Bardakjian, Consultant, Glendale, Calif.
D.A. Dechant, Dechant Infrastructure Services, Aurora, Colo.
B.D. Keil, Northwest Pipe Company, South Jordan, Utah
J.L. Luka, American SpiralWeld Pipe Company, Columbia, S.C.
R.D. Mielke (*alternate*), Northwest Pipe Company, Raleigh, N.C.
G.F. Ruchti (*alternate*), Consultant, Punta Gorda, Fla.
B.P. Simpson (*alternate*), American Cast Iron Pipe Company, Birmingham, Ala.
C.C. Sundberg, Victaulic, Issaquah, Wash.
R. Wu (*alternate*), Thompson Pipe Group, Grand Prairie, Tex.

User Members

L. Adams, US Bureau of Reclamation, Denver, Colo.
G.A. Andersen, New York City Bureau of Water Supply, Little Neck, N.Y.
B. Cheng, Metro Vancouver, Burnaby, B.C.
B. Fountain, San Diego County Water Authority, San Diego, Calif.
J. Fox, Tampa Bay Water, Clearwater, Fla.
S. Hattan, Tarrant Regional Water District, Fort Worth, Tex.
M. Lobik, Springfield Water & Sewer, Springfield, Mass.

Copyright © 2022 by American Water Works Association. All Rights Reserved

T. Peng, Metropolitan Water District, Los Angeles, Calif.

G. Ramon (*liaison, nonvoting*), Standards Council Liaison, Little Rock Water Reclamation Authority, Little Rock, Ark.

V. Scutelnicu, Los Angeles Department of Water and Power, Los Angeles, Calif.

M. Turney (*alternate*), Denver Water, Denver, Colo.

Copyright © 2022 by American Water Works Association. All Rights Reserved

This page intentionally blank.

Copyright © 2022 by American Water Works Association. All Rights Reserved

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.		PAGE
Foreword		
I	Introduction	ix
I.A	Background	ix
I.B	History	ix
II	Special Issues	ix
II.A	General	ix
II.B	Weld-After-Backfill	ix
III	Use of This Standard	x
III.A	Purchaser Options and Alternatives	x
III.B	Modification to Standard	x
IV	Major Revisions	xi
V	Comments	xi
Standard		
1	**General**	
1.1	Scope	1
1.2	Purpose	2
1.3	Application	2
2	**References**	2
3	**Definitions**	3
4	**Requirements**	
4.1	Equipment	4
4.2	Materials and Workmanship	4
4.3	Coating System	4
4.4	Surface Preparation	5
4.5	Coating Application (Field and Shop)	6
4.6	Coating Repair	7
4.7	Field Procedures	7
5	**Verification**	
5.1	Coating Materials Prequalification	8
5.2	Prequalification Requirements of Coating System	8
5.3	Quality Assurance and Records	10
5.4	Inspection and Testing by the Purchaser	10
5.5	Quality Control Requirements of Applied Coating System	11
5.6	Rejection	14
6	**Delivery**	
6.1	Marking	14
6.2	Packaging and Shipping	14
6.3	Affidavit of Compliance	15
Tables		
1	Prequalification Requirements of Coating System	10
2	Quality Control Requirements of Applied Coating System	11

Copyright © 2022 by American Water Works Association. All Rights Reserved

This page intentionally blank.

Copyright © 2022 by American Water Works Association. All Rights Reserved

Foreword

This foreword is for information only and is not a part of ANSI/AWWA C216.*

I. Introduction.

I.A. *Background.* Heat-shrinkable cross-linked polyolefin coatings for external use on special sections, connections, and fittings for underground steel water pipelines have been used since 1960. This standard establishes required performance standards for heat-shrinkable cross-linked polyolefin coatings.

I.B. *History.* The first edition of this standard was approved by the AWWA Board of Directors on Jan. 29, 1989, and had an effective date of July 1, 1989. Subsequent editions were approved on June 19, 1994, with an effective date of Aug. 1, 1995; on Jan. 23, 2000; on Jan. 21, 2007; and Jan. 24, 2015. This edition was approved on Oct. 24, 2022.

II. Special Issues.

II.A. *General.* ANSI/AWWA C216 is intended to govern the exterior coating of special sections, connections, and fittings for underground steel water pipelines. These types of coatings are generally used on pipe that has been coated before transportation to the field site. ANSI/AWWA C216 is based on the best-known experience, but it is not intended for unqualified use under all conditions. The advisability of its use for any installation must be reviewed by the purchaser.

II.B. *Weld-After-Backfill.* Weld-after-backfill is the sequence of assembling a welded joint, tack welding the outside joint, applying the exterior joint coating(s), backfilling the pipe joint, and then welding the inside joint at a later time (where internal welding is safe and practical). Weld-after-backfill is an acceptable practice provided that appropriate procedures and coating materials are used. Consult with the manufacturers and other responsible parties regarding recommended products, installation, and backfill procedures required for the weld-after-backfill sequence. At the request of the purchaser, the coating manufacturer shall provide testing or historical information to verify that the exterior joint coating will retain minimum performance requirements in accordance with the applicable standard throughout the heat-affected area.

* American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

Copyright © 2022 by American Water Works Association. All Rights Reserved

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. *Purchaser Options and Alternatives*. The following items should be included by the purchaser:

1. Standard used—that is, ANSI/AWWA C216, Heat-Shrinkable Cross-Linked Polyolefin Coatings for Steel Water Pipe and Fittings, of latest revision.
2. Whether compliance with NSF/ANSI 61, Drinking Water System Components—Health Effects, is required.
3. Any exceptions to the standard that may be required.
4. Description and number of each type of special sections, connections, and fittings for type of exterior protection.
5. Underground or underwater conditions.
6. Severe conditions (Sec. 1.1.1).
7. Maximum operating potable water temperature of the pipeline (Sec. 1.1.2).
8. Configuration of coating (types I, II, III, and IV) (Sec. 4.3.1.1).
9. Coating dimensions (Sec. 4.3.1.3).
10. Surface preparation (Sec. 4.4).
11. Filler material (Sec. 4.5.1.3).
12. Training (Sec. 4.5.1.5).
13. Repair (Sec. 4.6).
14. Conditions for outdoor storage (Sec. 4.7.2).
15. Prequalification (Sec. 5.1). NOTE: With reference to Sec. 5.1 (option 2), when submission of samples of proposed materials for testing by the purchaser is specified, the purchaser should address how testing costs will be assigned. According to commonly accepted industry practice, the purchaser is responsible for the cost of initial testing of coating material samples originally offered by the constructor. If any initial samples fail to conform to the standard, additional samples may be tested. The constructor pays for any additional testing.
16. Coating materials tests (Sec. 5.2).
17. Thickness (Sec. 5.2.2).
18. Frequency of adhesion testing, and adhesion testing on fittings, repairs, special sections, and appurtenances (Sec. 5.5.4.4).
19. Packaging (Sec. 6.2.1).
20. Affidavit of compliance if required (Sec. 6.3).

III.B. *Modification to Standard*. Any modification to the provisions, definitions, or terminology in this standard must be provided by the purchaser.

Copyright © 2022 by American Water Works Association. All Rights Reserved

IV. Major Revisions. Major changes made to the standard in this edition are as follows:

1. Sec. III.A Purchaser Options and Alternatives, added No. 18 Frequency of Adhesion Testing
2. Added a new Sec. 1.1.3 to the Scope for substrates other than carbon steel.
3. In Section 3: Definitions, Applicator was added.
4. Section 4 headings were revised to be consistent with AWWA standardized wording and headings.
5. Sec. 4.1 Equipment was revised to be consistent with the updated wording in other steel pipe coating standards.
6. Sec. 4.2 Materials and Workmanship was revised to be consistent with the updated wording in other steel pipe coating standards, and sections on safety and personnel were added.
7. In Sec. 4.3.1, the description of adhesive was expanded.
8. Sec. 4.4 Surface Preparation was revised to establish consistent language between similar AWWA steel pipe coating standards, and redundant language that is already included in the referenced SSPC standards was removed. References to SSPC-SP COM, SSPC-VIS 1, and SSPC-VIS 3 were also added to clarify when more thorough cleaning may be needed and which cleaning methods are considered more thorough.
9. The visual comparative standard section (old Sec. 4.3.2.3) was removed because it is duplicative with the language in the referenced SSPC-SP standards in Sec. 4.4.3.
10. Sec. 4.6 Coating Repair was added.
11. In Sec. 5.2.10, updated the heading to Tensile strength at break and updated the heading of Sec. 5.2.11 to Elongation at break.
12. In Table 1, changed the units for Adhesion to prepared steel and Impact resistance. In Table 2, changed the units for Field adhesion to prepared steel.
13. In Sec. 5.5.4.4, updated the frequency of the field peel test.
14. Sec. 6.3 was modified to include affidavits from both the coating manufacturer and the applicator.

V. Comments. If you have any comments or questions about this standard, please call AWWA Engineering and Technical Services at 303.794.7711; FAX at 303.795.7603; write to the department at 6666 West Quincy Avenue, Denver, CO 80235-3098; or email at standards@awwa.org.

Copyright © 2022 by American Water Works Association. All Rights Reserved

This page intentionally blank.

Copyright © 2022 by American Water Works Association. All Rights Reserved

ANSI/AWWA C216-22
(Revision of ANSI/AWWA C216-15)

American Water Works Association

Dedicated to the World's Most Important Resource®

AWWA Standard

Heat-Shrinkable Cross-Linked Polyolefin Coatings for Steel Water Pipe and Fittings

SECTION 1: GENERAL

Sec. 1.1 Scope

This standard describes the material, application, and field-procedure requirements for protective exterior coatings consisting of heat-shrinkable cross-linked polyolefin coatings. ANSI/AWWA C216 also describes the application of protective exterior coatings to special sections, connections, and fittings to be used in underground and underwater steel water pipelines.

Heat-shrinkable cross-linked polyolefin coatings may be field or shop applied as provided in this standard. This standard describes only heat-shrinkable coatings that consist of a cross-linked polyolefin backing that has been coated with an adhesive. These coatings are referred to as *heat-shrinkable coatings* throughout the remainder of this standard.

1.1.1 *Conditions not discussed in this standard.* This standard does not discuss the additional materials and procedures that may be required for severe conditions, such as those encountered during construction of some underwater lines, casing pipe, river crossings, and lines in exceptionally rocky areas. Also, applications such as extensive shop or field coating of steel pipe can exist that indicate a possible modification to the standard material may need to be considered. Under these

Copyright © 2022 by American Water Works Association. All Rights Reserved