ANSI/AWWA C224-17
(Revision of ANSI/AWWA C224-11)

American Water Works Association

Dedicated to the World's Most Important Resource®

AWWA Standard

Nylon-11-Based Polyamide Coatings and Linings for Steel Water Pipe and Fittings

Effective date: May 1, 2017.
First edition approved by AWWA Board of Directors June 17, 2001.
This edition approved Jan. 14, 2017.
Approved by American National Standards Institute Jan. 3, 2017.

American Water Works Association | STANDARD | *Since 1881*

Approved American National Standard ANSI


AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or code of any governmental authority. AWWA standards are intended to represent a consensus of the water industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed on the first page of the Official Notice section of *Journal – American Water Works Association*. The action becomes effective on the first day of the month following the month of *Journal – American Water Works Association* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; 212.642.4900; or emailing info@ansi.org.



This AWWA content is the product of thousands of hours of work by your fellow water professionals. Revenue from the sales of this AWWA material supports ongoing product development. Unauthorized distribution, either electronic or photocopied, is illegal and hinders AWWA's mission to support the water community.

ISBN-13, print: 978-1-62576-215-3 eISBN-13, electronic: 978-1-61300-415-9
DOI: http://dx.doi.org/10.12999/AWWA.C224.17

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopy, recording, or any information or retrieval system, except in the form of brief excerpts or quotations for review purposes, without the written permission of the publisher.

Copyright © 2017 by American Water Works Association
Printed in USA

Committee Personnel

The Steel Water Pipe Manufacturers Technical Advisory Committee (SWPMTAC) Task Group on C224, which reviewed and revised this edition, had the following personnel at the time:

Stephen Serpe, *Chair*
Ashley Fletcher, *Vice-Chair*

A. Fletcher, Steel Mains Pty. Ltd., Victoria, Australia	(AWWA)
G. Larsen, Smith-Blair, Texarkana, Texas	(AWWA)
B. Murphy, Sherman-Williams Company, Villaneuva, N.M.	(AWWA)
V. O'Dea, Tnemec Company Inc., Kansas City, Kan.	(AWWA)
S. Serpe, Arkema Inc., King of Prussia, Pa.	(AWWA)
G. Tate, Viking Johnson, Hitchen, U.K.	(AWWA)
J.A. Wise, Canus, International Sales Inc., Surrey, B.C., Canada	(AWWA)

The AWWA Standards Committee on Steel Pipe, which reviewed and approved this standard, had the following personnel at the time of approval:

John H. Bambei Jr., *Chair*
Dennis A. Dechant, *Vice-Chair*
John L. Luka, *Secretary*

General Interest Members

J.H. Bambei Jr., Bambei Engineering Services, Arvada, Colo.	(AWWA)
W.R. Brunzell, Brunzell Associates Ltd., Skokie, Ill.	(AWWA)
R.J. Card, Lockwood, Andrews & Newnam Inc., Houston, Texas	(AWWA)
R.L. Coffey, HDR Engineering Inc., Omaha, Neb.	(AWWA)
S.N. Foellmi, Black & Veatch Corporation, Irvine, Calif.	(AWWA)
R.L. Gibson, Freese and Nichols Inc., Fort Worth, Texas	(AWWA)
M.D. Gossett,* HDR Engineering Inc., Denver, Colo.	(AWWA)
M.B. Horsley,* Horsley Engineering LLC, Overland Park, Kan.	(AWWA)
R. Issa,* AECOM, McKinney, Texas	(AWWA)
R.A. Kufaas, Norske Corrosion & Inspection Services Ltd., Surrey, B.C., Canada	(AWWA)
J.L. Mattson, Corrosion Control Technologies, Sandy, Utah	(AWWA)
A. Murdock, CH2M, Salt Lake City, Utah	(AWWA)

* Alternate

R. Ortega,* Lockwood, Andrews & Newnam Inc., Houston, Texas (AWWA)
E.S. Ralph,† Standards Engineer Liaison, AWWA, Denver, Colo. (AWWA)
A.E. Romer, AECOM, Orange, Calif. (AWWA)
J.R. Snow, MWH Americas, Denver, Colo. (AWWA)
W.R. Whidden, Woolpert, Winter Park, Fla. (AWWA)

Producer Members

D.W. Angell,† Standards Council Liaison, American Flow Control, Birmingham, Ala. (AWWA)
S.A. Arnaout, Forterra Pressure Pipe, Dallas, Texas (AWWA)
H.H. Bardakjian, Consultant, Glendale, Calif. (AWWA)
D. Dechant, Dechant Infrastructure Service, Aurora, Colo. (AWWA)
V. DeGrande,* Ameron Water Transmission Group, Rancho Cucamonga, Calif. (AWWA)
W.B. Geyer, Steel Plate Fabricators Associates, Lake Zurich, Ill. (AWWA)
B.D. Keil, Northwest Pipe Company, Draper, Utah (AWWA)
J.L. Luka, American SpiralWeld Pipe Company, Columbia, S.C. (AWWA)
R.D. Mielke,* Northwest Pipe Company, Raleigh, N.C. (AWWA)
J. Olmos, Ameron International, Rancho Cucamonga, Calif. (AWWA)
G.F. Ruchti,* Consultant, Punta Gorda, Fla. (AWWA)
B.P. Simpson,* American Cast Iron Pipe Company, Birmingham, Ala. (AWWA)
C.C. Sundberg, Victaulic, Issaquah, Wash. (AWWA)
D. Walker, Avid Protective Products LTD/Tnemec Company, Oakville, Ont., Canada (AWWA)
J.A. Wise, Canus International Sales Inc., Surrey, B.C., Canada (AWWA)

User Members

L. Adams, US Bureau of Reclamation, Denver, Colo. (AWWA)
G.A. Andersen, New York City Bureau of Water Supply, Little Neck, N.Y. (AWWA)
B. Cheng, Metro Vancouver, Burnaby, B.C., Canada (AWWA)
M.E. Conner, San Diego County Water Authority, San Diego, Calif. (AWWA)
S. Hattan, Tarrant Regional Water District, Fort Worth, Texas (AWWA)
P.K. Karna, Tacoma Water, Tacoma, Wash. (AWWA)
T.J. Jordan,* Metropolitan Water District of Southern California, LaVerne, Calif. (AWWA)
M. McReynolds, Metropolitan Water District of Southern California, Oak Park, Calif. (AWWA)
M. Turney,* Denver Water, Denver, Colo. (AWWA)
N.A. Wigner, Los Angeles Department of Water and Power, Los Angeles, Calif. (AWWA)

* Alternate
† Liaison, nonvoting

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC. PAGE

Foreword

I Introduction vii
I.A Background vii
I.B History vii
I.C Acceptance vii
II Special Issues ix
II.A Advisory Information on Material Application ix
III Use of This Standard ix
III.A Purchaser Options and Alternatives ix
III.B Modification to Standard ix
IV Major Revisions x
V Comments x

Standard

1 General

1.1 Scope 1
1.2 Purpose 2
1.3 Application 2

2 References 2

3 Definitions 3

4 Requirements

4.1 Equipment 4
4.2 Materials and Workmanship 4
4.3 Primer 5
4.4 Polyamide Powder 5
4.5 Polyamide system application 6
4.6 Field Procedures 10

5 Verification

5.1 Polyamide System Materials Prequalification 10
5.2 Requirements of Coating and Lining Systems 11
5.3 Quality Assurance and Records 12
5.4 Inspection and Testing by the Purchaser 12
5.5 Quality Control Requirements of Applied Polyamide Systems 12
5.6 Rejection 13

6 Delivery

6.1 Marking 14
6.2 Packaging and Shipping 14
6.3 Affidavit of Compliance 14

Tables

1 Properties of Polyamide Powder Materials 5
2 Prequalification Requirements of Polyamide System 6
3 Quality Control Requirements of Applied Polyamide System 6

This page intentionally blank.

Foreword

This foreword is for information only and is not a part of ANSI/AWWA C224.*

I. Introduction.

I.A. *Background.* Polyamide (Nylon-11-based) coatings and linings are thermoplastics. Typically, they are placed by applying dry polyamide powder (ordinarily in a controlled plant environment, by any of several techniques, e.g., electrostatic spray, immersion in a fluidized bed, spray onto preheated article, or rotocoating) onto steel surfaces previously primed with a thin layer of epoxy primer (note that other primers may be used, as appropriate). When treated at the appropriate temperature, the dry polyamide powder melts to form a uniform, continuous polyamide layer on the steel surface. Simultaneously during this thermal treatment, chemical reactions occur between the steel surface and epoxy and between epoxy and polyamide. These chemical reactions provide for bonding between the polyamide and steel surface.

The first commercial use of polyamide systems for the protection (from corrosion) of steel used in water-handling applications was in West Germany in 1970. Regarding the United States, it is believed that first use was in 1985. However, prior to this, polyamide systems had been used in 1983 for the protection of the interior of steel piping used in the petroleum industry. Currently, the use of polyamides to protect steel has grown to include many types of articles (both interiors and exteriors) in a variety of industries, such as oil and natural gas exploration and production, and water and wastewater handling. Polyamide systems also can be used to protect accessory steel articles, such as pumps, valves, couplers, and flowmeters.

I.B. *History.* C224-01 was the first standard specifically concerning polyamide coating and lining systems. However, it is noted that polyamide-based systems have been used according to ANSI/AWWA Standard C550-01. The second edition of C224 was approved by the AWWA Board of Directors on Feb. 12, 2006. The third edition was approved on June 12, 2011. This edition was approved on Jan. 14, 2017.

I.C. *Acceptance.* In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the original consortium included the Water Research Foundation (formerly AwwaRF)

* American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

and the Conference of State Health and Environmental Managers (COSHEM). The American Water Works Association (AWWA) and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.* Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including

1. Specific policies of the state or local agency.

2. Two standards developed under the direction of NSF:† NSF/ANSI 60, Drinking Water Treatment Chemicals—Health Effects, and NSF/ANSI 61, Drinking Water System Components—Health Effects.

3. Other references, including AWWA standards, *Food Chemicals Codex*, *Water Chemicals Codex*,‡ and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdictions. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

Annex A, "Toxicology Review and Evaluation Procedures," to NSF/ANSI 61 does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of "unregulated contaminants" are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of Annex A procedures may not always be identical, depending on the certifier.

ANSI/AWWA C224 does not address additives requirements. Thus, users of this standard should consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.

2. Determine the status of certifications by parties offering to certify products for contact with, or treatment of, drinking water.

3. Determine current information on product certification.

---

* Persons outside the United States should contact the appropriate authority having jurisdiction.

† NSF International, 789 North Dixboro Road, Ann Arbor, MI 48105.

‡ Both publications available from National Academy of Sciences, 500 Fifth Street, NW, Washington, DC 20001.

II. Special Issues.

II.A. *Advisory Information on Material Application.* This standard defines the use of polyamide systems for the lining and coating of steel articles used for water handling in the following environments: aboveground, belowground, or underwater—under normal conditions. Also, this standard describes the quality of polyamide systems needed to produce long-term performance—in particular, long-term corrosion protection. Normal conditions are defined as those conditions specified by the polyamide system manufacturer (see Section 3) that are known beforehand not to adversely affect polyamide systems.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. *Purchaser Options and Alternatives.* The following items should be provided by the purchaser:

1. Standard used—that is, ANSI/AWWA C224, Nylon-11-Based Polyamide Coatings and Linings for Steel Water Pipe and Fittings, of latest revision
2. Any required exceptions to the standard.
3. Diameter, length, thickness, design, and location of coated steel articles.
4. For applications other than potable water, whether compliance with NSF/ANSI 61, Drinking Water System Components—Health Effects, is required.
5. Temperature (Sec. 1.1.2), pH, and composition of water to be handled.
6. Details of other federal, state or provincial, and local requirements (Sec. 4.2).
7. Weld treatment (Sec. 4.5.2.1).
8. Visual standards (Sec. 4.5.2.4).
9. Polyamide holdback at pipe ends (Sec. 4.5.3.2).
10. Polyamide thickness (Sec. 4.5.3.3).
11. Field-welded joint coating and lining (Sec. 4.5.5).
12. Pipe bedding and trench backfill (Sec. 4.6).
13. Inspection (Sec. 5.4).
14. Number of adhesion tests (Sec. 5.5.5).
15. Delivery (Section 6).
16. Outdoor storage (Sec. 6.2.2).
17. Affidavit of compliance, if required (Sec. 6.3).

III.B. *Modification to Standard.* Any modification of the provisions, definitions, or terminology in this standard must be provided by the purchaser.

IV. Major Revisions. Major changes made to the standard in this edition include the following:

1. The title of the standard was changed to be consistent with other AWWA steel pipe coating and lining standards.
2. Section 2, References, was updated.
3. The definition for *applicator* was added to Section 3, Definitions.
4. Sec. 4.2, Materials and Workmanship, was revised for consistency with the other coating and lining standards.
5. A new Sec. 4.2.2, Certification, was added to include a requirement for NSF/ANSI 61 certification on products if they will be in contact with potable water.
6. Sec. 4.5.2.3, Abrasive Blast Cleaning, was revised.
7. All existing wording in Sec. 4.6, Field Procedures, was removed. The section now references AWWA C604.
8. A new Sec. 5.2, Requirements of Coating and Lining Systems, was added that includes requirements for the polyamide material for properties, specific gravity, particle size distribution, melting point, water absorption, and inherent viscosity.
9. Sec. 5.2.2.6, Cathodic Disbondment, was updated.
10. In Sec. 5.5.3, Thickness, the reference to ASTM G12, which has been withdrawn, was replaced with ASTM D7091, which has replaced it.
11. Section 6, Delivery, was modified to be consistent with other AWWA steel pipe coating and lining standards.
12. Sec. 6.3 was modified to include affidavits from both the polyamide manufacturer and the applicator.

V. Comments. If you have any comments or questions about this standard, please call AWWA Engineering and Technical Services at 303.794.7711, FAX at 303.795.7603; write to the department at 6666 West Quincy Avenue, Denver, CO 80235-3098; or email at standards@awwa.org.