ANSI/AWWA **C228-25**

(Revision of ANSI/AWWA C228-19)

AWWA Standard

Stainless-Steel Pipe Flange Joints for Water Service—Sizes 2 In. Through 72 In. (50 mm Through 1,800 mm)

Effective date: Aug. 1, 2025.
First edition approved by Board of Directors Jan. 27, 2008.
This edition approved Jan. 23, 2025.
Approved by American National Standards Institute Jan. 15, 2025.

American Water Works Association

Approved American National Standard ANSI

STANDARD Since 1881

AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or code of any governmental authority. AWWA standards are intended to represent a consensus of the water industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed in the Official Notice section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

Caution Notice: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of ANSI approval. Purchasers of American National Standards may receive current information on all standards by writing to the American National Standards Institute, 1180 Avenue of the Americas 10th Floor, New York, NY 10036; calling 212.642.4900; or e-mailing info@ansi.org.

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including scanning, recording, or any information or retrieval system. Reproduction and commercial use of this material is prohibited, except with written permission from the publisher. Please send any requests or questions to permissions@awwa.org.

ISBN-13, print: 978-1-64717-266-4

ISBN-13, electronic: 978-1-61300-787-7

DOI: http://dx.doi.org/10.12999/AWWA.C228.25

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including scanning, recording, or any information or retrieval system. Reproduction and commercial use of this material is prohibited, except with written permission from the publisher.

Copyright © 2025 by American Water Works Association
Printed in USA

Copyright © 2025 by American Water Works Association. All Rights Reserved

Committee Personnel

The Steel Water Pipe Manufacturers Technical Advisory Committee (SWPMTAC) Task Group on ANSI/AWWA C228, which reviewed and revised this standard, had the following personnel at the time:

Mike Vanderbosch, *Chair*

S. Bradberry, Ford Meter Box Company, Inc., Pell City, Ala.
C. Boone, Romac Industries, Inc., Bothell, Wash.
R. Collins, JCM Industries, Inc., Nash, Tex.
D. DiGiallonardo, Primus Pipe & Tube, Inc., Wildwood, Fla.
C. Dodson, Smith Blair, Inc., Texarkana, Ark.
B. Ervin, Mueller Company, Cleveland, Tenn.
R. Fontes, Total Piping Solutions, Olean, N.Y.
S. Francis, Romac Industries, Inc., Bothell, Wash.
J. Grocki, Nickel Institute, Enfield, Conn.
K. Hicks, Ford Meter Box Company, Pell City, Ala.
A. Lemke, Romac Industries, Inc., Bothell, Wash.
M. Levine, Straub, Inc., Scottsdale, Ariz.
C. Littlebrant, Cascade Waterworks, Yorkville, Ill.
S. Morrison, Victaulic, Atlanta, Ga.
E. Nunes, Mueller Company, Cleveland, Tenn.
Z. Porter, Ford Meter Box Company, Pell City, Ala.
J. Reinheimer, Robar Industries Ltd., Surrey, B.C.
D. Seals, JCM Industries, Inc., Nash, Tex.
J. Tubb, JCM Industries, Inc., Nash, Tex.
M.A. Vanderbosch, CAB, Inc., Nacogdoches, Tex.
S. Withem, Smith Blair, Inc., Texarkana, Tex.

The AWWA Standards Committee on Stainless-Steel Pipe, which reviewed and approved this standard, had the following personnel at the time of approval:

J. Warren Green, *Chair*
Terri A. Tovey, *Vice-Chair*

General Interest Members

R.J. Card (*alternate*), Lockwood, Andrews & Newnam, Inc., Suwanee, Ga.
K.F. Despinoy, Stanley Consultants, Chicago, Ill.

Copyright © 2025 by American Water Works Association. All Rights Reserved

M. Garcia, AECOM, Denver, Colo.
J.W. Green, Lockwood, Andrews & Newnam, Inc., Oakbrook Terrace, Ill.
A. Gruber, STV, Inc., San Antonio, Tex.
J.E. Holzapfel, Naperville, Ill.
K.G. LeBrasse, Burns & McDonnell, Denver, Colo.
D. Mason (*liaison, nonvoting*), Standards Council Liaison, O & M Enterprises, Inc., Holden, Mo.
D.L. McPherson, HDR Engineering, Charlotte, N.C.
J. Metcalf, Dannenbaum Engineering Corp., Spring, Tex.
E.S. Ralph (*liaison, nonvoting*), Standards Engineer Liaison, AWWA, Denver, Colo.
T.A. Tovey, Jacobs Engineering, Portland, Ore.
R. Wagner (*alternate*), HDR Engineering, Dallas, Tex.

Producer Members

D. Dechant, Dechant Infrastructure Service, Aurora, Colo.
D. DiGiallonardo, Primus Pipe & Tube, Inc., Wildwood, Fla.
J.M. Grocki, Advantage Resources Consulting LLC, Hilton Head Island, S.C.
B.D. Keil, Northwest Pipe Company, Salt Lake City, Utah
A. Lemke, Romac Industries, Inc., Bothell, Wash.
R.D. Mielke (*alternate*), Northwest Pipe Company, Raleigh, N.C.
L. Prinsloo (*alternate*), Victaulic, Easton, Pa.
J. Reinheimer, Robar Industries Ltd., Surrey, B.C.
B.E. Ripley, Victaulic, Lexington, S.C.
D. Seals, JCM Industries, Inc., Nash, Tex.

User Members

L. Adams (*alternate*), US Bureau of Reclamation, Denver, Colo.
D. Hughes, Denver Water, Denver, Colo.
B.R. Osborne, Clark County Public Works, Las Vegas, Nev.
B.K. Powell, Green Bay Water Utility, Green Bay, Wis.
V. Price, City of Houston, Houston, Tex.
R. Schlosser, US Bureau of Reclamation, Denver, Colo.
D. Stickel, Saginaw-Midland Municipal Water, Bay City, Mich.
S. Sweis, San Diego County Water Authority, San Diego, Calif.

Copyright © 2025 by American Water Works Association. All Rights Reserved

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC. PAGE

Foreword

I Introduction vii
I.A Background vii
I.B History vii
I.C Acceptance ix
II Special Issues xi
II.A Chlorine and Chloramine Degradation of Elastomers xi
II.B Gasket Degradation Study xi
III Use of This Standard xi
III.A Purchaser Options and Alternatives xi
III.B Modification to Standard xii
IV Major Revisions xii
V Comments xiii

Standard

1 General

1.1 Scope 1
1.2 Purpose 1
1.3 Application 1

2 References 2

3 Definitions 3

4 Requirements

4.1 Materials 5
4.2 Fabrication 8
4.3 Attachment of Flanges 12

5 Verification

5.1 Inspection by the Purchaser 14
5.2 Quality Assurance 15

6 Delivery

6.1 Markings 15
6.2 Affidavit of Compliance 15

Appendixes

A Bibliography 17
B Postfabrication Cleaning of Stainless Steels 19

Figures

1 Attachment of Flange 12
2 Draft or Layback Measurement 13
3 Negative Draft or Layback 13

Tables

1 Flange Gasket Materials, Type, and Thickness 7
2 AWWA Standard Stainless-Steel Ring Flanges (Class SA–Class SE) 9
3 AWWA Standard Stainless-Steel Ring Flanges (Class SF) 10
4 AWWA Standard Stainless-Steel Blind Flange Thickness (Class SA–Class SF) 11

Copyright © 2025 by American Water Works Association. All Rights Reserved

This page intentionally blank.

Copyright © 2025 by American Water Works Association. All Rights Reserved

Foreword

This foreword is for information only and is not a part of ANSI/AWWA C228.*

I. Introduction.

I.A. *Background*. Stainless steel is a standard material used to construct piping and flanges. It offers very low corrosion rates, which makes it suitable for the handling of potable water while maintaining purity and quality.

I.B. *History*. In 1945, at the request of the American Society of Mechanical Engineers (ASME),† a committee having representatives from both ASME and AWWA was formed. The ASME/AWWA committee was charged with establishing standards for steel flanges having dimensions and pressure ratings commensurate with the pressures commonly used in water service. The standards were necessary because the lowest pressure ratings for steel flanges at that time were those having cold-water pressure ratings of 275 psi (1,896 kPa) (ASME B16.5, Pipe Flanges and Flanged Fittings) or 150-psi (1,034-kPa) primary pressure ratings. The ratings were far higher than those ordinarily needed for water service.

Generally accepted practice for the design of bolted flange connections considers all fields of usage and a wide range of pressure and temperature applications. In waterworks practice, it is not necessary, within the scope of this standard, to deal with temperatures greater than the atmospheric range, and it is possible to limit the scope of consideration to gaskets contained in this standard and to flanges that are flat faced. The designs were prepared in conformity with these limitations for carbon steel and first adopted in 1952. In 1999, AWWA developed a new standard for stainless-steel pipe, which then required a new standard for stainless-steel flanges.

In 1999, the AWWA Standards Council directed the Standards Committee on Steel Pipe to develop a standard for stainless-steel flanges used in water treatment and conveying facilities. In 2003, the Standards Council approved the formation of the Standards Committee on Stainless-Steel Pipe, which assumed responsibility for the development of this standard. The first edition of this standard was approved by the AWWA Board of Directors on Jan. 27, 2008. Subsequent editions were approved on June 8, 2014, and Jan. 24, 2019. This edition was approved on Jan. 23, 2025.

* American National Standards Institute, 1180 Avenue of the Americas, 10th Floor, New York, NY 10036.

† ASME, Two Park Avenue, New York, NY 10016.

Copyright © 2025 by American Water Works Association. All Rights Reserved

The original ASME/AWWA committee gave careful consideration to the following: (1) the effect of new standards on existing equipment; (2) the fact that cast valves and fittings will always have flanges of large outside diameter that cannot be reduced because of the wall thickness of this equipment; (3) the need for interchangeability of equipment through the use of common drilling patterns; and (4) the fact that standards could be based on the successful usage and good service records of existing installations.

A survey of water utility users indicated that it was desirable to maintain the outside diameter and drilling of flanged fittings and valves given in ANSI/AWWA C500, Gate Valves for Water and Sewerage Systems, and ANSI/ASME B16.1, Cast Iron Pipe Flanges and Flanged Fittings (for classes 25, 125, 250, and 800). The committee decided to follow this practice for sizes 6 in. through 48 in. (150 mm through 1,200 mm).

In its extensive deliberations, the ASME/AWWA committee had available the results of special research and testing conducted by ARMCO Steel Corporation, Bethlehem Steel Company, and Taylor Forge & Pipe Works. The various design methods and test results were given in *Steel Ring Flanges for Steel Pipe*, ARMCO Bulletin 47A (1947), from the American Rolling Mill Company, Middletown, Ohio. The design of flanges for waterworks service, with the results of the preceding report, was published in *Journal AWWA* in October 1950, pp. 931–939. A discussion in the paper by Taylor Forge & Pipe Works, participant in the ASME/AWWA committee, stated the reasons why a waterworks flange is not an ASME/Taylor Forge flange. Concern about high secondary stresses at the attachment, e.g., thick material to thin wall pipe, was covered there along with the published "Design of Wye Branches for Steel Pipe" (*Journal AWWA*, June 1955, Appendix C, pp. 581–630).

Beginning in 2006, a special flange task group investigated development history of the flange dimensions found within the standard. After five years of research, the task group reached the following conclusions.

1. There is no one exact stress-based design method that could reproduce the thickness values in the standard tables. However, it appears that the ring flange thicknesses in this standard are based on using the LaTour-Barnard design procedure (ARMCO Bulletin 47A, 1947) for ring flanges, which is based on ASME integral flange design procedures.

2. A current design analysis was performed based on the LaTour-Barnard proposed design method (which was based on physical tests on pipes with steel ring flanges) that demonstrated comparable results. It is worthwhile to mention that the original LaTour-Barnard design procedure was a bending stress design methodology.

Copyright © 2025 by American Water Works Association. All Rights Reserved

3. It has been established that flange thickness design based solely on a stress-based design procedure is incorrect. In R. Barnard's October 1950 *Journal AWWA* article, he wrote, "When the test results were analyzed, it became obvious that the design formulas used in establishing American Standard flange dimensions predicted fantastically high localized stresses even when the joint assembly performed satisfactorily. Since a method of designing by test was being sought, a reconciliation of the apparent contradictions between theory and test results had to be explored. To find the answer, attention was turned to the behavior under load of the steel being tested in pipe wall and flange. Also, the stress factors in the formulas were further examined to discover whether or not a different concept of design would compose the apparent differences between theory and test results. It was found that theory fits the data when the concept of calculated stress level design is displaced by a concept of limiting-strain design. Then there was good correlation between theory, the test results, and past field experience and practice." Simply put, the design of flange thickness was performed as a limiting strain type of design procedure and not based on stress. The limiting strain was 5,000 μin./in. as determined by the 0.5 percent load extension method.

4. Many steel ring flanges have been supplied with thicknesses and dimensions that match the tables herein since these initial investigations were performed in the 1940s and 1950s by the ASME/AWWA committees leading up to the first edition of AWWA C207—Steel Pipe Flanges for Waterworks Service, Sizes 4 In. Through 144 In. (100 mm Through 3,600 mm). As Barnard wrote in 1950, "The primary aim in flange design should be to prevent joint leakage since steel flange joints do not fail by fracture." The flange task group found this to be true over the past 70 years, as there have been no reported occurrences of steel flanges fracturing when servicing the pressure that they were supplied to meet.

5. The determination of the steel cylinder thickness at the flange attachment to be used in this standard is based on the design procedures for internal pressures shown in AWWA M11 *Steel Pipe: A Guide for Design and Installation*. This practice is deemed acceptable, based on empirical data of successful performance dating back to the early 1950s.

Tables 2 and 3 of this standard are based on historical dimensions and are presented without additional calculations.

I.C. *Acceptance*. In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of

Copyright © 2025 by American Water Works Association. All Rights Reserved

the original consortium included the Water Research Foundation (formerly AwwaRF) and the Conference of State Health and Environmental Managers (COSHEM). AWWA and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in or in contact with drinking water rests with individual states.[‡] Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including

1. Specific policies of the state or local agency.

2. Four standards developed under the direction of NSF:[§] NSF/ANSI/CAN[¶] 60, Drinking Water Treatment Chemicals—Health Effects; NSF/ANSI/CAN 61, Drinking Water System Components—Health Effects; NSF/ANSI/CAN 372, Drinking Water System Components—Lead Content; and NSF/ANSI/CAN 600, Health Effects Evaluation and Criteria for Chemicals in Drinking Water.

3. Other references, including AWWA standards, *Food Chemicals Codex, Water Chemicals Codex*,[**] and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI/CAN 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdictions. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

NSF/ANSI/CAN 600 (which formerly appeared in NSF/ANSI/CAN 60 and 61 as Annex A, "Toxicology Review and Evaluation Procedures") does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of "unregulated contaminants" are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of NSF/ANSI/CAN 600 procedures may not always be identical, depending on the certifier.

ANSI/AWWA C228 does not address additives requirements. Thus, users of this standard should consult the appropriate state or local agency having jurisdiction in order to

---

[‡] Persons outside the United States should contact the appropriate authority having jurisdiction.

[§] NSF International, 789 North Dixboro Road, Ann Arbor, MI 48105.

[¶] Standards Council of Canada, 55 Metcalfe Street, Suite 600, Ottawa, ON K1P 6L5 Canada.

[**] Both publications available from National Academies Press, 500 Fifth Street, NW, Washington, DC 20001.

Copyright © 2025 by American Water Works Association. All Rights Reserved

1. Determine additives requirements, including applicable standards.

2. Determine the status of certifications by parties offering to certify products for contact with or treatment of drinking water.

3. Determine current information on product certification.

II. Special Issues. Thickness and dimensional design of ring flanges have been based on references given in the history section of this foreword, as well as on industry standards and other empirical data. Thickness design of the blind flanges has been based on the ASME Code Design Method. For hub-flange applications, refer to ASME B16.47 and B16.5.

II.A. *Chlorine and Chloramine Degradation of Elastomers.* The selection of materials is critical for water service and distribution piping in locations where there is a possibility that elastomers will be in contact with chlorine or chloramines. Documented research has shown that elastomers such as gaskets, seals, valve seats, and encapsulations may be degraded when exposed to chlorine or chloramines. The impact of degradation is a function of the type of elastomeric material, chemical concentration, contact surface area, elastomer cross-section, environmental conditions, as well as temperature. Careful selection of and specifications for elastomeric materials and the specifics of their application for each water system component should be considered to provide long-term usefulness and minimum degradation (swelling, loss of elasticity, or softening) of the elastomer specified.

II.B. *Gasket Degradation Study*. A pipe gasket, having the hardness of a compressed fiber with a large mass relative to the small exposed surfaced area, experiences minimal degradation. This was validated in a 2004 research paper published in *Journal AWWA*,[††] in which the pipe gasket degradation in a 110-mg/L chloramine solution was found to degrade just the exposed surface.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. *Purchaser Options and Alternatives*. The following items should be provided by the purchaser:

1. Standard used—that is, ANSI/AWWA C228, Stainless-Steel Pipe Flange Joints for Water Service—Sizes 2 In. Through 72 In. (50 mm Through 1,800 mm), of latest edition.

[††] Bonds, R.W. 2004. "Effect of Chloramines on Ductile-iron Pipe Gaskets of Various Elastomer Compounds." *Journal AWWA*, 96(4):153–160.

Copyright © 2025 by American Water Works Association. All Rights Reserved

2. Whether compliance with NSF/ANSI/CAN 61, Drinking Water System Components—Health Effects, is required.

3. Details of federal, state, provincial, territorial, and local requirements (Sec. 4.1.1).

4. Mill test certification (Sec. 4.1.3.5).

5. Class of flange required (Tables 2, 3, and 4).

6. Inside diameter (ID) of flanges (Tables 2 and 3).

7. Gasket ID and type, elastomeric (rubber), compressed fiber gasket (CFG), or polytetrafluoroethylene (PTFE)-based (Sec. 4.1.5) and gasket thickness.

8. Affidavit of compliance, if required (Sec. 6.2).

III.B. *Modification to Standard*. Any modification of the provisions, definitions, or terminology in this standard must be provided by the purchaser.

IV. Major Revisions. Major revisions made to the standard in this edition include the following:

1. Updated Sec. I.C. Acceptance in the Foreword with the latest Standards Council language reflecting the addition of reference to NSF/ANSI/CAN 372 and NSF/ANSI/CAN 600.

2. Revised Sec. II. Special Issues in the Foreword to match the wording used in AWWA C207 for consistency.

3. Added "gasket ID" to Purchasers Options in III.A, Item 7 of the Foreword.

4. Added a reference to AWWA M11 in Sec. 1.3 Application.

5. Sec. 1.3.3 Flange design was revised.

6. The terms *Reclaimed water* and *Wastewater* were added to Section 3, Definitions.

7. Updated Sec. 4.1.1 Materials and Sec. 4.1.2 Permeation with the latest Standards Council boilerplate language.

8. Revised Sec. 4.1.4 Fasteners for clarity and consistency with AWWA C207.

9. Revised wording to improve clarity pertaining to gasket assembly stress value in Sec. 4.1.5.

10. Corrected wording at the bottom of Table 2 pertaining to dimensions in common with Class 125 gray iron flanges and ASME 16.5 150 psi flanges.

11. Corrected wording at the bottom of Table 3 pertaining to dimensions in common with the flanges in this table.

12. Bolt diameter for 22 in. flange in Table 3 corrected to 1.50 in.

Copyright © 2025 by American Water Works Association. All Rights Reserved

13. Added the ANSI/AWWA C207 Appendix A, Bibliography (with the addition of the 2009 ASCE Pipelines Bambei and Green paper) as the new ANSI/AWWA C228 Appendix A.

14. Added the ANSI/AWWA C231 Appendix B, Postfabrication Cleaning of Stainless Steels, as the new ANSI/AWWA C228 Appendix B.

V. Comments. If you have any comments or questions about this standard, please call AWWA Engineering and Technical Services Department at 303.794.7711; write to the department at 6666 West Quincy Avenue, Denver, CO 80235-3098; or e-mail at standards@awwa.org.

Copyright © 2025 by American Water Works Association. All Rights Reserved

This page intentionally blank.

Copyright © 2025 by American Water Works Association. All Rights Reserved

American Water Works Association

ANSI/AWWA C228-25
(Revision of ANSI/AWWA C228-19)

AWWA Standard

Stainless-Steel Pipe Flange Joints for Water Service—Sizes 2 In. Through 72 In. (50 mm Through 1,800 mm)

SECTION 1: GENERAL

Sec. 1.1 Scope

This standard describes stainless-steel, ring-type, slip-on flanges and blind flanges for use in conjunction with stainless-steel pipe used in facilities of waterworks service.

Sec. 1.2 Purpose

The purpose of this standard is to provide minimum material requirements and dimensions for a variety of stainless-steel flanges for attachment to stainless-steel piping systems.

Sec. 1.3 Application

1.3.1 *Intended use*. Flanges in this standard are described in the following tables:

1. Table 2 and Table 3, ring-type slip-on flanges
2. Table 4, blind flanges

Flanges covered in this standard are intended for use with stainless-steel pipe or appurtenances meeting the requirements of AWWA M11, ANSI/AWWA C220,

Copyright © 2025 by American Water Works Association. All Rights Reserved