PD ISO/TR 17881-3:2018



BSI Standards Publication

Textiles — Determination of certain flame retardants

Part 3: Chlorinated paraffin flame retardants

bsi.

National foreword

This Published Document is the UK implementation of ISO/TR 17881-3:2018.

The UK participation in its preparation was entrusted to Technical Committee TCI/80, Chemical testing of textiles.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2018
Published by BSI Standards Limited 2018

ISBN 978 0 580 98893 6

ICS 59.080.01

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 March 2018.

Amendments/corrigenda issued since publication

Date	Text affected

PD ISO/TR 17881-3:2018

TECHNICAL REPORT

ISO/TR 17881-3

First edition
2018-03-21

Textiles — Determination of certain flame retardants —

Part 3: Chlorinated paraffin flame retardants

Textiles — Détermination de certains retardateurs de flamme — Partie 3: Retardateurs de flamme à base de paraffines chlorées

Reference number
ISO/TR 17881-3:2018(E)

© ISO 2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword ..... **iv**
1 Scope **1**
2 Normative references **1**
3 Terms and definitions **1**
4 Principle **1**
5 Reagents **1**
6 Apparatus **2**
7 Procedure **3**
7.1 Preparation of standard solutions 3
7.1.1 Stock standard solutions 3
7.1.2 Working solutions 3
7.2 Specimen extraction 3
7.2.1 Ultrasonic wave extraction 3
7.2.2 Purification 3
7.3 Pretesting by GC-ECD 4
7.4 Determination by GC-FID 4
8 Calculation **4**
8.1 Pretesting result obtained by GC-ECD 4
8.2 Quantity of SCCPs obtained by GC-FID 4
9 Detection limit **5**
10 Test report **5**
Annex A (informative) **Test parameters for GC-ECD** **6**
Annex B (informative) **Test parameters for GC-FID** **10**

© ISO 2018 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*.

A list of all parts in the ISO 17881 series can be found on the ISO website.

© ISO 2018 – All rights reserved

TECHNICAL REPORT **ISO/TR 17881-3:2018**

Textiles — Determination of certain flame retardants —

Part 3: Chlorinated paraffin flame retardants

WARNING — The use of this document can involve hazardous substances and/or procedures. It refers only to technical suitability and does not purport to address all of the health and safety risks associated with its use. It is the responsibility of users of this document to take appropriate measures to ensure the safety and health of personnel and the environment prior to application of the document, and it is assumed that the execution of its provisions is entrusted to appropriately qualified and experienced people.

1 Scope

This document describes a method for determining short-chain chlorinated paraffins (C_{10}-C_{13}) (SCCPs) in textiles using carbon skeleton reaction gas chromatography with a flame ionization detector (GC-FID).

It is applicable to all kinds of textile products.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— IEC Electropedia: available at https://www.electropedia.org/

— ISO Online browsing platform: available at https://www.iso.org/obp

4 Principle

SCCPs are extracted from textile specimens by an ultrasonic generator with *n*-hexane/acetone. SCCPs are pretested by gas chromatography with an electron capture detector (GC-ECD) and then quantified by GC-FID using an external standard method. SCCPs are dechlorinated by reacting with hydrogen to generate straight-chain alkane (C_{10}-C_{13}) under the action of a $PdCl_2$ catalyst. GC-FID is used to determine the quantity of straight-chain alkane following an external standard method, and then the quantity of SCCPs is calculated.

5 Reagents

Unless otherwise specified, only reagents of recognized analytical grade are used.

5.1 Short-chain chlorinated paraffins (SCCPs) (C_{10}-C_{13}, 51,5 % Cl), 100 µg/ml in cyclohexane.

5.2 Short chain chlorinated paraffins (SCCPs) (C_{10}-C_{13}, 55,5 % Cl), 100 µg/ml in cyclohexane.

5.3 Short-chain chlorinated paraffins (SCCPs) (C_{10}-C_{13}, 63 % Cl), 100 µg/ml in cyclohexane.

© ISO 2018 – All rights reserved