PD ISO/TS 23151:2021



BSI Standards Publication

Nanotechnologies — Particle size distribution for cellulose nanocrystals

bsi.

National foreword

This Published Document is the UK implementation of ISO/TS 23151:2021.

The UK participation in its preparation was entrusted to Technical Committee NTI/1, Nanotechnologies.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

This publication is not to be regarded as a British Standard.

© The British Standards Institution 2021
Published by BSI Standards Limited 2021

ISBN 978 0 539 14472 7

ICS 07.120

Compliance with a Published Document cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 October 2021.

Amendments/corrigenda issued since publication

Date	Text affected

PD ISO/TS 23151:2021

TECHNICAL SPECIFICATION

ISO/TS 23151

First edition
2021-09

Nanotechnologies — Particle size distribution for cellulose nanocrystals

Nanotechnologies — Distribution en taille des particules pour les nanocristaux de cellulose

Reference number
ISO/TS 23151:2021(E)

© ISO 2021



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

© ISO 2021 – All rights reserved

Contents

Page

Foreword ... **iv**
Introduction ... **v**
1 Scope ... **1**
2 Normative references ... **1**
3 Terms and definitions ... **1**
4 Abbreviated terms ... **2**
5 Dispersion of CNCs ... **2**
5.1 General considerations ... 2
5.2 Dispersion of CNCs by sonication ... 3
5.3 Dynamic light scattering assessment of dispersions ... 4
5.4 Determination of optimal sonication energy ... 5
6 Sample preparation for microscopy ... **5**
6.1 General considerations ... 5
6.2 AFM sample preparation ... 6
6.3 TEM sample preparation ... 6
7 Atomic force microscopy ... **6**
7.1 General ... 6
7.2 Instrumentation and accessories ... 7
7.3 Microscope calibration ... 7
7.4 Data acquisition ... 7
7.5 Image analysis ... 8
8 Transmission electron microscopy ... **8**
8.1 General ... 8
8.2 Instrumentation and accessories ... 9
8.3 Microscope calibration ... 9
8.4 Data acquisition ... 9
8.5 Image analysis ... 9
9 Data analysis ... **10**
9.1 General ... 10
9.2 Assessment of data quality ... 10
9.3 Fitting distribution models to data ... 10
9.4 Measurement uncertainty ... 11
10 Test report ... **12**
10.1 Atomic force microscopy ... 12
10.1.1 General information ... 12
10.1.2 Sample ... 12
10.1.3 Data acquisition ... 12
10.1.4 Image analysis ... 13
10.2 Transmission electron microscopy ... 13
10.2.1 General information ... 13
10.2.2 Sample ... 13
10.2.3 Data acquisition ... 13
10.2.4 Image analysis ... 14
Annex A (informative) **Assessment of CNC dispersions** ... **15**
Annex B (informative) **Assessment of applied imaging force** ... **16**
Annex C (informative) **Interlaboratory comparison results: AFM** ... **18**
Annex D (informative) **Interlaboratory comparison results: TEM** ... **25**
Bibliography ... **34**

© ISO 2021 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 229, *Nanotechnologies*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html and www.iec.ch/national-committees.

© ISO 2021 – All rights reserved

Introduction

Cellulose nanomaterials, including cellulose nanocrystals (CNCs) and cellulose nanofibrils, are anticipated to have significant commercial impact. Cellulose nanocrystals are produced from naturally occurring cellulose, primarily from wood pulps and annual plants, by acid hydrolysis. Their production from readily available cellulose sources makes them a candidate for use as a potentially non-toxic, biodegradable and sustainable nanomaterial. The recent demonstration of the feasibility of large-scale CNC production and the availability of infrastructure for harvesting raw materials will facilitate their commercial development. CNCs and cellulose nanofibrils are produced in a number of countries on pilot, pre-commercial or commercial scales. Estimates of the market potential for cellulosic nanomaterials are as high as 35 million metric tons annually, depending on the predicted applications and the estimated market penetration[10],[11]. Standards for characterization of CNCs are required for material certification to facilitate sustained commercial and applications development.

Cellulose nanocrystals have high crystallinity and are nanorods with high aspect ratio, surface area and mechanical strength. They assemble to give a chiral nematic phase with unique optical properties and their surface chemistry can be modified to ensure colloidal stability in water and to facilitate dispersion in a variety of matrices. These properties, plus their biocompatibility, low cost and minimal toxicity, enable many potential applications. Industrial producers are working with receptor industries in various application areas, including nanocomposite materials, health and personal care products, paints, adhesives and thin films, rheology modifiers and optical films and devices. Standardization activities within ISO/TC 229 and ISO/TC 6 have focused on nomenclature and terminology, characterization methods in general and specific methods for determining surface functional groups, metal ion and dry ash content. Particle size distribution is also a key property for CNC characterization. Particle morphology and size distribution control some properties of individual CNCs and contribute in part to their organization in suspensions, dry films and matrices. These properties and chemical characteristics determine CNC colloidal stability, viscosity and self-assembly, as well as performance in applications (e.g. reinforcement of nanocomposites). Length distribution may also be used to differentiate among cellulose nanocrystal grades or products.

This document describes a method for reproducibly dispersing dry CNCs for preparation of microscopy samples, provides image acquisition protocols for atomic force and transmission electron microscopy and summarizes image analysis procedures for determining particle size distributions. The methods are compatible with analysis of CNCs as produced by several processes and can be extended to surface modified CNCs with adjustment of dispersion and sample deposition methods. The two microscopy methods provide complementary information, and both have been widely used for size analysis of CNCs.

© ISO 2021 – All rights reserved

Nanotechnologies — Particle size distribution for cellulose nanocrystals

1 Scope

This document describes methods for the measurement of particle size distributions for cellulose nanocrystals using atomic force microscopy and transmission electron microscopy. The document provides a protocol for the reproducible dispersion of the material using ultrasonication, as assessed using dynamic light scattering. Sample preparation for microscopy, image acquisition and data analysis are included.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/TS 80004-2, *Nanotechnologies — Vocabulary — Part 2: Nano-objects*

ISO 21363:2020, *Nanotechnologies — Measurements of particle size and shape distributions by transmission electron microscopy*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO/TS 80004-2 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

3.1
cellulose nanocrystal
nanocrystal predominantly composed of cellulose with at least one *elementary fibril* (3.3), containing predominantly crystalline and paracrystalline regions, with an aspect ratio of usually less than 50 but usually greater than 5, not exhibiting longitudinal splits, inter-particle entanglement, or network-like structures

Note 1 to entry: The dimensions are typically 3 nm to 50 nm in cross-section and 100 nm to several µm in length depending on the source of the cellulose nanocrystal.

Note 2 to entry: The aspect ratio refers to the ratio of the longest to the shortest dimension.

Note 3 to entry: Historically cellulose nanocrystals have been called nanocrystalline cellulose (NCC), whiskers such as cellulose nanowhiskers (CNW), and microfibrils such as cellulose microfibrils; they have also been called spheres, needles or nanowires based on their shape, dimensions and morphology; other names have included cellulose micelles, cellulose crystallites and cellulose microcrystals.

[SOURCE: ISO/TS 20477:2017]

© ISO 2021 – All rights reserved