INTERNATIONAL STANDARD

ISO 19940

First edition
2017-11

Tyre stiffness index testing procedure for passenger car extended mobility and run flat tyres

Procédure d'essai de l'indice de rigidité de pneumatiques à mobilité étendue et pour roulage à plat pour voiture particulière

Reference number
ISO 19940:2017(E)

© ISO 2017



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

 © ISO 2017 – All rights reserved

Contents

Page

Foreword ... **iv**

1 Scope ... **1**

2 Normative references ... **1**

3 Terms and definitions ... **1**

4 Test method ... **3**

4.1 General ... 3

4.2 Inflated tyre — Vertical stiffness measurement ... 4

4.2.1 Tyre inflation pressure ... 4

4.2.2 Tyre positioning ... 4

4.2.3 Rims ... 4

4.2.4 Equipment minimum requirements ... 4

4.2.5 Machine set-up ... 4

4.2.6 Maximum testing load ... 5

4.2.7 Procedure ... 5

4.3 Zero inflation pressure tyre — Structural stiffness determination ... 6

4.3.1 General ... 6

4.3.2 Mathematical model of the vertical forces ... 7

4.3.3 Quality of the approximation ... 8

4.3.4 Mathematical model of the total stiffness ... 8

4.3.5 Deflection calculation ... 8

4.3.6 Structural stiffness calculation ... 9

4.4 Structural part of the TSI ... 9

4.5 Air part of the TSI ... 10

4.6 Tyre stiffness index (TSI) calculation ... 10

Annex A (informative) **Test report example** ... **12**

Bibliography ... **13**

© ISO 2017 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 31, *Tyres, rims and valves*, Subcommittee SC 3, *Passenger car tyres and rims*.

© ISO 2017 – All rights reserved

Tyre stiffness index testing procedure for passenger car extended mobility and run flat tyres

1 Scope

This document specifies the testing method for determining the tyre stiffness index of passenger car tyres for the products capable of supplying the vehicle with the basic tyre functions, at least, at a speed of 80 km/h (50 mph) and a distance of 80 km when operating in flat tyre running mode, as per ISO 16992.

This method is meant to determine the above mentioned index, for the characterization of the expected tyre's stiffness through its air and structural components.

To reach the target, the vertical force and the vertical deflection, in the sense of absolute position in *Z* direction under different operating conditions, are measured (approximated in case of zero inflation pressure) and combined through the metrics defined in this document.

This method is not intended to be used for conventional tyres.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4000-1, *Passenger car tyres and rims — Part 1: Tyres (metric series)*

ISO 4000-2, *Passenger car tyres and rims — Part 2: Rims*

ISO 16992, *Passenger car tyres — Spare unit substitutive equipment (SUSE)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

3.1
conventional tyre
pneumatic tyre designed for use in an inflated state

3.2
run flat tyre
self supporting tyre
SST
pneumatic tyre structure provided with any technical solutions (for example, reinforced sidewalls, etc.) designed to operate in an inflated mode and allowing the tyre, mounted on the appropriate wheel and in the absence of any supplementary component, to supply the vehicle with the basic tyre functions at a specified speed and distance when operating in flat tyre running mode

© ISO 2017 – All rights reserved

3.3
extended mobility tyre
EMT
pneumatic tyre featuring technology designed on purpose to operate in an inflated mode and allowing the tyre, mounted on the appropriate wheel and in the absence of any supplementary component, to supply the vehicle with the basic tyre functions at a specified speed and distance when operating in flat tyre running mode

3.4
test rim
rim on which a tyre is required to be fitted for testing

3.5
inflation pressure
pressure taken with the tyre at ambient temperature, as indicated by the tyre manufacturer and which does not include any pressure build-up due to tyre usage

3.6
zero inflation pressure running mode
state of the tyre while operating in deflated condition, obtained by removing the valve-core

3.7
speed symbol
code signifying the maximum speed at which the tyre can carry a load corresponding to its *load index* (3.8) under service conditions specified by the tyre manufacturer

Note 1 to entry: Refer to ISO 4000-1:2015, Table 3.

3.8
load index
LI
numerical code associated to the maximum load that a tyre can carry at the speed indicated by its *speed symbol* (3.7) under service conditions specified by the tyre manufacturer

Note 1 to entry: Refer to ISO 4000-1:2015, Table 2.

3.9
loading force
F_Z
force measured during the loading condition (either in wheel spindle axle or in the loading plate), in the loading direction

3.10
loading speed
v_L
speed used to apply the load on the tyre

3.11
absolute position
z
position of either the tyre or the loading plate

Note 1 to entry: Absolute position is expressed in mm.

3.12
reference inflation pressure
P_{ref}
inflation pressure (3.5) to be used as a first step in testing conditions

Note 1 to entry: See Table 1.

© ISO 2017 – All rights reserved

3.13
test inflation pressure
P_i
inflation pressure (3.5) at each step "*i*"

Note 1 to entry: Inflation pressure is expressed in kPa.

3.14
vertical stiffness
K_Z
tyre stiffness measured under vertical force input in inflated conditions

Note 1 to entry: Vertical stiffness is expressed in N/mm.

3.15
total stiffness
K_{tot}
tyre characteristic linked to tyre *structural stiffness* (3.16) and *air stiffness* (3.17), for each test inflation pressure value

Note 1 to entry: In case the test inflation pressure is P_{ref} (3.12), then K_{tot} is equal to tyre's *vertical stiffness*, K_Z (3.14).

3.16
structural stiffness
K_{str}
tyre *vertical stiffness* (3.14) measured in "zero i.p. running mode"

Note 1 to entry: Structural stiffness is expressed in N/mm.

Note 2 to entry: It is a function of the tyre's construction and technological content.

3.17
air stiffness
K_{air}
tyre characteristic, calculated as the difference between tyre *vertical stiffness* (3.14) and tyre *structural stiffness* (3.16)

Note 1 to entry: Air stiffness is expressed in N/mm.

Note 2 to entry: It is a function of the air volume and the *inflation pressure* (3.5) of the tyre itself.

3.18
deflection
S_Z
vertical displacement of the plate in the z direction

3.19
tyre diameter offset
IG
change of the outer diameter due to the inflation of the tyre

4 Test method

4.1 General

Tyres, to be considered run flat tyre or self-supporting tyre (SST) or extended mobility tyre (EMT) shall successfully complete the related endurance tests as described in ISO 16992.

© ISO 2017 – All rights reserved