IEC 60216-5

Edition 4.0 2022-11

INTERNATIONAL STANDARD

NORME INTERNATIONALE

colour inside

Electrical insulating materials – Thermal endurance properties – Part 5: Determination of relative temperature index (RTI) of an insulating material

Matériaux isolants électriques – Propriétés d'endurance thermique – Partie 5: Détermination de l'indice de température relatif (ITR) d'un matériau isolant



IEC 60216-5:2022-11 (en-fr)



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2022 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Secretariat
3, rue de Varembé
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC
The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications
The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform
The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, …). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished
Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc
If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch
Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org
The world's leading online dictionary on electrotechnology, containing more than 22 300 terminological entries in English and French, with equivalent terms in 19 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

A propos de l'IEC
La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC
Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Recherche de publications IEC - webstore.iec.ch/advsearchform
La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études, …). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished
Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

Service Clients - webstore.iec.ch/csc
Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch
Découvrez notre puissant moteur de recherche et consultez gratuitement tous les aperçus des publications. Avec un abonnement, vous aurez toujours accès à un contenu à jour adapté à vos besoins.

Electropedia - www.electropedia.org
Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 300 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 19 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

IEC 60216-5

Edition 4.0 2022-11

INTERNATIONAL STANDARD

NORME INTERNATIONALE

colour inside

Electrical insulating materials – Thermal endurance properties – Part 5: Determination of relative temperature index (RTI) of an insulating material

Matériaux isolants électriques – Propriétés d'endurance thermique – Partie 5: Détermination de l'indice de température relatif (ITR) d'un matériau isolant

INTERNATIONAL ELECTROTECHNICAL COMMISSION

COMMISSION ELECTROTECHNIQUE INTERNATIONALE

ICS 19.020; 29.020; 29.035.01

ISBN 978-2-8322-6014-2

Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

® Registered trademark of the International Electrotechnical Commission
Marque déposée de la Commission Electrotechnique Internationale

CONTENTS

FOREWORD 4
1 Scope 6
2 Normative references 6
3 Terms, definitions, symbols and units 7
3.1 Terms and definitions 7
3.2 Symbols and units 8
4 Objectives of RTI determination 10
5 Experimental procedures 10
5.1 Selection of reference EIM 10
5.2 Selection of diagnostic test for extent of ageing 10
5.3 Ageing procedures 10
6 Calculation procedures 11
6.1 Thermal endurance data – Calculation of intermediate parameters 11
6.2 Calculation of RTI 12
6.3 Statistical and numerical tests 13
6.3.1 Tests of IEC 60216-3 13
6.3.2 Precision of correlation time 13
6.3.3 Lower confidence interval of RTI 13
6.3.4 Extrapolation 14
7 Results and report 14
7.1 Results of statistical and numerical tests 14
7.2 Results 14
7.3 Report 15
8 Material testing by short-term thermal ageing 15
9 Insulation classification 16
Annex A (informative) Repeatability of correlation time 17
A.1 Overview 17
A.2 F-test for linearity 17
A.3 Standard error of the difference of two means 17
A.4 Student's t-test for difference of two means 18
A.5 Combination of data 19
Annex B (informative) Thermal class assignment 20
Annex C (informative) Computer program 23
C.1 General 23
C.1.1 Overview 23
C.1.2 Convenience program execution 24
C.2 Structure of data files used by the program 25
C.3 Executing the calculation of RTI 26
C.4 Output files and graph 26
Annex D (informative) Selection of the reference EIM 28
D.1 Overview 28
D.2 Designation of reference EIM 28
D.3 Reporting items for reference EIM 28
Bibliography 29

Figure 1 – Thermal endurance graphs 11
Figure 2 – Unacceptable thermal endurance graphs 11
Figure C.1 – Shortcut property dialog for program launch 25
Figure C.2 – Thermal endurance graphs 26
Figure C.3 – Example thermal endurance graphs 27

Table 1 – Input parameters for the calculations concerning RTI 12
Table B.1 – Thermal class equivalents for insulating material 20
Table B.2 – F– function; p = 0,05 21
Table B.3 – t–function 22

INTERNATIONAL ELECTROTECHNICAL COMMISSION

_____

ELECTRICAL INSULATING MATERIALS – THERMAL ENDURANCE PROPERTIES –

Part 5: Determination of relative temperature index (RTI) of an insulating material

FOREWORD

1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
6) All users should ensure that they have the latest edition of this publication.
7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 60216-5 has been prepared by IEC technical committee 112: Evaluation and qualification of electrical insulating materials and systems. It is an International Standard.

This fourth edition cancels and replaces the third edition published in 2008. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

a) Annex C "Computer program" has been completely reworked;
b) in 3.1, the terms "ATE" and "RTE" were replaced by "ATI" and "RTI" to emphasize their reference to an electrical insulating material (EIM).

This standard is to be read in conjunction with IEC 60216-1:2013, IEC 60216-2:2005 and IEC 60216-3:2021.

The text of this International Standard is based on the following documents:

Draft	Report on voting
112/582/FDIS	112/588/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/standardsdev/publications.

A list of all parts in the IEC 60216 series, published under the general title *Electrical insulating materials – Thermal endurance properties*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The "colour inside" logo on the cover page of this document indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

ELECTRICAL INSULATING MATERIALS – THERMAL ENDURANCE PROPERTIES –

Part 5: Determination of relative temperature index (RTI) of an insulating material

1 Scope

This part of IEC 60216 specifies the experimental and calculation procedures to be used for deriving the relative temperature index of a material from experimental data obtained in accordance with the instructions of IEC 60216-1 and IEC 60216-2. The calculation procedures are supplementary to those of IEC 60216-3.

Guidance is also given for assessment of thermal ageing after a single fixed time and temperature, without extrapolation.

The experimental data can in principle be obtained using destructive, non-destructive or proof tests, although destructive tests have been much more extensively employed. Data obtained from non-destructive or proof tests can be “censored”, in that measurement of times taken to reach the endpoint have been terminated at some point after the median time but before all specimens have reached end-point (see IEC 60216-1).

Guidance is given for preliminary assignment of a thermal class for an electrical insulating material (EIM), based upon the thermal ageing performance.

While the thermal classification of an EIM is not directly related to the thermal classification of an electrical insulation system (EIS), the thermal classification of an EIS follows the same concepts as presented in this part of the 60216 series. The calculation procedures of this standard apply to the determination of the thermal class of an EIS when the thermal stress is the prevailing ageing factor.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60216-1:2013, *Electrical insulating materials – Thermal endurance properties – Part 1: Ageing procedures and evaluation of test results*

IEC 60216-2:2005, *Electrical insulating materials – Thermal endurance properties – Part 2: Determination of thermal endurance properties of electrical insulating materials – Choice of test criteria*

IEC 60216-3:2021, *Electrical insulating materials – Thermal endurance properties – Part 3: Instructions for calculating thermal endurance characteristics*

3 Terms, definitions, symbols and units

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at https://www.electropedia.org/
- ISO Online browsing platform: available at https://www.iso.org/obp

3.1.1
electrical insulating material
EIM
material of low electric conductivity, used to separate conducting parts at different electric potentials or to isolate such parts from the surroundings

3.1.2
assessed temperature index
ATI
numerical value of the temperature index in degrees Celsius of the reference EIM

Note 1 to entry: The value of the ATI can vary between applications for the same material.

3.1.3
candidate EIM
material for which an estimate of the thermal endurance is required to be determined

Note 1 to entry: The determination is made by simultaneous thermal ageing of the material and a reference EIM.

3.1.4
reference EIM
material with known thermal endurance (derived from service experience or previous RTI or TI evaluation), used as a reference for comparative tests with the candidate EIM

3.1.5
central second moment of a data group
sum of the squares of the differences between the data values and the value of the group mean divided by the number of data in the group

3.1.6
correlation time for RTI
estimated time to endpoint of the reference EIM at a temperature equal to its ATI in degrees Celsius

3.1.7
degrees of freedom
number of data values minus the number of parameter values

3.1.8
standard error
standard error of an estimate of the true value of a data group property is the value of the standard deviation of the hypothetical sampling population of which the group property can be considered to be a member

Note 1 to entry: For the group mean it is equal to the group standard deviation divided by the square root of the number of data in the group, and indicates the uncertainty in the true value of the mean.

Note 2 to entry: This standard is concerned only with means and the difference between two means (see Clause A.3).

3.1.9
standard deviation
square root of the variance of a data group or sub-group

3.1.10
relative temperature index
RTI
determined by test in relation to the thermal performance of a known reference EIM

3.1.11
variance of a data group
sum of the squares of the deviations of the data from a reference level defined by one or more parameters, divided by the number of degrees of freedom

Note 1 to entry: The reference level can, for example, be a mean value (1 parameter) or a line (2 parameters, in this document, the slope and the intercept with the y axis).

3.2 Symbols and units

a_A	Regression coefficient (y-intercept) of thermal endurance equation for reference EIM
a_B	Regression coefficient (y-intercept) of thermal endurance equation for candidate EIM
b_A	Regression coefficient (slope) of thermal endurance equation for reference EIM
b_B	Regression coefficient (slope) of thermal endurance equation for candidate EIM
X	Variable for statistical analysis equal to $1/(\vartheta + \Theta_0)$
Y	Variable for statistical analysis equal to ln (τ)
ϑ	Ageing temperature in determination of RTI
Θ_0	Temperature on Kelvin scale equal to 0 °C
τ	Time to endpoint
τ_c	Estimated time to endpoint of reference EIM at a temperature equal to ATI (“correlation time”)
$\mu_{2(A)}$	Central second moment of x values for reference EIM
$\mu_{2(B)}$	Central second moment of x values for candidate EIM
n_A	Number of y values for reference EIM data
n_B	Number of y values for candidate EIM data
T	Student’s t distributed stochastic variable

S	Standard error of the difference of two means
s_A^2	Variance of y values for reference EIM data
s_B^2	Variance of y values for candidate EIM data
$\overline{x}_A$	General mean of x-values for reference EIM data
$\overline{x}_B$	General mean of x-values for candidate EIM data
$\overline{y}_A$	General mean of y-values for reference EIM data
$\overline{y}_B$	General mean of y-values for candidate EIM data
θ_A	Temperature in degrees Celsius equal to ATI
θ_B	Temperature in degrees Celsius equal to RTI
$\hat{X}_B$	x value corresponding to θ_B
$\hat{X}_A$	x value corresponding to θ_A
$\theta_{c(B)}$	Lower confidence limit of θ_B
$\theta_{c(A)}$	Lower confidence limit of θ_A
$X_{L(B)}$	x value corresponding to lower confidence limit of θ_B
$X_{L(A)}$	x value corresponding to lower confidence limit of θ_A
Δ_B	Lower confidence interval of θ_B
Δ_A	Lower confidence interval of θ_A
$HIC_{B(c)}$	Halving interval of candidate EIM at a time equal to τ_c
s_D^2	Variance associated with the difference between the mean y-values for the two materials
n_D	Degrees of freedom of s_D^2
υ_A, υ_B	Logarithms of the longest mean times to endpoint for materials A and B
b_r	Intermediate variable: adjusted value of b for calculation of temperature confidence interval
s_r	Intermediate variable: adjusted value of s for calculation of temperature confidence interval