IEC 60216-6

Edition 3.0 2022-11

INTERNATIONAL STANDARD

NORME INTERNATIONALE

colour inside

Electrical insulating materials – Thermal endurance properties – Part 6: Determination of thermal endurance indices (TI and RTI) of an insulating material using the fixed time frame method

Matériaux isolants électriques – Propriétés d'endurance thermique – Partie 6: Détermination des indices d'endurance thermique (IT et ITR) d'un matériau isolant en utilisant la méthode de trame de durées fixes



IEC 60216-6:2022-11 (en-fr)



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2022 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Secretariat
3, rue de Varembé
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC
The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications
The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform
The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, …). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished
Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc
If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch
Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org
The world's leading online dictionary on electrotechnology, containing more than 22 300 terminological entries in English and French, with equivalent terms in 19 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

A propos de l'IEC
La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC
Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Recherche de publications IEC - webstore.iec.ch/advsearchform
La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études, …). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished
Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

Service Clients - webstore.iec.ch/csc
Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch
Découvrez notre puissant moteur de recherche et consultez gratuitement tous les aperçus des publications. Avec un abonnement, vous aurez toujours accès à un contenu à jour adapté à vos besoins.

Electropedia - www.electropedia.org
Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 300 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 19 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

IEC 60216-6

Edition 3.0 2022-11

INTERNATIONAL STANDARD

NORME INTERNATIONALE

colour inside

Electrical insulating materials – Thermal endurance properties – Part 6: Determination of thermal endurance indices (TI and RTI) of an insulating material using the fixed time frame method

Matériaux isolants électriques – Propriétés d'endurance thermique – Partie 6: Détermination des indices d'endurance thermique (IT et ITR) d'un matériau isolant en utilisant la méthode de trame de durées fixes

INTERNATIONAL ELECTROTECHNICAL COMMISSION

COMMISSION ELECTROTECHNIQUE INTERNATIONALE

ICS 17.220.99; 29.035.01

ISBN 978-2-8322-6022-7

Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

® Registered trademark of the International Electrotechnical Commission
Marque déposée de la Commission Electrotechnique Internationale

CONTENTS

FOREWORD 5
1 Scope 7
2 Normative references 7
3 Terms, definitions, symbols and abbreviated terms 8
3.1 Terms and definitions 8
3.2 Symbols and abbreviated terms 11
4 FTFM protocol 12
4.1 Principles of FTFM protocol 12
4.2 Objective of FTFM protocol 12
5 TI determination 13
5.1 Ageing procedures 13
5.2 Ageing times and temperatures 13
5.3 Test specimens 13
5.3.1 Preparation 13
5.3.2 Number of specimens 14
5.4 Diagnostic tests 14
5.5 Selection of end-points 15
5.6 Establishment of initial property value 15
5.7 Ageing conditions 15
5.7.1 Ageing ovens 15
5.7.2 Environmental conditions 15
5.7.3 Conditions for property measurement 16
5.8 Procedure for ageing 16
6 Calculation procedures 16
6.1 General principles 16
6.1.1 Thermal endurance calculation 16
6.1.2 Property value – equivalent temperature transform (Calculation of hypothetical ageing temperature derived from the value of a property) 17
6.2 Precision of calculations 17
6.3 Derivation of temperatures equivalent to property values 17
6.3.1 General 17
6.3.2 Preliminary calculations 17
6.3.3 Regression calculations (property on temperature) 18
6.3.4 Linearity test 20
6.3.5 Estimation of end-point temperatures equivalent to property values 21
6.4 Regression analysis (temperature on time) 21
6.4.1 General 21
6.4.2 Group means and variances 21
6.4.3 General means and variances 21
6.4.4 Regression 22
6.5 Statistical tests 23
6.5.1 Variance equality test 23
6.5.2 Linearity test (F-test) 24
6.5.3 Estimates of x and y and their confidence limits 24
6.6 Thermal endurance graph 26
7 Calculation and requirements for results 26

7.1 Calculation of thermal endurance characteristics 26
7.2 Reporting of results 27
7.2.1 Summary of statistical tests and reporting 27
7.2.2 Report format 27
8 Report 27
9 RTI determination 28
10 Additional symbols 28
11 Experimental procedures 29
11.1 Selection of reference EIM 29
11.2 Selection of diagnostic test for extent of ageing 29
11.3 Ageing procedures 29
12 Calculation procedures 29
12.1 General principles 29
12.2 Input data 29
12.3 RTI 30
12.4 Confidence limits 31
12.5 Extrapolation 32
13 Results and report 33
13.1 Results of statistical and numerical tests 33
13.2 Result 33
13.3 Report 33
Annex A (normative) Decision flow chart 34
Annex B (normative) Decision table 36
Annex C (informative) Statistical tables 37
Annex D (informative) Suggested ageing times and temperatures 41
D.1 TI determination 41
D.1.1 Correlation time (TI) = 20 000 h 41
D.1.2 Other correlation times for TI calculation (see 12.3) 41
D.2 RTI determination 42
Annex E (informative) Figures 43
Annex F (normative) Statistical significance of the difference between two regression estimates 46
Annex G (informative) Computer program 47
G.1 General 47
G.1.1 Overview 47
G.1.2 Convenience program execution 48
G.2.1 Content of file Control6.ftd 50
G.2.2 Report 52
G.2.3 Thermal endurance graph 54

Figure A.1 – Decision flow chart 35
Figure E.1 – Property-temperature graph with regression line 43
Figure E.2 – Thermal endurance graph 43
Figure E.3 – Ageing times and temperatures in relation to thermal endurance graph 44
Figure E.4 – Ageing times and temperatures in relation to thermal endurance graph 44
Figure E.5 – Ageing times and temperatures in relation to thermal endurance graph 45

Figure G.1 – Shortcut property dialog for program launch 49
Figure G.2 – Thermal endurance graph 54

Table 1 – Intermediate data values 30
Table B.1 – Decision table 36
Table C.1 – χ^2-function 37
Table C.2 – t-function 37
Table C.3 – F-function, P = 0,05 38
Table C.4 – F-function, P = 0,005 39
Table D.1 – Ageing temperatures and times 41

INTERNATIONAL ELECTROTECHNICAL COMMISSION

_____

ELECTRICAL INSULATING MATERIALS – THERMAL ENDURANCE PROPERTIES –

Part 6: Determination of thermal endurance indices (TI and RTI) of an insulating material using the fixed time frame method

FOREWORD

1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
6) All users should ensure that they have the latest edition of this publication.
7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 60216-6 has been prepared by IEC technical committee 112: Evaluation and qualification of electrical insulating materials and systems. It is an International Standard.

This second edition cancels and replaces the first edition published in 2003. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

a) clarification of definition of index properties vs. endurance properties;
b) complete rework of Annex G and the corresponding program.

The text of this International Standard is based on the following documents:

Draft	Report on voting
112/583/FDIS	112/589/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/standardsdev/publications.

A list of all parts in the IEC 60216 series, published under the general title *Electrical insulating materials – Thermal endurance properties*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The "colour inside" logo on the cover page of this document indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

ELECTRICAL INSULATING MATERIALS – THERMAL ENDURANCE PROPERTIES –

Part 6: Determination of thermal endurance indices (TI and RTI) of an insulating material using the fixed time frame method

1 Scope

This part of IEC 60216 specifies the experimental and calculation procedures for deriving the thermal endurance characteristics, temperature index (TI) and relative temperature index (RTI) of an electrical insulating material (EIM) using the “fixed time frame method (FTFM)”.

In this protocol, the ageing takes place for a small number of fixed times, using the appropriate number of ageing temperatures throughout each time, the properties of the specimens being measured at the end of the relevant time interval. This differs from the procedure of IEC 60216-1, where ageing is conducted at a small number of fixed temperatures, property measurement taking place after ageing times dependent on the progress of ageing.

The diagnostic tests employed in the fixed time frame method are restricted to destructive tests. The method has not yet been applied to non-destructive or proof test procedures.

Both the TI and the RTI determined according to the FTFM protocol are derived from experimental data obtained in accordance with the instructions of IEC 60216-1 and IEC 60216-2 as modified in this part of IEC 60216. The calculation procedures and statistical tests are modified from those of IEC 60216-3 and IEC 60216-5.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60212, *Standard conditions for use prior to and during the testing of solid electrical insulating materials*

IEC 60216-1:2013, *Electrical insulating materials –Thermal endurance properties – Part 1: Ageing procedures and evaluation of test results*

IEC 60216-2, *Electrical insulating materials – Thermal endurance properties – Part 2: Determination of thermal endurance properties of electrical insulating materials – Choice of test criteria*

IEC 60216-3:2021, *Electrical insulating materials – Thermal endurance properties – Part 3: Instructions for calculating thermal endurance characteristics*

IEC 60216-4-1, *Electrical insulating materials – Thermal endurance properties – Part 4-1: Ageing ovens – Single-chamber ovens*

IEC 60216-4-2, *Electrical insulating materials – Thermal endurance properties – Part 4-2: Ageing ovens – Precision ovens for use up to 300 °C*

IEC 60216-4-3, *Electrical insulating materials – Thermal endurance properties – Part 4-3: Ageing ovens – Multi-chamber ovens*

IEC 60216-5:2022, *Electrical insulating materials – Thermal endurance properties – Part 5: Determination of relative temperature index (RTI) of an insulating material*

IEC 60493-1, *Guide for the statistical analysis of ageing test data – Part 1: Methods based on mean values of normally distributed test results*

3 Terms, definitions, symbols and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at https://www.electropedia.org/
- ISO Online browsing platform: available at https://www.iso.org/obp

3.1.1
electrical insulating material
EIM
material of low electric conductivity, used to separate conducting parts at different electric potentials or to isolate such parts from the surroundings

3.1.2
assessed temperature index
ATI
numerical value of the temperature index in degrees Celsius of the reference EIM

Note 1 to entry: The ATI of a specific material may vary between different applications of the material.

3.1.3
ageing temperature
temperature in degrees Celsius at which a group of specimens is thermally aged

3.1.4
end-point temperature
temperature in degrees Celsius at which a specimen is considered to have reached end-point after ageing for a specified time

3.1.5
candidate EIM
material for which an estimate of the thermal endurance is required to be determined

Note 1 to entry: The determination is made by simultaneous thermal ageing of the material and a reference EIM.

3.1.6
central second moment of a data group
sum of the squares of the differences between the data values and the value of the group mean divided by the number of data items in the group

3.1.7
95 % confidence limit
statistical parameter, calculated from test data, which with 95 % confidence constitutes an upper or lower limit for the true value of a quantity estimated by statistical analysis

Note 1 to entry: This implies that there is only 5 % probability that the true value of the quantity estimated is actually larger (or smaller) than the upper (or lower) confidence limit.

Note 2 to entry: In other connections, confidence values other than 95 % may sometimes be used, e.g. in the linearity test for destructive test data.

3.1.8
reference EIM
material with known thermal endurance, preferably derived from service experience, used as a reference for comparative tests with the candidate EIM

3.1.9
correlation coefficient
number expressing the completeness of the relation between members of two data sets, equal to the covariance divided by the square root of the product of the variances of the sets

Note 1 to entry: The value of its square is between 0 (no correlation) and 1 (complete correlation).

Note 2 to entry: In this standard, the two data sets are the values of the independent variable and the means of the corresponding dependent variable groups.

3.1.10
correlation time for RTI
estimated time to end-point of the reference EIM at a temperature equal to its ATI in degrees Celsius

Note 1 to entry: In this document, it is expressed by symbol τ_C, see Clause 10.

3.1.11
correlation time for TI
hypothetical time to end-point used to calculate TI

Note 1 to entry: Its usual value is 20 000 h, see Clause D.1.

3.1.12
covariance, <of data sets>
for two sets of data with equal numbers of elements where each element in one set corresponds to one in the other, sum of the products of the deviations of the corresponding members from their set means, divided by the number of degrees of freedom

3.1.13
degrees of freedom
number of data values minus the number of parameter values

3.1.14
destructive test
diagnostic property test, where the test specimen is irreversibly changed by the property measurement, in a way which precludes a repeated measurement on the same specimen

Note 1 to entry: An example of a destructive test is the measurement of electric strength. An example of a non-destructive test is the measurement of dissipation factor tan δ.

3.1.15
end-point line
line parallel to the temperature axis intercepting the property axis at the end-point value

3.1.16
halving interval
HIC
numerical value of the temperature interval in Kelvin which expresses the halving of the time to end-point taken at a time equal to TI

3.1.17
regression analysis
process of deducing the best fit line expressing the relation of corresponding members of two data groups by minimizing the sum of squares of deviations of members of one of the groups from the line

3.1.18
regression coefficients
coefficients of the equation of the best fit line derived by regression analysis

3.1.19
relative temperature index
RTI
determined by test in relation to the thermal performance of a known reference EIM

3.1.20
significance
probability of a value of a statistical function greater than a specified value

Note 1 to entry: The value is equal to $(1–p)$ where p is the cumulative distribution function value. Significance is conventionally printed in upper case (P).

3.1.21
standard deviation
square root of the variance of a data group or sub-group

3.1.22
standard error of an estimate of the true value of a data group property
value of the standard deviation of the hypothetical sampling population of which the group property may be a member

Note 1 to entry: For an estimate of the group mean, the standard error is equal to the group standard deviation divided by the square root of the number of data items in the group, and indicates the uncertainty in the estimate of the true value of the mean. This standard is concerned only with means and the difference between two means.

3.1.23
temperature index
TI
numerical value of the temperature in degrees Celsius determined by test by itself

Note 1 to entry: This rating is based on 20 000 h life, unless otherwise specified, based on one of the end-of-life criteria listed in IEC 60216-2.

3.1.24
temperature group, <of specimens>
number of specimens being exposed together to thermal ageing at the same temperature in the same oven

Note 1 to entry: Where there is no risk of ambiguity, either temperature groups or test groups may be referred to simply as “groups”.

3.1.25
test group, <of specimens>
number of specimens removed together from a temperature group for destructive testing

Note 1 to entry: Where there is no risk of ambiguity, either temperature groups or test groups may be referred to simply as “groups”.

3.1.26
thermal endurance graph
graph in which the logarithm of the time to reach a specified end-point in a thermal endurance test is plotted against the reciprocal thermodynamic (absolute) test temperature

3.1.27
thermal endurance graph paper
graph paper having a logarithmic time scale as the ordinate and values proportional to the reciprocal of the thermodynamic (absolute) temperature as the abscissa

Note 1 to entry: The ordinate is usually graduated in powers of ten (from 10 h to 100 000 h is often a convenient range). The abscissa is usually graduated in a non-linear (Celsius) temperature scale oriented with temperature increasing from left to right.

3.1.28
time group, <of specimens>
all test groups removed for testing at the same time

3.1.29
variance of a data group
sum of the squares of the deviations of the data from a reference level defined by one or more parameters divided by the number of degrees of freedom

Note 1 to entry: The reference level can, for example be a mean value (1 parameter) or a line (2 parameters, here intercept on the axis of the independent variable and slope).

3.2 Symbols and abbreviated terms

The following symbols are used in the calculations of Clauses 6, 7, 12 and Annex A, Annex B and Annex C.

Symbol	Description	Clause
a	Regression coefficient: intercept of regression line with x-axis	6.4.4
b	Regression coefficient: slope of regression line relative to y-axis	6.4.4
b_r	Parameter derived from b for calculation of $\hat{Y}_c$	6.5.3
b_p	Regression coefficient for destructive test calculations	6.3.5
c	Parameter in calculation of χ^2	6.5.1
F	F-distributed variance ratio for linearity test	6.3.4, 6.5.2
g, h, i, j	Indexing parameters for regression calculations	6.3, 6.4
HIC	Halving interval	7.1
k	Number of ageing times	6.1.1
N	Total number of x_{ij} values	6.4.3
n_i	Number of x_{ij} values in time group i	6.1.1
P	Significance of the value of a statistical test function	Annex A, Annex B and Annex C
p_e	End-point property value	6.3
p_{gh}	Property value h in temperature group g (time group i implied)	6.3
$\bar{p}_g$	Mean property value in temperature group g (time group i implied)	6.3
q	Base of logarithms in calculation of χ^2	6.5.1
r	Number of temperature groups selected in time group i	6.3.3
r^2	Square of correlation coefficient	6.4.4

Symbol	Description	Clause
s^2	Total (non-regression) variance of x-values	6.5.2
s^2_{lg}	Variance of property values in temperature group g (time group i implied)	6.3.3
s^2_a	Value of s^2 adjusted to allow for acceptable non-linearity	6.5.2
s^2_r	Parameter derived from s^2 for calculation of $\hat{Y}_c$	6.5.3
t	Student's *t*-distributed stochastic variable	6.5.3
TC, TC_a	Lower confidence limit of TI or TI_a (see s^2_a above)	7.1
$t_{p,N}$	Value of t with probability p and N degrees of freedom	6.5.3
x_{ij}	Value of x, index number j, in time group i	6.3.5
$\bar{x}$	General mean of x-values	6.4.3
$\hat{X}$, $\hat{X}_c$	Estimate of x, and its confidence limit	6.5.3
y_i	Value of y for time group i	6.1.1
$\bar{y}$	General mean of y-values	6.4.3
$\hat{Y}$, $\hat{Y}_c$	Estimate of y, and its confidence limit	6.5.3
z_{ij}	Reciprocal kelvin temperature for ϑ_{ij}	6.1.1
$\mu_2(y)$	Central 2nd moment of y values	6.4.3
ν	Total number of property values in time group (i implied)	6.3.3
χ^2	χ^2 distributed variable for variance equality (Bartlett's) test	6.5.1
ϑ_{ij}	Ageing temperature for specimen group j in time group i	6.1.1
Θ_0	273,15 K (corresponding to 0 °C)	6.1.1
τ_i	Ageing time for time group i	6.1.1

4 FTFM protocol

4.1 Principles of FTFM protocol

The FTFM (fixed time frame method) protocol is based upon the principle that thermal ageing for determination of thermal endurance characteristics is carried out over a small number of fixed times, with a sufficient range of ageing temperatures at each time to ensure that the property values determined reach the end-point in a satisfactory manner.

In this it differs from the fixed temperature frame procedure of IEC 60216-1, where a small number of ageing temperatures is employed, with ageing being carried out with testing at intervals, until the end-point has been reached.

4.2 Objective of FTFM protocol

The protocol shall achieve the following advantages:

The determination of thermal endurance characteristics is completed in a fixed, predetermined time.