INTERNATIONAL STANDARD

ISO 10074

Fourth edition
2021-05

Anodizing of aluminium and its alloys — Specification for hard anodic oxidation coatings on aluminium and its alloys

Anodisation de l'aluminium et de ses alliages — Spécification pour l'anodisation dure de l'aluminium et des alliages d'aluminium

Reference number
ISO 10074:2021(E)

© ISO 2021



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword ... **iv**
Introduction ... **v**
1 Scope ... **1**
2 Normative references ... **1**
3 Terms and definitions ... **1**
4 Material classification ... **2**
5 Appearance ... **2**
6 Thickness ... **2**
7 Surface density ... **2**
8 Resistance to wear/abrasion ... **3**
8.1 General ... 3
8.2 Abrasive wheel wear test method ... 3
8.3 Abrasive jet test method ... 4
8.4 Taber abrasion test method ... 5
9 Vickers microhardness ... **5**
10 Resistance to corrosion ... **6**
Annex A (normative) **Information to be supplied by the customer to the anodizer** ... **7**
Annex B (normative) **Abrasion test** ... **8**
Annex C (normative) **Preparation of standard specimen** ... **11**
Annex D (informative) **Sampling procedures** ... **12**
Annex E (normative) **Breakdown voltage** ... **13**
Annex F (normative) **Process qualification and approval** ... **14**
Annex G (informative) **Packaging and delivery of anodized articles** ... **15**
Annex H (informative) **Processing guidance** ... **16**
Bibliography ... **18**

© ISO 2021 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 2, *Organic and anodic oxidation coatings on aluminium*.

This fourth edition cancels and replaces the third edition (ISO 10074:2017), which has been technically revised. The main changes compared with the previous edition are as follows:

— pretest abrasion test numbers have been added as requirements to the abrasive wheel wear test.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2021 – All rights reserved

Introduction

Hard anodizing is an electrolytic treatment which results in the formation of a hard and usually thick coating of alumina used primarily for engineering purposes.

Hard anodizing can be applied to cast or wrought aluminium and aluminium alloys; however, alloys containing more than 5 % copper and/or 8 % silicon and die casting alloys require special anodizing procedures. To obtain optimum microhardness, wear resistance or low surface roughness characteristics, low contents of alloy are selected.

Unless otherwise specified, articles are anodized after all heat-treatment, machining, welding, forming and perforating operations. The best results are achieved on machined surfaces. Sharp edges are machined to a radius of at least 10 times the intended thickness to avoid "burning" and/or spalling.

Hard anodizing will usually result in a dimensional increase on each surface equal to about 50 % of the coating thickness. The dimensions of the component prior to anodizing will allow for this, if necessary.

The thickness is generally within the range of 25 µm to 150 µm. Low thickness (up to 25 µm) is sometimes used in a variety of applications, such as splines and threads. Normal thickness (50 µm to 80 µm) is used for wear or insulation requirements. High thickness (150 µm) is used for repairing purposes, but thick coatings tend to be softer in outer regions. Very hard coatings reduce the fatigue strength. This phenomenon can be minimized by applying shot peening before hard anodizing (see H.6), by reducing thickness and/or by sealing. Hard anodizing tends to increase surface roughness. This can be limited with low alloy contents and/or mechanical finishing.

Hard anodic oxidation coatings are mainly used to obtain the following:

— resistance to wear through abrasion or erosion;

— electrical insulation;

— thermal insulation;

— build-up (to repair parts out of tolerance on machining or worn parts);

— resistance to corrosion (when sealed).

© ISO 2021 – All rights reserved

Anodizing of aluminium and its alloys — Specification for hard anodic oxidation coatings on aluminium and its alloys

1 Scope

This document specifies requirements for hard anodic oxidation coatings on aluminium and its alloys, including test methods.

It also specifies the information to be supplied by the customer to the anodizer (see Annex A).

It is not applicable to coatings produced by processes such as those referred to as plasma electrolytic oxidation, micro-arc oxidation, plasma-chemical anodic oxidation, anodic spark deposition or spark anodizing.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1463, *Metallic and oxide coatings — Measurement of coating thickness — Microscopical method*

ISO 2106, *Anodizing of aluminium and its alloys — Determination of mass per unit area (surface density) of anodic oxidation coatings — Gravimetric method*

ISO 2360, *Non-conductive coatings on non-magnetic electrically conductive base metals — Measurement of coating thickness — Amplitude-sensitive eddy-current method*

ISO 2376, *Anodizing of aluminium and its alloys — Determination of breakdown voltage and withstand voltage*

ISO 4516, *Metallic and other inorganic coatings — Vickers and Knoop microhardness tests*

ISO 6344-1, *Coated abrasives — Grain size analysis — Part 1: Grain size distribution test*

ISO 7583, *Anodizing of aluminium and its alloys — Terms and definitions*

ISO 8251, *Anodizing of aluminium and its alloys — Measurement of abrasion resistance of anodic oxidation coatings*

ISO 9227, *Corrosion tests in artificial atmospheres — Salt spray tests*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 7583 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

3.1
lot
articles of the same nominal composition and temper which are processed together

© ISO 2021 – All rights reserved

3.2
lot acceptance test
test on a production *lot* (3.1) to determine its conformity to specified requirements

4 Material classification

The properties and characteristics of hard anodic oxidation coatings are significantly affected by both the alloy and the method of production.

Consequently, for the purposes of this document, materials are classified into five alloy groupings as follows.

— Class 1: all wrought alloys except those in Class 2.

— Class 2 (a): alloys of the 2 000 series and any other alloys that contain more than 5 % copper.

— Class 2 (b): alloys of the 5 000 series containing 2 % or more magnesium and alloys of the 7 000 series.

— Class 3 (a): casting alloys with less than 2 % copper and/or 8 % silicon.

— Class 3 (b): other casting alloys.

Information to be supplied by the customer to the anodizer shall be in accordance with Annex A.

5 Appearance

The significant surface shall be completely anodized. The visual appearance shall be substantially uniform. There shall be no spalling, blistering or powdery (burnt) areas. Visual examination shall be a lot acceptance test.

Crazing or microcracks shall not normally be a reason for rejection.

6 Thickness

Thickness measurements shall be made on the significant surfaces, but not within 5 mm of contact (jigging) marks, nor in the immediate neighbourhood of a sharp edge.

Measurement shall be made using either the non-destructive eddy current method described in ISO 2360 or the destructive microscopical method described in ISO 1463. In the case of a dispute, the microscopical method (ISO 1463) shall be used.

Measurement of thickness or, where relevant, final dimensions shall be dealt with in a lot acceptance test.

7 Surface density

The surface density (coating mass per unit area), when measured in accordance with ISO 2106 on unsealed anodic oxidation coatings with a nominal thickness of 50 µm ± 5 µm, shall have the minimum values given in Table 1.

If the coating thickness is not 50 µm, the surface density shall be corrected proportionately.

WARNING — A method specified in ISO 2106 requires the use of a reagent containing chromium(VI). Chromium(VI) is toxic and its solutions are hazardous to the environment and severely hazardous to waters.

© ISO 2021 – All rights reserved