INTERNATIONAL STANDARD

ISO 10271

Third edition
2020-08

Dentistry — Corrosion test methods for metallic materials

Médecine bucco-dentaire — Méthodes d'essai de corrosion des matériaux métalliques

Reference number
ISO 10271:2020(E)

© ISO 2020



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword ..... **v**
Introduction ..... **vi**
1 Scope **1**
2 Normative references **1**
3 Terms and definitions **1**
4 Test methods **3**
4.1 Static immersion test 3
4.1.1 Information required 3
4.1.2 Application 3
4.1.3 Reagents 3
4.1.4 Apparatus 3
4.1.5 Solution preparation 4
4.1.6 Samples 4
4.1.7 Test procedure 5
4.1.8 Elemental analysis 6
4.1.9 Test report 6
4.2 Electrochemical test 6
4.2.1 Information required 6
4.2.2 Application 6
4.2.3 Reagents 6
4.2.4 Apparatus 7
4.2.5 Solution preparation 7
4.2.6 Samples 7
4.2.7 Test procedure 9
4.2.8 Test report 12
4.3 Sulfide tarnish test (cyclic immersion) 13
4.3.1 Information required 13
4.3.2 Application 13
4.3.3 Reagents 13
4.3.4 Apparatus 13
4.3.5 Solution preparation 14
4.3.6 Samples 14
4.3.7 Test procedure 14
4.3.8 Inspection 15
4.3.9 Test report 15
4.4 Sulfide tarnish test (static immersion) 15
4.4.1 Information required 15
4.4.2 Application 15
4.4.3 Reagents 15
4.4.4 Apparatus 15
4.4.5 Solution preparation 16
4.4.6 Samples 16
4.4.7 Test procedure 17
4.4.8 Inspection 17
4.4.9 Test report 17
4.5 Static immersion test with periodic analysis 18
4.5.1 Information required 18
4.5.2 Application 18
4.5.3 Reagents 18
4.5.4 Apparatus 18
4.5.5 Solution preparation 18
4.5.6 Samples 19
4.5.7 Test procedure 20

© ISO 2020 – All rights reserved

4.5.8 Elemental analysis 21
4.5.9 Test report 21
4.6 Dental amalgam 22
4.7 Crevice corrosion 22
4.7.1 Principle 22
4.7.2 Application 22
4.7.3 Test medium 22
4.7.4 Materials 22
4.7.5 Apparatus 22
4.7.6 Specimen 23
4.7.7 Procedure 24
4.7.8 Inspection 24
4.7.9 Test report 24
Annex A (informative) **Corrosion test method development** **26**
Bibliography **32**

© ISO 2020 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 106, *Dentistry*, Subcommittee SC 2, *Prosthodontic materials*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 55, *Dentistry,* in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 10271:2011), which has been technically revised. The main changes compared with the previous edition are as follows:

— in the Scope, the statement about this document not being applicable to "appliances for orthodontics" and "dental amalgam" has been removed;

— in 4.1.6.3, a NOTE has been added to the static immersion test method acknowledging that "measuring the total surface area of orthodontic appliances can be difficult" and, therefore, if required in the appropriate standard, "it is acceptable for the ion release for each element of a set of orthodontic brackets to be reported in terms of µg in seven days for a specified number of orthodontic brackets";

— since sodium sulfide hydrate (approximately 35 % Na_2S) analytical grade is not available in every country, text was added to the appropriate test methods indicating that sodium sulfidenonahydrate ($Na_2S{\cdot}9H_2O$), ≤ 98 % may be used;

— this document has been harmonized with ISO 22674:2016 by making changes in the preparation sections of the various test methods that reflect changes that were made for the preparation of metals supplied for metal-ceramic restorations in ISO 22674:2016;

— subclause 4.6 "Dental amalgam" has been added, which refers the user to ISO/TS 17988 when testing the corrosion behaviour of dental amalgam;

— subclause 4.7 "Crevice corrosion" has been added, which provides a test method to evaluate the susceptibility of a dental metallic material to crevice corrosion.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2020 – All rights reserved

Introduction

This document was developed from the original Technical Report (ISO/TR 10271[1)]) as a result of worldwide demand for standard test methods to determine the acceptability of metallic materials for oral restorations in relation to corrosion.

Specific qualitative and quantitative requirements for freedom from biological hazard are not included in this document, but it is recommended that reference be made to ISO 10993-1 and ISO 7405 for assessing possible biological or toxicological hazards.

The testing of the corrosion behaviour of metallic materials in dentistry is complicated by the diversity of the materials themselves, their applications and the environment to which they are exposed. Variation occurs between devices and within the same device during the exposure time. The type of corrosion behaviour or effect can also vary with exposure time. Accordingly, it is not possible to specify a single test capable of covering all situations, nor is it a practical proposition to define a test for each situation. This document, therefore, gives detailed procedures for test methods that have been found to be of merit as evidenced by considerable use.

In the second edition, two new test methods were added. To supplement the existing static immersion test, a static immersion test with periodic analysis was added. A major reason for the addition of this test is that the rate of corrosion of most dental metallic materials varies over time. Thus, the aim of this supplementary test is to provide information on this variation in the corrosion of a dental metallic material. A classification scheme to interpret the rate of corrosion of a tested material with time (i.e. steady, decreasing, increasing) was not included as part of the static immersion test with periodic analysis. It is intended to monitor the use of the test through appropriate working groups of ISO/TC 106 to ascertain whether a classification scheme is needed in a future revision of this document. In this third edition, a classification scheme is still not included.

To supplement the sulfide tarnish test (cyclic immersion), a sulfide tarnish test (static immersion) was also added to the second edition of this document. This test has been used successfully for many years to evaluate the corrosion of silver alloys.

In addition, the second edition added Annex A, which sets out a procedure for each element of the test system such that a consistent approach can be taken for the development of further test methods. Equally, it is recognized that any element can represent only the current recommendation, but changes in the future are unlikely to change the framework.

The third edition differs from the second by the removal of the statement in the Scope about the document not being applicable to "appliances for orthodontics" and "dental amalgam". With the appliances for orthodontics change in mind, a NOTE was added to the static immersion test acknowledging that "measuring the total surface area of orthodontic appliances can be difficult" and stating that, if required in the appropriate standard, "it is acceptable for the ion release for each element of a set of orthodontic brackets to be reported in terms of µg in seven days for a specified number of orthodontic brackets". Also, with reference to dental amalgam, a subclause on dental amalgam (see 4.6) has been added, which refers the user to ISO/TS 17988 when testing the corrosion behaviour of dental amalgam. Additionally, there is a clarification statement that the test methods given in 4.1 to 4.5 are still not applicable to the evaluation of dental amalgam.

The third edition was harmonized with ISO 22674:2016 by adding to the preparation sections of the various test methods the following change concerning metals supplied for metal-ceramic restorations:

— "Following the manufacturer's instructions, simulate the oxidation procedure and four ceramic firings at the highest temperature recommended for fusing ceramic to the metallic material. Remove and place the specimens on a ceramic plate (which is at room temperature) to cool to room temperature after the oxidation and ceramic firing simulation."

1) Withdrawn document.

© ISO 2020 – All rights reserved

Additionally, since sodium sulfide hydrate (approximately 35 % Na_2S) analytical grade is not available in every country, this third edition includes a statement, which was added to the appropriate test methods, indicating that sodium sulfide nonahydrate ($Na_2S·9H2O$), ≤ 98 % may be used.

Also of importance, a test method to evaluate the susceptibility of a dental metallic material to crevice corrosion was added as 4.7.

It is not the purpose of this document to propose corrosion test methods for specific applications or to set limits as precise as those that may be required in a standard relating to a type of product and its application.

© ISO 2020 – All rights reserved

Dentistry — Corrosion test methods for metallic materials

1 Scope

This document specifies test methods and procedures to determine the corrosion behaviour of metallic materials used in the oral cavity. It is intended that these test methods and procedures be referred to in individual International Standards specifying such metallic materials.

This document is not applicable to dental instruments.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 1942, *Dentistry — Vocabulary*

ISO 3585, *Borosilicate glass 3.3 — Properties*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 6344-1, *Coated abrasives — Grain size analysis — Part 1: Grain size distribution test*

ISO 7183, *Compressed-air dryers — Specifications and testing*

ISO/TS 17988, *Dentistry — Corrosion test methods for dental amalgam*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1942 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

3.1
breakdown potential
E_p
least noble potential at which pitting or *crevice corrosion* (3.4), or both, initiates and propagates

3.2
corrosion
physicochemical interaction between a metallic material and its environment that results in a partial or total destruction of the material or in a change of its properties

3.3
corrosion product
substance formed as a result of *corrosion* (3.2)

© ISO 2020 – All rights reserved

3.4
crevice corrosion
corrosion (3.2) associated with and taking place in or near a narrow aperture or crevice

3.5
current density
value of electric current per unit surface area flowing through a conductor

3.6
dynamic immersion test
test in which the *specimen* (3.15) is exposed to a corrosive solution under conditions of relative motion between specimen and solution

3.7
electrode potential
potential difference between the *specimen* (3.15) and a reference electrode

3.8
electrolyte
solution or liquid that conducts an electrical current by means of ions

3.9
open-circuit potential
E_{ocp}
potential of an electrode measured with respect to a reference electrode or another electrode when no current flows

3.10
pitting corrosion
localized *corrosion* (3.2) that results in pits

3.11
potentiodynamic test
test in which the *electrode potential* (3.7) is varied at a predetermined rate and the relationship between *current density* (3.5) and electrode potential is recorded

3.12
potentiostatic test
test in which the *electrode potential* (3.7) is maintained constant

3.13
sample
totality of material for one type being tested, the group of all such *specimens* (3.15)

3.14
set
subgroup of the *specimens* (3.15) of a *sample* (3.13)

3.15
specimen
test piece
individual single example of an object for testing

3.16
static immersion test
test in which the *specimen* (3.15) is exposed to a corrosive solution under conditions of effectively no relative motion between specimen and solution

3.17
stress corrosion
corrosion (3.2) resulting from the combined action of static tensile stress and an *electrolyte* (3.8)

© ISO 2020 – All rights reserved