INTERNATIONAL STANDARD

ISO 10290

Second edition
2018-11

Textiles — Cotton yarns — Basis for specification

Textiles — Fils de coton — Spécifications

Reference number
ISO 10290:2018(E)

© ISO 2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

 © ISO 2018 – All rights reserved

Contents

Page

Foreword ..... **iv**

1 Scope **1**

2 Normative references **1**

3 Terms and definitions **1**

4 Requirements **3**
4.1 General 3
4.2 Yarn linear density 3
4.3 Evenness and faults 3
4.4 Breaking load/tenacity and elongation at break 3
4.5 Skein breaking strength 3
4.6 Yarn twist 3
4.7 Moisture regain 3
4.8 Yarn appearance 3
4.9 Yarn hairiness 3

5 Marking **3**

6 Sampling and inspection **4**

7 Quality control **4**

Annex A (informative) **Examples of cotton yarn specifications** **5**

Bibliography **6**

© ISO 2018 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 23, *Fibres and yarns*.

This second edition cancels and replaces the first edition (ISO 10290:1993), which has been technically revised. The main changes compared to the previous editions are as follows:

— the title has been changed to "*Textiles — Cotton yarns — Basis for specification*";

— in Clause 2, ISO 3951:1989 has been replaced by ISO 3951-4 and ISO 16549, ISO 17202, ASTM D2255, ASTM D5647 have been added;

— in Clause 3, the definitions of "tenacity", "breaking tenacity" and "twist factor" have been revised;

— in Clause 4, three subclauses ("yarn faults", "yarn appearance" and "yarn hairiness") have been added;

— in Clause 5, three items ("quality level of consignment", "end use of yarn" and "packing and storage condition") have been added;

— Table A.1 has been expanded to give examples of specifications of breaking elongation, hairiness and faults.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2018 – All rights reserved

Textiles — Cotton yarns — Basis for specification

1 Scope

This document specifies criteria, with relevant test methods, to be applied in describing single spun grey cotton yarns. These yarns are widely used in international trade.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2, *Textiles — Designation of the direction of twist in yarns and related products*

ISO 2060, *Textiles — Yarn from packages — Determination of linear density (mass per unit length) by the skein method*

ISO 2061, *Textiles — Determination of twist in yarns — Direct counting method*

ISO 2062, *Textiles — Yarns from packages — Determination of single-end breaking force and elongation at break using constant rate of extension (CRE) tester*

ISO 3951-4, *Sampling procedures for inspection by variables — Part 4: Procedures for assessment of declared quality levels*

ISO 6741-1, *Textiles — Fibres and yarns — Determination of commercial mass of consignments — Part 1: Mass determination and calculations*

ISO 6939, *Textiles — Yarns from packages — Method of test for breaking strength of yarn by the skein method*

ISO 16549, *Textiles — Unevenness of textile strands — Capacitance method*

ISO 17202, *Textiles — Determination of twist in single spun yarns — Untwist/retwist method*

ASTM D2255, *Standard test method for grading spun yarns for appearance*

ASTM D5647, *Standard guide for measuring hairiness of yarns by the photo-electric apparatus*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

3.1
linear density
mass per unit length of a yarn

Note 1 to entry: It is expressed in tex or multiples or sub-multiples thereof (see ISO 1144).

[SOURCE: ISO 1139:1973, 3.7]

© ISO 2018 – All rights reserved

3.2
tex
number of grams per kilometre of yarn

Note 1 to entry: The tex system is described in ISO 1144.

3.3
breaking load
maximum load (or force) applied to a specimen in a tensile test carried to rupture

Note 1 to entry: For yarns, it is preferably expressed in centinewton.

[SOURCE: ISO 3060:1974, 3.2, modified — Note 1 to entry has been added]

3.4
elongation at break
increase in length of a specimen produced by the *breaking load* (3.3)

Note 1 to entry: It is usually expressed as a percentage of the original nominal length.

3.5
tenacity
tensile force per unit of *linear density* (3.1) of the unstrained specimen

Note 1 to entry: It is preferably expressed in centinewtons per tex.

[SOURCE: ISO 3060:1974, 3.4]

3.6
breaking tenacity
tenacity (3.5) corresponding to the *breaking load* (3.3)

Note 1 to entry: For specimens of known linear density, the breaking tenacity can be obtained directly from tensile testing machines which can be suitable adjusted to indicate tenacity instead of breaking load.

[SOURCE: ISO 3060:1974, 3.4, modified — Note 1 to entry has been added]

3.7
twist
number of turns about the axis of a length equal to the nominal gauge length before untwisting

Note 1 to entry: Twist is preferably expressed as turns per metre (turns/m), but it may be expressed as turns per centimetre (turns/cm).

[SOURCE: ISO 2061:2015, 3.1]

3.8
twist factor
measure of the spiralling orientation of the fibres in a spun yarn or of the filaments in a filament yarn

Note 1 to entry: The twist factor is related to the angle which fibres on the surface of the yarn make with the axis of the yarn and is a measure of the hardness of the resulting yarn due to *twist* (3.7).

[SOURCE: ISO 2061:2015, 3.7]

3.9
grey cotton yarn
yarn made of cotton fibres as it leaves the spinning frame, without any bleaching, dyeing or finishing treatment

Note 1 to entry: The yarn may be waxed or unwaxed.

© ISO 2018 – All rights reserved