INTERNATIONAL STANDARD

ISO 10788

First edition
2014-05-15

Space systems — Lunar simulants

Systèmes spatiaux — Simulation de la poussiére lunaire

Reference number
ISO 10788:2014(E)

© ISO 2014



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword ..... **iv**

Introduction ..... **v**

1 Scope **1**

2 Terms and definitions and abbreviated terms **1**
2.1 Terms and definitions 1
2.2 Abbreviated terms 2

3 Characteristics of lunar regolith previously defined in the Lunar Sourcebook© **2**
3.1 Minerologies 2
3.2 Physical and chemical properties 3

4 Quantitative measurement properties of lunar simulants **4**
4.1 General 4
4.2 Comparative baseline 4
4.3 Impurities and contamination 4
4.4 Validation of figures of merit 4
4.5 Composition figure of merit 5
4.6 Size distribution figure of merit 7
4.7 Shape figure of merit 8
4.8 Density figure of merit 8

Bibliography **10**

© ISO 2014 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 20, *Aircraft and space vehicles*, Subcommittee SC 14, *Space systems and operations*.

© ISO 2014 – All rights reserved

Introduction

This International Standard provides lunar systems developers and operators with a specific quantitative measure for lunar regolith simulants in comparison to other simulants and with relation to sampled lunar materials from Apollo and Lunakhod missions. Developers of lunar systems will use simulants as test materials. This International Standard is a reference for quantitative measures of lunar simulants finer than 10 cm. It describes four properties (composition, size, shape, and density) which are the minimum number of properties needed for such uses as comparative testing involving simulants or civil engineering. The quantitative measures of lunar dust simulants are based on the quantitative measures of lunar regolith samples collected at multiple lunar landing sites of the Apollo missions.

This International Standard provides communication of the geological quality of the simulant between developing organizations and systems operations organizations.

© ISO 2014 – All rights reserved

Space systems — Lunar simulants

1 Scope

This International Standard is a reference for quantitative measures of lunar simulants.

2 Terms and definitions and abbreviated terms

2.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

2.1.1
agglutinate
vesiculated glass bonded particle containing other particles (lithic fragments), of which the bonding glass contains spherical particles of iron

Note 1 to entry: The lunar spherules are typically 3 – 100 nanometers in diameter and formed contemporaneous with the glass.

Note 2 to entry: Six features characterize lunar agglutinates: size, surface area with relation to volume, composition, nanophase iron content, flow banding, and multiple generations.

2.1.2
angularity
an expression of roundness

EXAMPLE A poorly rounded grain is described as angular.

Note 1 to entry: This definition has been taken from the *Glossary of Geology* (see Reference [5]).

2.1.3
aspect ratio
ratio of the maximum Feret diameter divided into the orthogonal Feret diameter

Note 1 to entry: Values range from > 0 to 1 and equal to 1 for a circle.

2.1.4
Feret diameter
distance between two parallel lines which are tangent to the perimeter of a particle

Note 1 to entry: The maximum Feret diameter is defined as the greatest distance between two parallel lines which are still tangent to the perimeter of the particle.

2.1.5
figure of merit
degree to which a sample matches a reference

Note 1 to entry: Scaling (normalization) forces the norm of the difference of two composition vectors to lie between 0 and 1, and subtraction from unity results in a figure of merit of 1 for a perfect match and 0 for not match at all.

© ISO 2014 – All rights reserved

2.1.6
Heywood circularity factor
expression of the complexity of a particle's perimeter

Note 1 to entry: Formally, the Heywood circularity factor is equal to 1 divided by particle perimeter divided by the circumference of a circle with the same area as the particle. This is numerically equal to the "circularity" defined by Waddell (1933). It is expressed in this manner to make it apparent that the Heywood factor is the inverse of a common definition of "circularity", another common measure.

Note 2 to entry: Values range from > 0 to 1 and equal 1 for a circle.

2.1.7
lithic fragments
physically discrete solids of any rock type whose normative composition is within the range of the target terrain

Note 1 to entry: Lithic fragments have texture and mineralogy. Texture is a more important feature than mineralogy for lithic fragments. Texture describes the grain to grain connectivity boundary. Lunar textures cannot be replicated on Earth.

2.1.8
lunar terrains
mare and highlands

2.1.9
regolith
all particulate surface material including rocks, soils, and dust

Note 1 to entry: As stated in the Introduction, this International Standard is limited in scope to regolith 10 cm and smaller. Rocks, soils, and dust are not differentiated on the basis of size.

2.1.10
re-use
after a simulant volume is used (any sequence of events in which a simulant volume is removed from a storage container) then placed back into storage, any future use constitutes re-use

2.1.11
sphericity
degree to which the shape of a particle approaches a sphere

2.2 Abbreviated terms

c_x concentration or portion of a sample for the x^{th} item in the sample

FoM Figure of Merit

RFD Relative Frequency Distribution

w_i weighting factor. w is a value between one and zero. i is an index which refers to the characteristic being weighted, such as glass (a grain type)

3 Characteristics of lunar regolith previously defined in the Lunar Sourcebook©

3.1 Minerologies

The lunar surface mineralogy is variable across major terrain. These properties are qualitative; they cannot be described in a quantitative manner related to any known spatial distribution across the lunar surface. The listing of the primary minerologies in Reference [3] includes

© ISO 2014 – All rights reserved