INTERNATIONAL STANDARD

ISO 11125-7

Second edition
2018-09

Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives —

Part 7: Determination of moisture

Préparation des subjectiles d'acier avant application de peintures et de produits assimilés — Méthodes d'essai pour abrasifs métalliques destinés à la préparation par projection —

Partie 7: Détermination de l'humidité

Reference number
ISO 11125-7:2018(E)

© ISO 2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

 © ISO 2018 – All rights reserved

Contents

Page

Foreword ..... **iv**
1 Scope **1**
2 Normative references **1**
3 Terms and definitions **1**
4 Apparatus **1**
5 Sampling **2**
6 Procedure **2**
6.1 Test portion 2
6.2 Determination 2
7 Expression of results **2**
8 Test report **2**
Annex A (informative) **International Standards for metallic blast-cleaning abrasives** **3**
Bibliography **4**

© ISO 2018 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 12, *Preparation of steel substrates before application of paints and related products.*

This second edition cancels and replaces the first edition (ISO 11125-7:1993), which has been technically revised.

The main changes compared to the previous edition are as follows:

— Annex A has been technically revised.

A list of all parts in the ISO 11125 series can be found on the ISO website.

© ISO 2018 – All rights reserved

Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives —

Part 7: Determination of moisture

1 Scope

This document specifies a test method for the determination of the level of free moisture present in metallic blast-cleaning abrasives. It is determined by measuring the mass lost on heating.

This is one of a number of parts of ISO 11125 dealing with the sampling and testing of metallic abrasives for blast-cleaning.

The types of metallic abrasive and requirements for each are contained in the various parts of ISO 11124.

The ISO 11124 and ISO 11125 series have been drafted as a coherent set of International Standards on metallic blast-cleaning abrasives. Information on all parts of both series is given in Annex A.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

4 Apparatus

Ordinary laboratory apparatus and glassware, together with the following.

4.1 **Balance**, capable of weighing to an accuracy of 0,01 g.

4.2 **Oven**, capable of being maintained at a temperature of (110 ± 5) °C.

4.3 **Container** or **tray**, capable of withstanding the heat applied and of sufficient volume to allow the test portion to be spread in a thin layer.

4.4 **Desiccator**, containing a desiccant such as dried silica gel impregnated with cobalt chloride.

© ISO 2018 – All rights reserved