INTERNATIONAL STANDARD

ISO 11125-9

First edition
2021-08

Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives —

Part 9: Wear testing and performance

Reference number
ISO 11125-9:2021(E)

© ISO 2021



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

© ISO 2021 – All rights reserved

Contents

Page

Foreword ..... **iv**
Introduction ..... **v**
1 Scope **1**
2 Normative references **1**
3 Terms and definitions **2**
4 Principle **3**
5 Samples **3**
6 Preliminary testing **3**
7 Apparatus **3**
8 Blast-cleaning abrasive testing under laboratory conditions **4**
8.1 Testing machines 4
8.2 Test method procedures 4
8.2.1 100 % breakdown method 4
8.2.2 Full wear test (100 % replacement method) 7
8.2.3 Stabilized consumption test 8
9 Transmitted energy tests **10**
9.1 Transmitted energy test (100 % replacement) 10
9.1.1 General 10
9.1.2 Test method 10
9.2 Transmitted energy test (at full saturation) 10
9.2.1 General 10
9.2.2 Test method 10
9.2.3 Test evaluation 10
9.2.4 Example 10
10 Test report **11**
Bibliography **13**

© ISO 2021 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 12, *Preparation of steel substrates before application of paints and related products.*

A list of all parts in the ISO 11125 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2021 – All rights reserved

Introduction

This document is a part of the ISO 11125 series that specifies test methods for metallic blast-cleaning abrasives.

During blast-cleaning, metallic abrasives are subjected to repeated impacts on the substrate to be prepared. These mechanical impacts result in abrasive material fatigue until particles breakdown.

The service life of the metallic blast-cleaning abrasives is influenced by:

— the type of abrasive, in particular, its size and shape, its resilience, its hardness and its internal defects;

— the hardness and the surface conditions of the substrate to be prepared;

— the blasting machine and its settings.

The principle of an abrasive service life testing machine is based on a high number of impacts between a representative sample of the abrasive to be tested and a given target.

Several testing machines exist on the market and depending on their design, the service life obtained under laboratory conditions may or may not be comparable to field operation.

It is important that the user is aware of the different parameters and the respective adjustability. The parameters of the testing machines can vary from one machine to another and therefore can result in different test results.

In general, the effect of wear and consumption are tested. Special arrangements may be required for specific test procedures. The results can be used for comparison purposes (quality inspection) or for monitoring (quality control) of the deliveries for uniformity.

© ISO 2021 – All rights reserved

Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives —

Part 9:
Wear testing and performance

1 Scope

This document specifies three procedures to test the service life of a blast-cleaning abrasive under laboratory conditions.

The performance of an abrasive is also measured by its ability to clean, via transmission of kinetic energy to the substrate in the blasting process. This document also specifies the procedures that can be performed in the same testing machines to help evaluate abrasive performance under laboratory conditions.

This document applies to the testing of virgin metallic blasting media in the delivery state by centrifugal blasting under laboratory conditions.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11124-3, *Preparation of steel substrates before application of paints and related products — Specifications for metallic blast-cleaning abrasives — Part 3: High-carbon cast-steel shot and grit*

ISO 11124-4, *Preparation of steel substrates before application of paints and related products — Specifications for metallic blast-cleaning abrasives — Part 4: Low-carbon cast-steel shot*

ISO 11124-5, *Preparation of steel substrates before application of paints and related products — Specifications for metallic blast-cleaning abrasives — Part 5: Cut steel wire*

ISO 11125-1, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 1: Sampling*

ISO 11125-2, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 2: Determination of particle size distribution*

ISO 11125-3, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 3: Determination of hardness*

ISO 11125-4, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 4: Determination of apparent density*

ISO 11125-5, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 5: Determination of percentage defective particles and of microstructure*

ISO 11125-6, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 6: Determination of foreign matter*

© ISO 2021 – All rights reserved

ISO 11125-7, *Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives — Part 7: Determination of moisture*

ISO 12944-4, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 4: Types of surface and surface preparation*

ISO 565:1990, *Test sieves — Metal wire cloth, perforated metal plate and electroformed sheet — Nominal sizes of openings*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 11124-3, ISO 11124-4, ISO 11124-5, ISO 11125-1, ISO 11125-2, ISO 11125-3, ISO 11125-4, ISO 11125-5, ISO 11125-6, ISO 11125-7, ISO 12944-4 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at https://www.electropedia.org/

3.1
blast-cleaning abrasive
solid material intended to be used for abrasive blast-cleaning

3.2
service life
duration of the usability of the *blast-cleaning abrasive* (3.1)

Note 1 to entry: In this field of application the service life is given in the number of cycles in which 100 % of the material wears. In practice, the worn material is removed from the system by ventilation, in the laboratory this is achieved by sieving.

3.3
abrasive consumption
weight of loss of abrasive divided by the weight of thrown abrasive

Note 1 to entry: It is expressed in g/1 000 kg.

3.4
Almen strip
UNS G10700 carbon steel specimen that is used to calibrate the energy of an abrasive stream

3.5
Almen strip holding fixture
device used to fasten *Almen strips* (3.4) in suitable locations that represent the position and angular orientation of the surfaces of a part where the intensity is to be determined and verified

3.6
arc height
flat *Almen strip* (3.4) that, when subjected to a stream of shot moving at an adequate velocity, bends in an arc corresponding to the amount of energy transmitted by the shot stream

Note 1 to entry: The height of the curved arc measured in millimetre is the arc height, measured by an Almen gauge.

3.7
Almen intensity
Almen strip *arc height* (3.6) at saturation

Note 1 to entry: This term comes into effect only when saturation is achieved.

© ISO 2021 – All rights reserved

Note 2 to entry: Surface preparation is not solely a question of Almen intensity. Size and hardness of the blasting media are important to achieve a good surface cleaning or a good surface roughness.

3.8
saturation
minimum number of cycles necessary to achieve the desired *Almen intensity* (3.7) which, when doubled does not increase the Almen strip *arc height* (3.6) by more than 10 %

3.9
saturation curve
curve that plots Almen strip *arc height* (3.6) (ordinate) with the number of cycles (abscissa)

Note 1 to entry: See Figure 2.

3.10
transmitted energy
ability of the abrasive to transmit its kinetic energy to the substrate to perform useful work in cleaning or preparing the surface

4 Principle

The service life of metallic blast-cleaning abrasive is determined by various factors. It is dependent on the substrate itself, on the blasting system and its operating parameters, as well as on the blasting media. Therefore, laboratory testing can only give an indication of the consumption or wear of the metallic blast-cleaning abrasive.

5 Samples

Sampling for either preliminary testing or testing by centrifugal blasting under laboratory conditions, or both, shall be carried out in accordance with ISO 11125-1. The sample taken should be about 1 kg to 2 kg. This is sufficient material to complete the full suite of tests.

6 Preliminary testing

All abrasive samples should be tested for particle size distribution, hardness, density, defects, microstructure and foreign matter according to ISO 11125-2, ISO 11125-3, ISO 11125-4, ISO 11125-5 and ISO 11125-6, respectively. Samples which fail preliminary testing shall not be subject to centrifugal blasting machine tests.

7 Apparatus

7.1 Abrasive service life testing machine, whose principle is based on a high number of impacts between a representative sample of the abrasive to be tested and a given target.

The design and operation of the testing machine are specified in the operating instructions.

Depending on the design of the testing machines, the force of the impact between the abrasive and the target is controlled by the speed of the abrasive or by the speed of the target. The setting of these speeds shall be done as recommended by the manufacturer.

The test machine is equipped with a device allowing the recirculation of the abrasive after each cycle, the test media remaining in the machine for a predetermined number of cycles, or test interval.

Calibration of the testing machine shall be done as recommended by the manufacturer, using a representative sample of an abrasive of known service life.

NOTE Different testing machines produce different results.

© ISO 2021 – All rights reserved