INTERNATIONAL STANDARD

ISO 11810

Second edition
2015-12-15

Lasers and laser-related equipment — Test method and classification for the laser resistance of surgical drapes and/or patient protective covers — Primary ignition, penetration, flame spread and secondary ignition

Lasers et équipements associés aux lasers — Méthode d'essai et classification de la résistance au laser pour des draps chirurgicaux et/ou des couvertures de protection des patients — Inflammation principale, pénétration et inflammation secondaire

Reference number
ISO 11810:2015(E)

© ISO 2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword ... **iv**
Introduction ... **v**
1 Scope ... **1**
2 Normative references ... **1**
3 Terms and definitions ... **1**
4 Principle ... **3**
5 Significance and use of the test ... **3**
6 Apparatus ... **4**
6.1 General ... 4
6.2 Containment box ... 5
6.3 Specimen holder ... 5
6.4 Laser system ... 9
6.4.1 Laser ... 9
6.4.2 Power meter ... 9
6.5 Gas supply system ... 9
6.6 Environment ... 9
6.6.1 Ambient air conditions ... 9
6.6.2 Oxygen enriched atmospheres ... 9
6.7 Smoke evacuation device ... 10
7 Reagents and materials ... **10**
8 Preparation of specimens ... **10**
8.1 Sampling ... 10
8.1.1 Single use products ... 10
8.1.2 Reusable products ... 10
8.2 Specimens ... 10
8.3 Quantities ... 10
8.4 Conditioning ... 10
9 Preparation of apparatus ... **11**
10 Test methods ... **11**
10.1 General conditions ... 11
10.2 Primary ignition and penetration ... 11
10.2.1 Principle ... 11
10.2.2 Testing procedure ... 14
10.3 Secondary ignition ... 15
10.3.1 Principle ... 15
10.3.2 Testing procedure ... 16
11 Classification ... **18**
11.1 General ... 18
11.2 Laser-induced primary ignition (I) ... 18
11.3 Resistance to laser penetration (P) ... 18
11.4 Laser-induced secondary ignition (SI) ... 18
12 Test report ... **19**
Bibliography ... **20**

© ISO 2015 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 172, *Optics and photonics*, Subcommittee SC 9, *Electro-optical systems*.

This second edition cancels and replaces ISO 11810-1:2005 and ISO 11810-2:2007 which have been technically revised.

© ISO 2015 – All rights reserved

Introduction

Some laser applications in medicine can require laser-resistant surgical drapes or other patient-protective covers. Surgical drapes or other patient-protective covers are necessary when a sterile procedure is performed and the surrounding area needs to be protected from liquids, secretions and inadvertent laser radiation. While conventional surgical drapes or other patient-protective covers are not necessarily laser-resistant, specifically designed surgical drapes offer the possibility of laser resistance.

Laser induced risks include ignition, flammability, melting, penetration, thermal transfer and reflectivity. Textile and non-woven drape materials can have other risks but they can provide a laser barrier. While there are many potential ignition devices present in the operating room (e.g. fibre optic illumination systems, electro-surgical units, hot wire cauteries), this test method addresses only the laser ignition source. This International Standard is intended for use in testing a surgical drape or other patient-protective cover that claims to be laser-resistant. In addition, areas within this product can vary in material composition or design. Depending on the claims being made by the manufacturer or end-user requirements, all areas for which laser resistance is claimed might need to be tested.

CO_2 lasers can induce the most challenging conditions of all medical lasers. Ignition/flammability tests and penetration tests can reveal more challenging laser wavelengths as well as modes of laser delivery, for example Q-switching in the nanosecond range. The 20 W CO_2 laser (continuous wave) has been selected as the laser for this International Standard.

Users of this test method are cautioned that the laser resistance of a surgical drape or other patient-protective cover will be wavelength sensitive and that a surgical drape or other patient-protective cover should be tested at the wavelengths for which it is intended to be used. If tested using other wavelengths, it is necessary to explicitly state the power settings and modes of delivery.

The results from this International Standard should not be applied to other wavelengths and temporal formats.

The performance of laser-resistant surgical drapes or other patient-protective covers can be changed when used in combination rather than individually.

© ISO 2015 – All rights reserved

Lasers and laser-related equipment — Test method and classification for the laser resistance of surgical drapes and/or patient protective covers — Primary ignition, penetration, flame spread and secondary ignition

CAUTION — This test method can involve hazardous materials, operations and equipment. This International Standard provides advice on minimizing some of the risks associated with its use but does not purport to address all such risks. It is the responsibility of the user of this International Standard to establish appropriate safety and health practices and to determine the applicability of regulatory limitations prior to use.

1 Scope

This International Standard is applicable to disposable and reusable, as well as woven and non-woven materials used as surgical drapes and other patient-protective covers which claim to be laser-resistant. The purpose of this International Standard is to provide a standardized method for testing and classifying surgical drapes and other patient-protective covers with respect to laser-induced hazards. An appropriate classification system is given. It is not the purpose of this International Standard to serve as a general fire safety specification, and as such, this International Standard does not cover other sources of ignition.

All materials reflect portions of the beam and it is necessary for the user to decide whether specular reflectance can be a hazard. This measurement, however, is not covered in this International Standard.

The test procedure can be used to assess the laser induced flammability properties of non-laser-resistant items

NOTE Users of products tested by this method are cautioned that the laser resistance of a surgical drape and/or patient-protective cover will be wavelength sensitive and that a surgical drape and/or patient-protective cover are better tested at the wavelength for which it is intended to be used. If tested using other wavelengths, it is necessary to explicitly state the power settings and modes of delivery.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11145, *Optics and photonics — Lasers and laser-related equipment — Vocabulary and symbols*

ISO 11146-1, *Lasers and laser-related equipment — Test methods for laser beam widths, divergence angles and beam propagation ratios — Part 1: Stigmatic and simple astigmatic beams*

ISO 80000-4, *Quantities and units — Part 4: Mechanics*

IEC 60825-1, *Safety of laser products — Part 1: Equipment classification and requirements*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

© ISO 2015 – All rights reserved

3.1
afterflame
persistence of flaming of a material, under specified test conditions, after the ignition source has been removed

3.2
afterflame time
length of time for which a material continues to flame, under specified test conditions, after the ignition source has been removed

3.3
afterglow
persistence of glowing of a material, under specified test conditions, after cessation of flaming or, if no flaming occurs, after the ignition source has been removed

3.4
afterglow time
time during which a material continues to glow, under specified test conditions, after cessation of flaming or, if no flaming occurs, after the ignition source has been removed

3.5
beam diameter
d_{95}
diameter of an aperture in a plane perpendicular to the beam axis which contains 95 % of the total beam power

3.6
beam cross-sectional area
A_{95}
smallest area containing 95 % of the total beam power

Note 1 to entry: Adapted from ISO 11145:2006, 3.2.1.

3.7
combustion
any continuing burning process that occurs in or on the specimen caused by a chemical process of oxidation with the liberation of heat

EXAMPLE Flame, smouldering, rapid evolution of smoke.

3.8
damage
any change, other than combustion, which can affect the safety of the patient or efficacy of the product due to increasing the risk of ignition

EXAMPLE Local heating, melting, creation of holes, pyrolysis.

3.9
flammable
subject to ignition and flaming combustion

3.10
ignition
creation of combustion induced by the delivery of power

3.11
laser resistance
measure of the ability of a material to withstand laser power without ignition or damage

© ISO 2015 – All rights reserved

3.12
melting behaviour
softening of a material under the influence of heat (including shrinking, dripping and burning of molten material, etc.)

3.13
patient-protective cover
material, other than a surgical drape, intended to protect a patient

3.14
penetration resistance
ability of a material to prevent the passage of laser energy

3.15
product
finished medical device (surgical drape or other patient-protective cover) that can be composed of one or more homogeneous materials (samples)

3.16
reusable product
product intended to be laundered and re-sterilized for multiple use

3.17
secondary ignition
ignition of a specimen by an underlying material caused to burn by a laser beam transmitted through the specimen

3.18
single use
product intended to be used once and then discarded

3.19
surgical drape
material intended to be draped over a patient during surgery

3.20
thermal resistance
ability of a material to resist conduction of heat

4 Principle

WARNING — This test method can result in a rocket-like fire involving the surgical drape. Such a fire can produce intense heat and light and toxic gases.

To simulate worst-case conditions, the material is exposed to laser power of known characteristics in an environment of up to 98 % ± 2 % oxygen.

5 Significance and use of the test

5.1 This International Standard describes a uniform and repeatable test method for measuring the primary ignition, penetration, flame spread and secondary ignition of surgical drapes and other patient-protective covers. Variables involved in laser ignition have been fixed in order to establish a basis for comparison. This test method can be used to compare differing types and designs.

5.2 A large number and range of variables is involved in ignition of surgical drapes. A change in one variable can affect the outcome of the test. Caution should be exercised, since the direct applicability of the results of this test method to the clinical situation has not been fully established.

© ISO 2015 – All rights reserved