INTERNATIONAL STANDARD

ISO 12108

Third edition
2018-07

Metallic materials — Fatigue testing — Fatigue crack growth method

Matériaux métalliques — Essais de fatigue — Méthode d'essai de propagation de fissure en fatigue

Reference number
ISO 12108:2018(E)

© ISO 2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

 © ISO 2018 – All rights reserved

Contents

Page

Foreword ..... **v**

Introduction ..... **vi**

1 Scope **1**

2 Normative references **1**

3 Terms and definitions **1**

4 Symbols and abbreviated terms **4**
4.1 Symbols 4
4.2 Abbreviated terms for specimen identification 5

5 Apparatus **5**

6 Specimens **6**
6.1 General 6
6.2 Crack plane orientation 6
6.3 Starter notch precracking details 8
6.4 Stress-intensity factor 10
6.5 Specimen size 10
6.6 Specimen thickness 10
6.7 Residual stress 10

7 Procedure **11**
7.1 Fatigue precracking 11
7.2 Crack length measurement 11
7.3 Constant-force-amplitude, K-increasing, test procedure for $da/dN > 10^{-5}$ mm/cycle 12
7.4 K-decreasing procedure for $da/dN < 10^{-5}$ mm/cycle 13

8 Crack length measurement **15**
8.1 Resolution 15
8.2 Interruption 15
8.3 Static force 15
8.4 Measurement interval 15
8.5 Symmetry 16
8.6 Out-of-plane cracking 16
8.7 Crack tip bifurcation 16
8.8 Non-visual crack length measurement 16
8.9 Visual crack length measurement 16

9 Calculations **16**
9.1 Crack-front curvature 16
9.2 Determining the fatigue crack growth rate 17
9.2.1 General 17
9.2.2 Secant method 17
9.2.3 Incremental polynomial method 18
9.3 Determination of the fatigue crack growth threshold 18

10 Test report **18**
10.1 General 18
10.2 Material 18
10.3 Test specimen 19
10.4 Precracking terminal values 19
10.5 Test conditions 19
10.6 Test analysis 20
10.7 Presentation of results 20

Annex A (normative) **Compact tension (CT) specimen** **27**

Annex B (normative) **Centre crack tension (CCT) specimen** **32**

© ISO 2018 – All rights reserved

Annex C (normative) **Single edge notch tension (SENT) specimen** **38**

Annex D (normative) **Single edge notch bend (SENB) specimens** **41**

Annex E (informative) **Non-visual crack length measurement methodology — Electric potential difference[9][12][36]** **48**

Bibliography **51**

 © ISO 2018 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 4, *Fatigue, fracture and toughness testing*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This third edition cancels and replaces the second edition (ISO 12108:2012), which has been technically revised. The main changes compared to the previous edition are as follows:

— The document has been reorganized to move the formulae and drawings for each of the test specimens from the main body of the document into a separate normative annex for each specimen.

— Guidance on the effects of residual stress on fatigue crack growth rate data has been expanded.

© ISO 2018 – All rights reserved

Introduction

This document is intended to provide specifications for generation of fatigue crack growth rate data. Test results are expressed in terms of the fatigue crack growth rate as a function of crack-tip stress-intensity factor range, ΔK, as defined by the theory of linear elastic fracture mechanics[15][16][17][18][19][20]. Expressed in these terms, the results characterize a material's resistance to subcritical crack extension under cyclic force test conditions. This resistance is independent of specimen planar geometry and thickness, within the limitations specified in Clause 6.

This document describes a method of subjecting a precracked notched specimen to a cyclic force. The crack length, a, is measured as a function of the number of elapsed force cycles, N. From the collected crack length and corresponding force cycles relationship, the fatigue crack growth rate, da/dN, is determined and is expressed as a function of stress-intensity factor range, ΔK.

Materials that can be tested by this method are limited by size, thickness and strength only to the extent that the material remains predominantly in an elastic condition during testing and that buckling is precluded.

Specimen size can vary over a wide range. Proportional planar dimensions for six standard configurations are presented. The choice of a particular specimen configuration can be dictated by the actual component geometry, compression test conditions or suitability for a particular test environment.

Specimen size is a variable that is subjective to the test material's 0,2 % proof strength and the maximum stress-intensity factor applied during test. Specimen thickness can vary independently of the planar size, within defined limits, so long as large-scale yielding is precluded and out-of-plane distortion or buckling is not encountered. Any alternate specimen configuration other than those included in this document can be used, provided there exists an established stress-intensity factor calibration expression, i.e. stress-intensity factor geometry function, $g\ (a/W)$[21][22][23].

Residual stresses[24][25], crack closure[26][27], specimen thickness, cyclic waveform, frequency and environment, including temperature, can markedly affect the fatigue crack growth data but are in no way reflected in the computation of ΔK, and so should be recognized in the interpretation of the test results and be included as part of the test report. All other demarcations from this method should be noted as exceptions to this practice in the final report.

For crack growth rates above 10^{-5} mm/cycle, the typical scatter in test results generated in a single laboratory for a given ΔK can be in the order of a factor of two[28]. For crack growth rates below 10^{-5} mm/cycle, the scatter in the da/dN calculation can increase to a factor of 5 or more. To ensure the correct description of the material's da/dN versus ΔK behaviour, a replicate test conducted with the same test parameters is highly recommended.

Service conditions can exist where varying ΔK under conditions of constant K_{max} or K_{mean} control[29] can be more representative than data generated under conditions of constant force ratio; however, these alternate test procedures are beyond the scope of this document.

© ISO 2018 – All rights reserved

Metallic materials — Fatigue testing — Fatigue crack growth method

WARNING — This document does not address safety or health concerns, should such issues exist, that can be associated with its use or application. The user of this document has the sole responsibility to establish any appropriate safety and health concerns.

1 Scope

This document describes tests for determining the fatigue crack growth rate from the fatigue crack growth threshold stress-intensity factor range, ΔK_{th}, to the onset of rapid, unstable fracture.

This document is primarily intended for use in evaluating isotropic metallic materials under predominantly linear-elastic stress conditions and with force applied only perpendicular to the crack plane (mode I stress condition), and with a constant force ratio, R.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

3.1
crack length
a
crack size
linear measure of a principal planar dimension of a crack from a reference plane to the crack tip

3.2
cycle
smallest segment of a force-time or stress-time function which is repeated periodically

Note 1 to entry: The terms “fatigue cycle”, “force cycle” and “stress cycle” are used interchangeably. The letter N is used to represent the number of elapsed cycles.

3.3
fatigue crack growth rate
$\mathrm{d}a/\mathrm{d}N$
extension in crack length

3.4
maximum force
F_{max}
force having the highest algebraic value in the cycle, a tensile force being positive and a compressive force being negative

© ISO 2018 – All rights reserved

3.5
minimum force
F_{min}
force having the lowest algebraic value in the cycle, a tensile force being positive and a compressive force being negative

3.6
force range
ΔF
algebraic difference between the maximum and minimum forces in a cycle

$$\Delta F = F_{max} - F_{min}$$

3.7
force ratio
R
stress ratio
algebraic ratio of the minimum force or stress to the maximum force or stress in a cycle

$$R = F_{min}/F_{max}$$

Note 1 to entry: R can also be calculated using the values of stress-intensity factors; $R = K_{min}/K_{max}$.

3.8
stress-intensity factor
K
magnitude of the ideal crack-tip stress field for the opening mode force application to a crack in a homogeneous, linear-elastically stressed body, where the opening mode of a crack corresponds to the force being applied to the body perpendicular to the crack faces only (mode I)

Note 1 to entry: The stress-intensity factor is a function of applied force, crack length, specimen size and geometry.

3.9
maximum stress-intensity factor
K_{max}
highest algebraic value of the stress-intensity factor in a cycle, corresponding to F_{max} and current crack length

3.10
minimum stress-intensity factor
K_{min}
lowest algebraic value of the stress-intensity factor in a cycle, corresponding to F_{min} and current crack length

Note 1 to entry: This definition remains the same, regardless of the minimum force being tensile or compressive. For a negative force ratio ($R < 0$), there is an alternate, commonly used definition for the minimum stress-intensity factor, $K_{min} = 0$. See 3.11.

3.11
stress-intensity factor range
ΔK
algebraic difference between the maximum and minimum stress-intensity factors in a cycle

$$\Delta K = K_{max} - K_{min}$$

Note 1 to entry: The variables ΔK, R and K_{max} are related as follows: $\Delta K = (1 - R)\, K_{max}$.

Note 2 to entry: For $R \leq 0$ conditions, see 3.10 and 10.6.

© ISO 2018 – All rights reserved

Note 3 to entry: When comparing data developed under $R \leq 0$ conditions with data developed under $R > 0$ conditions, it can be beneficial to plot the da/dN data versus K_{max}.

3.12
fatigue crack growth threshold stress-intensity factor range
ΔK_{th}
asymptotic value of ΔK for which da/dN approaches zero

Note 1 to entry: For most materials, the threshold is defined as the stress-intensity factor range corresponding to 10^{-7} mm/cycle. When reporting ΔK_{th}, the corresponding lowest decade of da/dN data used in its determination should also be included.

3.13
normalized *K*-gradient
$C = (1/K)\, dK/da$
fractional rate of change of K with increased crack length, a

$$C = 1/K\,(dK/da) = 1/K_{max}\,(dK_{max}/da) = 1/K_{min}\,(dK_{min}/da) = 1/\Delta K\,(d\Delta K/da)$$

3.14
***K*-decreasing test**
test in which the value of the normalized K-gradient, C, is negative

Note 1 to entry: A K-decreasing test is conducted by reducing the stress-intensity factor either by continuously shedding or by a series of steps, as the crack grows.

3.15
***K*-increasing test**
test in which the value of C is positive

Note 1 to entry: For standard specimens, a constant force amplitude results in a K-increasing test where the value of C is positive and increasing.

3.16
stress-intensity factor geometry function
$g\,(a/W)$
mathematical expression, based on experimental, numerical or analytical results, that relates the stress-intensity factor to force and crack length for a specific specimen configuration

3.17
crack-front curvature correction length
a_{cor}
difference between the average through-thickness crack length and the corresponding crack length at the specimen faces during the test

3.18
fatigue crack length
a_{fat}
length of the fatigue crack, as measured from the root of the machined notch

Note 1 to entry: See Figure 2.

3.19
notch length
a_n
length of the machined notch, as measured from the load line to the notch root

Note 1 to entry: See Figure 2.

© ISO 2018 – All rights reserved

3.20
specimen width
W
linear measure of a principal planar dimension of a specimen from a reference plane to the specimen edge

4 Symbols and abbreviated terms

4.1 Symbols

See Table 1.

Table 1 — Symbols and their designations

Symbol	Designation	Unit
Loading		
C	Normalized K-gradient	mm^{-1}
E	Tensile modulus of elasticity	MPa
F	Force	kN
F_{max}	Maximum force	kN
F_{min}	Minimum force	kN
ΔF	Force range	kN
K	Stress-intensity factor	$MPa \cdot m^{1/2}$
K_{max}	Maximum stress-intensity factor	$MPa \cdot m^{1/2}$
K_{min}	Minimum stress-intensity factor	$MPa \cdot m^{1/2}$
ΔK	Stress-intensity factor range	$MPa \cdot m^{1/2}$
ΔK_i	Initial stress-intensity factor range	$MPa \cdot m^{1/2}$
ΔK_{th}	Fatigue crack growth threshold stress-intensity factor range	$MPa \cdot m^{1/2}$
N	Number of cycles	cycle
R	Force ratio	kN/kN
R_m	Ultimate tensile strength at the test temperature	MPa
$R_{p0,2}$	0,2 % proof strength at the test temperature	MPa
Geometry		
a	Crack length or size measured from the reference plane to the crack tip	mm
a_{cor}	Crack-front curvature correction length	mm
a_{fat}	Fatigue crack length measured from the notch root	mm
a_n	Machined notch length	mm
a_p	Precrack length	mm
B	Specimen thickness	mm
D	Hole diameter for CT, SENT or CCT specimen, loading tup diameter for bend specimens	mm
$g(a/W)$	Stress-intensity factor geometry function	unitless
h	Notch height	mm
W	Specimen width measured from the reference plane to the specimen edge	mm
$(W - a)$	Uncracked ligament	mm
Crack growth		
da/dN	Fatigue crack growth rate	mm/cycle
Δa	Change in crack length, crack extension	mm

© ISO 2018 – All rights reserved