INTERNATIONAL STANDARD

ISO 1215

Third edition
2015-05-15

Virgin cork, raw reproduction cork, ramassage, gleanings, burnt cork, corkwaste, boiled cork pieces and raw corkwaste — Definitions and packaging

Liège mâle, liège de reproduction cru, liège de ramassage, liège gisant, liège flambé, déchets, morceaux de liège bouillis et rebuts bouillis — Définitions et emballage

Reference number
ISO 1215:2015(E)

© ISO 2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword ..... **iv**
1 Scope **1**
2 Normative references **1**
3 Terms and definitions **1**
4 Packaging **1**
5 Marking **1**
6 Losses during transport **2**

© ISO 2015 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 87, *Cork*.

This third edition cancels and replaces the second edition (ISO 1215:1986), which has been technically revised.

© ISO 2015 – All rights reserved

Virgin cork, raw reproduction cork, ramassage, gleanings, burnt cork, corkwaste, boiled cork pieces and raw corkwaste — Definitions and packaging

1 Scope

This International Standard applies to commercially dry virgin cork, raw reproduction cork, ramassage, gleanings, burnt cork, corkwaste, boiled cork pieces, and boiled corkwaste and specifies the conditions of packaging for each type.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 633, *Cork — Vocabulary*

ISO 2386, *Corkwood in planks, virgin cork, ramassage, gleanings, corkwood refuse and corkwaste — Determination of moisture content*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 633 and ISO 2386 and the following apply.

3.1
commercially dry corkwood
corkwood in which the moisture content, determined in accordance with ISO 2386, is not higher than 14 %

Note 1 to entry: Virgin cork, raw reproduction cork, ramassage, gleanings, burnt cork, corkwaste, boiled cork pieces, and boiled corkwaste are types of corkwood.

3.2
packaging mass
combined mass of the *commercially dry corkwood* (3.1) and its package

4 Packaging

The types of cork to which the present standard applies shall be packed, unless agreed otherwise, in nets or in bags.

The packaging mass (nets, bags, or other packaging contractually accepted) shall not be superior to 3 % of the total mass of the conditioned ball whose moisture is less than 14 %.

5 Marking

The packaging shall indicate the type of cork conditioning, the name or trademark of the producer and/or exporter, as well as the country of origin.

© ISO 2015 – All rights reserved