INTERNATIONAL STANDARD

ISO 12625-7

Third edition
2021-08

Tissue paper and tissue products —

Part 7: Determination of optical properties — Measurement of brightness and colour with D65/10° (outdoor daylight)

Papier tissue et produits tissue —

Partie 7: Détermination des propriétés optiques — Mesurage du degré de blancheur et de la couleur en D65/10° (lumière du jour extérieure)

Reference number
ISO 12625-7:2021(E)

© ISO 2021



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword ..... **iv**
Introduction ..... **v**
1 Scope **1**
2 Normative references **1**
3 Terms and definitions **1**
4 Principle **3**
5 Apparatus **3**
6 Calibration **4**
7 Sampling **5**
8 Conditioning **5**
9 Preparation of test pieces **5**
10 Procedure **5**
10.1 General 5
10.2 Measurement of D65 brightness 5
10.3 Measurement of colour (D65/10°) 6
11 Calculation **6**
11.1 D65 brightness 6
11.2 Colour (D65/10°) 6
11.2.1 Single value 6
11.2.2 Mean value 7
11.2.3 Dispersion of the results 7
12 Test report **7**
Annex A (informative) **Precision** **9**
Bibliography **12**

© ISO 2021 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 2, *Test methods and quality specifications for paper and board,* in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 172, *Pulp, paper and board,* in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 12625-7:2014), which has been technically revised.

The main changes compared to the previous edition are as follows:

— alternative formulae in 11.2.1 have been removed because they were not relevant for tissue paper.

A list of all parts in the ISO 12625 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2021 – All rights reserved

Introduction

Brightness and colour measurement can be performed under various illumination and observation conditions. This document deals with D65/10° conditions, which refer to an outdoor daylight.

C/2° conditions (indoor daylight) are considered in ISO 12625-15. Although both International Standards deal with brightness and colour, results obtained are usually different and do not correlate.

Optical measurement is affected by the geometry of the instruments used and by the texture of the material. The design of the instrument to use according to this document and the routine to adopt for its calibration are specified in ISO 2469 and ISO 11475.

The optical properties are related to the visual appearance of the material. Therefore, although optical properties are intrinsic properties of tissue paper, they are not functional properties.

Brightness should not be confused with the optical property called CIE whiteness, which is based on reflectance data obtained over the full visible spectral range (VIS) in contrast to the measurement of brightness, which is limited to the blue region of VIS.

Due to its importance for some countries, three different test methods for the determination of optical properties were developed:

— this document, i.e. ISO 12625-7;

— ISO 12625-15;

— ISO 12625-16.

© ISO 2021 – All rights reserved

Tissue paper and tissue products —

Part 7:
Determination of optical properties — Measurement of brightness and colour with D65/10° (outdoor daylight)

1 Scope

This document specifies testing procedures for the instrumental determination of brightness and colour of tissue paper and tissue products viewed under outdoor daylight conditions. It also gives specific instructions for the preparation of test pieces (single-ply, multi-ply products) and for the optical measurements of products, where special precautions can be necessary.

NOTE The properties called ISO brightness and colour with C/2° (indoor daylight) are measured with an instrument adjusted to a much lower UV content than that specified in this document. The measurements of ISO brightness and colour with C/2° (indoor daylight) are described in ISO 12625-15.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

ISO 2469, *Paper, board and pulps — Measurement of diffuse radiance factor (diffuse reflectance factor)*

ISO 4094, *Paper, board and pulps — General requirements for the competence of laboratories authorized for the issue of optical reference transfer standards of level 3*

ISO 11475:2017, *Paper and board — Determination of CIE whiteness, D65/10 degrees (outdoor daylight)*

ISO/CIE 11664-4, *Colorimetry — Part 4: CIE 1976 L*a*b* colour space*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

3.1
diffuse radiance factor
R
ratio of the radiation reflected and emitted from a body to that reflected from the perfect reflecting diffuser under the same conditions of diffuse illumination and normal detection

Note 1 to entry: The ratio is often expressed as a percentage.

© ISO 2021 – All rights reserved

[SOURCE: ISO 2469:2014, 3.2]

3.2
intrinsic diffuse radiance factor
R_∞
diffuse radiance factor (3.1) of a layer or pad of material thick enough to be opaque, i.e. such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured radiance factor

Note 1 to entry: The radiance factor of a single non-opaque sheet is dependent on the background and is not a material property.

Note 2 to entry: The ratio is often expressed as a percentage.

[SOURCE: ISO 2469:2014, 3.3]

3.3
reflectance factor
quotient of the flux reflected in the directions by a given cone with apex at a surface element and the flux reflected in the same directions by a perfect reflecting diffuser identically irradiated or illuminated

Note 1 to entry: The ratio is often expressed as a percentage.

Note 2 to entry: This term shall be used only when it is known that the test material exhibits no luminescence (fluorescence).

[SOURCE: CIE S 017 ILV:2020, 17-24-070]

3.4
D65 brightness
intrinsic diffuse radiance factor (3.2) measured with a reflectometer having the characteristics described in ISO 2469, equipped with a filter or corresponding function having an effective wavelength of 457 nm (and a half bandwidth of 44 nm), and adjusted so that the UV content of the irradiation incident upon the test piece corresponds to that of the CIE standard illuminant D65

Note 1 to entry: The filter function is described more fully by the weighting factors given in ISO 2470-2.

3.5
tristimulus values
X_{10},Y_{10},Z_{10}
amounts of the reference colour stimuli, in a given trichromatic system, required to match the colour of the stimulus considered

Note 1 to entry: In ISO 5631-2 the CIE standard illuminant D65 and the CIE 1964 (10°) standard observer are used to define the trichromatic system.

Note 2 to entry: The subscript 10 is applied to conform to the CIE convention that tristimulus units have the subscript 10 when the CIE 1964 (10°) standard colorimetric observer is used.

[SOURCE: CIE S 017 ILV:2020, 17-23-038]

3.6
colour (D65/10°)
L^*, a^* and b^* values of the sample according to the CIELAB 1976 system described in ISO/CIE 11664-4, corresponding to the CIE standard illuminant D65 described in ISO 11664-2 and the CIE 1964 standard colorimetric observer described in ISO/CIE 11664-1, determined by measurement under the conditions specified in ISO 5631-2

Note 1 to entry: The quantity L^* is a measure of the lightness of the test piece, where $L^* = 0$ corresponds to black and $L^* = 100$ is defined by the perfect reflecting diffuser. Visually, the quantities a^* and b^* represent respectively the red-green and yellow-blue axes in colour space, such that

— $+a^*$ is a measure of the degree of redness of the test piece,

© ISO 2021 – All rights reserved

— -a^* is a measure of the degree of greenness of the test piece,

— +b^* is a measure of the degree of yellowness of the test piece,

— -b^* is a measure of the degree of blueness of the test piece, and

— if both a^* and b^* are equal to zero, the test piece is grey.

4 Principle

A test piece is illuminated diffusely in a standardized instrument and the light reflected normal to the surface is either allowed to pass through a defined optical filter and then measured by a photodetector or measured by an array of photosensitive diodes, where each diode responds to a different effective wavelength. The brightness is then determined directly from the output from the photodetector or by calculation from the photosensitive diode outputs using the appropriate weighting function and colour coordinates are calculated for D65/10° conditions.

Precision data are available in Annex A.

5 Apparatus

5.1 Reflectometer or spectrophotometer, having the geometric, spectral and photometric characteristics described in ISO 2469 and calibrated in accordance with the provisions of ISO 2469, and equipped for the measurement of blue reflectance factor.

5.1.1 In the case of a filter **reflectometer**, the radiation falling upon the test piece shall have a UV content corresponding to that of the CIE standard illuminant D65, adjusted or verified using the fluorescent reference standard (5.2.2).

5.1.2 In the case of an abridged **spectrophotometer**, the instrument shall have an adjustable filter with a cut-off wavelength of 395 nm or some other system for adjustment and control and this filter shall be adjusted or the system shall be calibrated using the fluorescent reference standard (5.2.2), so that the UV content of the illumination falling upon the sample corresponds to that of the CIE standard illuminant D65.

5.2 Reference standard for calibration of the instrument

5.2.1 Non-fluorescent reference standard for photometric calibration, issued by an ISO 4094 authorized laboratory in accordance with the provisions of ISO 2469.

5.2.2 Fluorescent reference standard for use in adjusting the UV content of the radiation incident upon the sample, having a CIE whiteness (D65/10°) unit assigned by an ISO 4094 authorized laboratory as prescribed in ISO 11475:2017, Annex B.

NOTE 1 Greater precision in the D65 brightness measurement would be attained if a fluorescent reference standard having an assigned D65 brightness unit were used. It is, however, important for the industry to have only one UV-filter adjustment for all measurements under CIE illuminant D65 conditions. For this reason, a reference standard having an assigned CIE whiteness (D65/10°) value as prescribed in ISO 11475 is used.

NOTE 2 To use sufficiently frequently to ensure satisfactory calibration and UV adjustment.

5.3 Working standards

5.3.1 Two plates of flat opal glass, ceramic or other suitable non-fluorescent material, cleaned and calibrated as described in ISO 2469.

© ISO 2021 – All rights reserved