International Standard

ISO 12834

First edition
2024-08

Textiles — Synthetic filament yarns — Determination of dynamic thermal draw-force of partially oriented yarns (POY)

Textiles — Fils de filaments synthétiques — Détermination de la force d'étirage thermique dynamique des fils partiellement orientés (POY)

Reference number
ISO 12834:2024(en)

© ISO 2024



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword ... **iv**

1 Scope ... **1**

2 Normative references ... **1**

3 Terms and definitions ... **1**

4 Principle ... **1**

5 Apparatus ... **1**

6 Testing conditions ... **2**
6.1 Pretension ... 2
6.2 Heater temperature ... 2
6.3 Draw-ratio ... 2
6.4 Testing speed ... 3
6.5 Testing length ... 3

7 Sampling ... **3**

8 Test procedure ... **3**
8.1 Preparation of test specimen ... 3
8.2 Setting of testing conditions ... 3
8.3 Threading of test specimen ... 4
8.4 Specimen testing ... 4

9 Calculation and expression of results ... **5**

10 Precision ... **5**

11 Test report ... **5**

Annex A (informative) **Optimization of heater temperature, testing speed and draw-ratio in determination of dynamic thermal draw-force** ... **6**

Annex B (normative) **Calculation of statistic values** ... **9**

Annex C (informative) **Precision** ... **11**

Bibliography ... **12**

© ISO 2024 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 23, *Fibres and yarn*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2024 – All rights reserved

Textiles — Synthetic filament yarns — Determination of dynamic thermal draw-force of partially oriented yarns (POY)

1 Scope

This document specifies a method for the determination of the dynamic thermal draw-force of partially oriented synthetic filament yarns.

It is applicable to partially oriented polyester (PES), polyamide (PA) and polypropylene (PP) filament yarns, with a linear density less than 800 dtex.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

ISO 2076, *Textiles — Man-made fibres — Generic names*

3 Terms and definitions

For the purpose of this document, the terms and definitions given in ISO 2076 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp/ui

— IEC Electropedia: available at https://www.electropedia.org/

3.1
dynamic thermal draw-force
force caused by drawing the running filament yarns to a certain ratio under a certain heater temperature and testing speed

4 Principle

The continuous filament yarn runs into the dynamic thermal draw-force tester at a certain testing speed under constant pretension, then passes a heater and drawing device. It is drawn to a specific ratio while being heated at a specified temperature. The dynamic thermal draw-force is determined.

5 Apparatus

5.1 Dynamic thermal draw-force tester, which meets the following requirements:

a) tensioning device to apply specified pretension on filament yarns and maintain tension to an accuracy of ±10 %;

b) heater to maintain temperature to an accuracy of ±2 °C;

NOTE The results of thermal draw-force being tested in heaters with different length can differ.

© ISO 2024 – All rights reserved