INTERNATIONAL STANDARD

**ISO 12985-2**

Second edition
2018-05

# Carbonaceous materials used in the production of aluminium — Baked anodes and cathode blocks —

## Part 2: Determination of apparent density and of open porosity using a hydrostatic method

*Produits carbonés utilisés pour la production de l'aluminium — Anodes cuites et blocs cathodiques —*

*Partie 2: Détermination de la masse volumique apparente et de la porosité ouverte par une méthode hydrostatique*

Reference number
ISO 12985-2:2018(E)

© ISO 2018



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

 © ISO 2018 – All rights reserved

# Contents

Page

**Foreword** ..... **iv**
**1 Scope** ..... **1**
**2 Normative references** ..... **1**
**3 Terms and definitions** ..... **1**
**4 Principle** ..... **1**
**5 Reagents** ..... **1**
**6 Apparatus** ..... **2**
**7 Sampling** ..... **2**
**8 Procedure** ..... **2**
8.1 Determination of dry sample mass ..... 2
8.2 Determination of the volume ..... 2
**9 Calculation** ..... **3**
**10 Precision** ..... **3**
10.1 Apparent density ..... 3
10.1.1 Repeatability ..... 3
10.1.2 Reproducibility ..... 3
10.2 Open porosity ..... 3
10.2.1 Repeatability ..... 3
10.2.2 Reproducibility ..... 4
**11 Test report** ..... **4**
**Bibliography** ..... **5**

© ISO 2018 – All rights reserved

# Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 226, *Materials for the production of primary aluminium*.

This second edition cancels and replaces the first edition, ISO 12985-2:2000, of which it constitutes a minor revision.

A list of all parts in the ISO 12985 series can be found on the ISO website.


© ISO 2018 – All rights reserved

# Carbonaceous materials used in the production of aluminium — Baked anodes and cathode blocks —

# Part 2: Determination of apparent density and of open porosity using a hydrostatic method

## 1 Scope

This document specifies a hydrostatic method for the determination of the apparent density and the open (to water) porosity of carbonaceous products used in the production of aluminium.

This hydrostatic method was developed principally to determine the open porosity but can also be used to measure the apparent density. This document is especially applicable to samples of complex on irregular geometry (due to drilling difficulties).

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 8007-1, *Carbonaceous materials used in the production of aluminium — Sampling plans and sampling from individual units — Part 1: Cathode blocks*

ISO 8007-2, *Carbonaceous materials used in the production of aluminium — Sampling plans and sampling from individual units — Part 2: Prebaked anodes*

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

## 4 Principle

The apparent density of a material is defined as the ratio of its dry mass to its volume. The volume is determined by the measurement of the Archimedes force (the mass of the displaced liquid) applied to the sample saturated with water after boiling. The open porosity is simply measured by calculating the ratio of the mass (volume) of water which has penetrated into the sample after boiling to the mass (volume) of the displaced water measured with the hydrostatic balance.

## 5 Reagents

**5.1 Distilled water**, or water of equivalent purity.

© ISO 2018 – All rights reserved