INTERNATIONAL STANDARD

ISO 13257

Second edition
2018-11

Thermoplastics piping systems for non-pressure applications — Test method for resistance to elevated temperature cycling

Systèmes de canalisations thermoplastiques pour applications sans pression — Méthode d'essai de résistance à des cycles de température élevée

Reference number
ISO 13257:2018(E)

© ISO 2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

 © ISO 2018 – All rights reserved

Contents

Page

Foreword ..... **iv**

1 Scope **1**

2 Normative references **1**

3 Terms and definitions and symbols **1**
3.1 Terms and definitions 1
3.2 Symbols 2

4 Principle **2**

5 Apparatus **2**

6 Test assembly **3**
6.1 General 3
6.2 Assembly for pipes with integral socket (for $d_n \geq 40$ mm) 3
6.3 Assembly for pipes without integral sockets (for $d_n \geq 40$ mm). 3
6.4 Mounting 6
6.5 Anchoring 7

7 Procedure **7**

8 Test report **9**

© ISO 2018 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 1, *Plastics pipes and fittings for soil, waste and drainage (including land drainage)*.

This second edition cancels and replaces the first edition (ISO 13257:2010), which has been technically revised. The major modifications to the previous edition are:

— revision of the Scope to delete the references to application areas "B", "BD" and "UD";

— addition in the Scope of the range of nominal outside diameters of components to which this method is applicable;

— addition of a definition for “sagging”;

— complete review of Clause 6, Test assemblies, in particular distinction between test assemblies including pipes with integral sockets and fittings with socket and spigot (Figure 1) and test assemblies including pipes without integral socket and fittings with sockets (Figure 2) for components $d_n \geq 40$ mm;

— in Clause 7, addition of Figure 4 to illustrate the measuring point of the column of water.

Any feedback or questions on this document should be directed to the user’s national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2018 – All rights reserved

Thermoplastics piping systems for non-pressure applications — Test method for resistance to elevated temperature cycling

1 Scope

This document specifies a test method for determining the resistance to elevated temperature cycling of thermoplastics piping systems for non-pressure applications, inside buildings or buried in the ground within the building structure.

This document is applicable to piping systems with components of nominal outside diameters up to and including 200 mm.

Although limited to nominal outside diameters up to and including 200 mm, the test results may be extrapolated to products of larger nominal outside diameters from the same range.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/TS 7024:2005, *Plastics piping systems for soil and waste discharge (low and high temperature) inside buildings — Thermoplastics — Recommended practice for installation*

3 Terms and definitions and symbols

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— IEC Electropedia: available at http://www.electropedia.org/

— ISO Online browsing platform: available at https://www.iso.org/obp/

3.1.1
nominal outside diameter
d_n
specified diameter assigned to a nominal size (DN/OD or DN/ID)

Note 1 to entry: It is expressed in millimetres.

3.1.2
sagging
S_g
deformation of the pipe occurring from the test conditions, which is measured after the test at a defined location in vertical direction downwards

Note 1 to entry: It is expressed in millimetres.


© ISO 2018 – All rights reserved

3.1.3
expansion gap
distance between the bottom of a socket and the spigot of the inserted component allowing expansion of the system


Note 1 to entry: Adapted from ISO/TS 7024:2005, definition 3.2.4.

3.2 Symbols

For the purposes of this document, the symbols given in ISO/TS 7024 and the following apply:



ring seal socket



guide brackets (for free movement of pipe)



anchor brackets (for fixed point)

4 Principle

A test assembly of pipes and fittings is subjected to a given pattern of thermal cycling by using hot and cold water alternately for a given number of cycles during which the leaktightness of joints is verified by inspection and sagging of the pipe is checked against a limit after the test.

5 Apparatus

5.1 Thermometer or **other temperature measuring device,** capable of measuring with an accuracy of 0,5 °C or better. The resolution of the thermometer or the temperature measuring device shall be 0,1 °C or better. The thermometer or the temperature measuring device shall be capable of recording the relevant temperature, with a reaction time less than or equal to 20 s, from 20 °C to 90 °C.

5.2 Timer, with an accuracy of 1 s.

5.3 Cold water source, capable of supplying at the inlet of the test assembly, every 4 min, the following quantities of water at (15 ± 5) °C (see 7.3):

a) for Programme A, (30 ± 0,5) l in (60 ± 2) s;

b) for Programme B, (15 ± 0,5) l in (60 ± 2) s.

5.4 Hot water source, capable of supplying at the inlet of the test assembly, every 4 min, the following volumes of water at (93 ± 2) °C (see 7.3):

a) for Programme A, (30 ± 0,5) l in (60 ± 2) s;

b) for Programme B, (15 ± 0,5) l in (60 ± 2) s.

However, in order to improve the reproducibility, it is recommended that the hot water temperature is maintained at (93 ± 1) °C.

5.5 Plugs or **other closures**, to seal, temporarily, the water outlet (see 7.1 and 7.4).

© ISO 2018 – All rights reserved