INTERNATIONAL STANDARD

ISO 14309

Second edition
2019-07

Rubber, vulcanized or thermoplastic — Determination of volume and/or surface resistivity

Caoutchouc vulcanisé ou thermoplastique — Détermination de la résistivité transversale et/ou superficielle

Reference number
ISO 14309:2019(E)

© ISO 2019



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword ..... **iv**
Introduction ..... **v**
1 Scope **1**
2 Normative references **1**
3 Terms and definitions **1**
4 Principle **2**
5 Apparatus **2**
6 Calibration **6**
7 Test pieces **6**
7.1 Form 6
7.2 Number of test pieces 7
8 Conditioning **7**
9 Test conditions **7**
9.1 Temperature and humidity 7
9.2 Applied voltage 7
10 Test procedure **7**
11 Expression of results **8**
11.1 Volume resistivity 8
11.2 Surface resistivity 8
12 Test report **9**
Annex A (informative) **Electrode materials** **10**
Annex B (informative) **Suitable range of test conditions** **11**
Annex C (normative) **Calibration schedule** **13**
Annex D (informative) **Effective area of guarded electrode** **15**
Bibliography **18**

© ISO 2019 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This second edition cancels and replaces the first edition (ISO 14309:2011), which has been technically revised.

The main changes compared to the previous edition are as follows:

— A detailed explanation on the requirement for the electrode gap for volume resistivity has been added in 5.4.2.

— The typical dimension for D_2 has been changed to (60 ± 0,5) mm in 5.4.2.

— To calculate the volume resistivity, the effective area of the main electrode is now derived from $D_1 + B_g$ in 11.1, and the information on B_g has been newly included as Annex D.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2019 – All rights reserved

Introduction

Rubber materials are widely used in many industries, either as the major material or forming a part of the product, because of their unique physical properties which can be tailored by compounding to match the particular requirements of the product specification. Although rubbers are generally regarded as insulating materials, they can be made electrically conductive or dissipative by compounding with a certain amount of carbon black or ionizable ingredients. Hence, the range of electrical resistance to be measured is very wide. It is difficult, however, to obtain high accuracy for measurements in the high-resistance range due to a number of factors.

In this document, the guarded-electrode system is used to determine the resistivity of rubber test pieces since it is considered a good compromise between minimizing the errors by shunting away stray currents and using more unwieldy measurement instruments (see also IEC 62631-3-1).

ISO 1853, on the other hand, covers rubber materials with medium to low resistance, i.e. resistivities of 10^8 Ω·m or below. It specifies three methods for determining volume resistivity which minimize or eliminate contact resistance.

The methods specified in this document were originally designed for the determination of both surface and volume resistivity of insulating rubber materials, but their use can be extended to cover the range from high to low resistivity.

It is known that the test results are sensitive to the test conditions, such as temperature and humidity, and to heat and strain history.

© ISO 2019 – All rights reserved

Rubber, vulcanized or thermoplastic — Determination of volume and/or surface resistivity

WARNING 1 — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to determine the applicability of any other restrictions.

WARNING 2 — Certain procedures specified in this document might involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

1 Scope

This document specifies a method for the determination of the volume and the surface resistivity of vulcanized or thermoplastic rubbers. The method can be applied to materials with a resistivity from 10^1 Ω·m to 10^{17} Ω·m.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1382, *Rubber — Vocabulary*

ISO 18899:2013, *Rubber — Guide to the calibration of test equipment*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1382 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

3.1
volume resistance
R_v
quotient of a direct-current voltage applied between two electrodes in contact with opposite faces of a test piece and the current between the electrodes, excluding current along the surface

Note 1 to entry: It is expressed in ohms (Ω).

3.2
surface resistance
R_s
quotient of a direct-current voltage applied between two electrodes on the same surface of a test piece and the current between the electrodes

Note 1 to entry: It is expressed in ohms (Ω).

© ISO 2019 – All rights reserved

3.3
volume resistivity
ρ_v
measured volume resistance calculated to apply to a cube of unit side

Note 1 to entry: It is expressed in ohm metres (Ω·m).

3.4
surface resistivity
ρ_s
measured surface resistance calculated to apply to a square

Note 1 to entry: It is expressed in ohms (Ω) and the size of the square is immaterial.

3.5
guarded-electrode system
electrode system composed of three electrodes, a guard, and a guarded and an unguarded electrode to reduce measurement errors by protecting the current-measuring electrode from the interfering influences of voltages other than the test voltage, and of stray conductances

Note 1 to entry: Guarding depends on interposing, in all critical insulated parts, guard electrodes which intercept all stray currents that might otherwise cause errors. The guard electrodes are connected together, constituting the guard system and forming with the measurement terminals a three-terminal network. When suitable connections are made, stray currents from spurious external voltages are shunted away from the measurement circuit by the guard system, the insulation resistance from either measurement terminal to the guard system shunts a circuit element which should be of very much lower resistance, and the specimen resistance constitutes the only direct path between the measurement terminals. By this technique, the probability of error is considerably reduced (see 5.3.2 of IEC 62631-3-1:2016 for more details).

4 Principle

The volume and surface resistances of a rubber test piece are determined, using a suitable arrangement of electrodes, from the current flowing when a voltage is applied. The volume and surface resistivities are calculated from the measured resistances, which include the contact resistance.

5 Apparatus

The test equipment consists of a power supply, current-measuring equipment and electrodes:

5.1 Stabilized direct-current power supply, capable of applying a voltage of 1 V to 1 000 V to the test piece.

5.2 Voltmeter, capable of measuring the applied voltage with an accuracy of ±2 %.

5.3 Ammeter or other current-measuring device, capable of measuring a current of 0,01 pA to 100 mA, depending on the resistivity of the test piece to be measured. The accuracy of the current-measuring device shall be better than 5 %.

5.4 Electrodes

5.4.1 Guarded-electrode system

Three electrodes shall be applied to the test piece:

— a main electrode (circular);

— a ring electrode (annular);

© ISO 2019 – All rights reserved