International Standard

ISO 14705

Fine ceramics (advanced ceramics, advanced technical ceramics) — Test method for hardness of monolithic ceramics at room temperature

Céramiques techniques — Méthodes d'essai de dureté des céramiques monolithiques à température ambiante

Fourth edition
2026-09

Reference number
ISO 14705:2026(en)

© ISO 2026



COPYRIGHT PROTECTED DOCUMENT

© ISO 2026

All rights reserved.

This ISO publication is protected by copyright and is owned by ISO and/or its licensors.

The content of this ISO publication is provided under licence, not sold. Use is subject to the applicable licence terms issued by ISO, an ISO member body, or an authorized third-party distributor.

Except as required for implementation or expressly permitted by a separate licence, no part of this ISO publication may be reproduced, distributed, modified, used, or made available in any form or by any means – electronic or mechanical, including photocopying, scanning, recording, or posting on internal or external digital platforms.

Any use beyond the scope of the granted rights is prohibited and may result in legal action.

ISO copyright office
CP 401 • CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword ... **iv**

1 Scope ... **1**

2 Normative references ... **1**

3 Terms and definitions ... **1**

4 Vickers hardness ... **2**
4.1 Principle ... 2
4.2 Symbols, abbreviated terms and designations ... 2
4.3 Significance and use ... 4
4.4 Apparatus ... 4
4.5 Test pieces ... 5
4.6 Procedure ... 5
4.7 Accuracy and uncertainties ... 8
4.8 Test report ... 8

5 Knoop hardness ... **12**
5.1 Principle ... 12
5.2 Symbols, abbreviated terms and designations ... 12
5.3 Significance and use ... 14
5.4 Apparatus ... 14
5.5 Test pieces ... 15
5.6 Procedure ... 15
5.7 Accuracy and uncertainty ... 16
5.8 Test report ... 17

Bibliography ... **21**

© ISO 2026 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 206, *Fine ceramics*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 184, *Advanced technical ceramics,* in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 14705:2016), which has been technically revised.

The main changes are as follows:

— clarification of the required resolution of the diagonal measuring system (4.4.3 and 5.4.3);

— modification of the required measurement accuracy (4.6.12 and 5.6.12).

Any feedback or questions on this document should be directed to the user’s national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2026 – All rights reserved

Fine ceramics (advanced ceramics, advanced technical ceramics) — Test method for hardness of monolithic ceramics at room temperature

1 Scope

This document specifies a test method for determining the Vickers and Knoop hardness of monolithic fine ceramics at room temperature.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4545-1, *Metallic materials — Knoop hardness test — Part 1: Test method*

ISO 4545-2, *Metallic materials — Knoop hardness test — Part 2: Verification and calibration of testing machines*

ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method*

ISO 6507-2, *Metallic materials — Vickers hardness test — Part 2: Verification and calibration of testing machines*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at https://www.electropedia.org/

3.1
Vickers hardness
value obtained by dividing the applied force by the projected area of the indentation, calculated from the arithmetic mean of the measured diagonals of the indentations, assuming that the indentation is a permanent imprint of the undeformed indenter

Note 1 to entry: Vickers hardness may be expressed either

a) with units of GPa, obtained by dividing the applied force in N by the projected area of the indentation in mm^2,

or

b) as a dimensionless Vickers hardness number, obtained by dividing the applied force in N by a scaling factor corresponding to the standard gravity (9,806 65 m/s^2) and by the projected area of the indentation in mm^2.

Note 2 to entry: The scaling factor ensures that the resulting dimensionless value is numerically identical to legacy calculations historically expressed in kgf/mm^2.

© ISO 2026 – All rights reserved

3.2
Vickers indenter
indenter in the shape of a right-angle pyramid with a square base and an angle between opposite faces of 136°

Note 1 to entry: See Table 1 and Figure 1.

3.3
Knoop hardness
value obtained by dividing the applied force by the projected area of the indentation, calculated from the measured long diagonal of the indentation, assuming that the indentation is a permanent imprint of the undeformed indenter

Note 1 to entry: The Knoop hardness may be expressed either

a) with units of GPa, obtained by dividing the applied force in N by the projected area of the indentation in mm^2,

or

b) as a dimensionless Knoop hardness number, obtained by dividing the applied force in N by a scaling factor corresponding to the standard gravity (9,806 65 m/s^2) and by the projected area of the indentation in mm^2.

Note 2 to entry: The scaling factor ensures that the resulting dimensionless value is numerically identical to legacy calculations historically expressed in kgf/mm^2.

3.4
Knoop indenter
indenter in the shape of a rhombic-based pyramid with the two angles between the opposite edges at 172,5° and 130°

Note 1 to entry: See Table 3 and Figure 6.

4 Vickers hardness

4.1 Principle

Forcing a diamond indenter in the form of a right-angle pyramid with a square base, and with a specified angle between opposite faces at the vertex into the surface of a test piece and measuring the length of the diagonals of the indentation left in the surface after removal of the test force, *F*. See Figure 1 and Figure 2.

4.2 Symbols, abbreviated terms and designations

4.2.1 See Table 1, Figure 1 and Figure 2.

4.2.2 The Vickers hardness is expressed either as a physical unit of pressure (GPa) or as a conventional, dimensionless hardness number.

When using SI unit (GPa), the hardness value is denoted by the unit symbol GPa, followed by the designation HV and a value representing the exact test force in Newtons (N)

EXAMPLE 1 15,0 GPa HV 9,807 N represents a Vickers hardness of 15,0 GPa, determined with a test force of 9,807 N.

When using the dimensionless Vickers hardness number, the value is denoted by the symbol HV, preceded by the hardness value and followed by a force indicator number representing the nominal test force (see Table 2).

EXAMPLE 2 1 500 HV 1 represents a Vickers hardness number of 1 500, determined with a test force indicator of 1 (corresponding to a nominal test force of 9,807 N).

© ISO 2026 – All rights reserved