INTERNATIONAL STANDARD

ISO 14916

Second edition
2017-03

Thermal spraying — Determination of tensile adhesive strength

Projection thermique — Mesure de l'adhérence par essais de traction

Reference number
ISO 14916:2017(E)

© ISO 2017



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword ... **iv**
Introduction ... **v**
1 Scope ... **1**
2 Normative references ... **1**
3 Terms and definitions ... **1**
4 Principles ... **2**
5 Equipment for testing and measuring and auxiliary equipment ... **3**
5.1 Test instruments ... 3
5.2 Measurement instrument ... 3
5.3 Specimen fixing device for bonding of the tensile adhesive specimen ... 4
6 Specimens ... **4**
6.1 Shape of specimens ... 4
6.2 Material of the specimen ... 6
6.3 Preparing the substrate and loading blocks ... 6
6.4 Preparing and spraying of the specimen ... 8
6.5 Manufacture of the specimens for tensile testing ... 9
6.5.1 Machining of the coated substrate block (or test disc) and preparation for bonding ... 9
6.5.2 Gluing the specimen ... 9
6.5.3 Bonding agent ... 9
6.6 Reference specimen ... 10
6.7 Number of specimens to be tested ... 10
7 Applying the testing ... **10**
8 Measurement readings and evaluation ... **11**
9 Test report — Documentation ... **12**
10 Possible sources of fault when preparing the specimens and on testing ... **13**
Annex A (informative) **Work instructions for gluing** ... **14**
Annex B (informative) **Recommendations for further auxiliary equipment** ... **17**
Annex C (informative) **Function areas on the tensile adhesive specimen and possibilities of fracture locations according to ASTM C633-13** ... **21**
Annex D (informative) **Record for the applied tensile adhesive test according to this document** ... **22**
Bibliography ... **26**

© ISO 2017 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*.

This second edition cancels and replaces the first edition (ISO 14916:1999), which has been technically revised.

© ISO 2017 – All rights reserved

Introduction

The determination of the tensile adhesive strength of a thermal spray coating can play an important role in the quality control of production. Deviations from the normal and qualified procedure can be recognized when preparing and spraying a component.

If the fracture occurs cohesively in the coating when applying the tensile adhesive strength test, the coating's strength in the direction normal to the surface is supplied. Influences of variations in spray conditions can be identified via proper interpretation of tensile test results. Microscopic investigations of the fractured surface can supply further information for judging the quality of the coating's structure.

A revision of the existing document had been required as a result of the identification of significant influences on the test results caused by the tensile test bonding procedure and by the properties of the adhesive itself. These findings were not adequately covered in the previous version of this document.

© ISO 2017 – All rights reserved

Thermal spraying — Determination of tensile adhesive strength

1 Scope

This document specifies the procedure to determine the tensile adhesive strength of thermally sprayed coatings under tension in the direction normal to the surface of the coating by applying a tensile test. By using this procedure, comparability of the test results is ensured.

The test is intended to determine the tensile adhesive strength between the thermally sprayed coating and the substrate material or between the bond and top coat and/or of the cohesive strength of the related coat of the coating system. In some cases, thermally sprayed coatings might have more than two layers. The method specified in this document applies also to determine the tensile adhesive strength between the interfaces of different layers in a coating system which consists of more than two layers.

This test is sufficient to compare coatings manufactured using same or similar feedstock materials and thermal spray processes with each other. The tensile adhesive strength test is not intended to provide absolute values for evaluation of the durability of coatings under operational use.

The test is used to assess the influence of substrate preparation, the spraying conditions and the process parameter on the tensile adhesive strength of thermally sprayed coatings. It can also be employed in order to monitor the consistency of the manufacturing and spraying processes.

NOTE This tensile test can also be applied to very thin coatings. Moreover, the infiltration of bonding agent into the thermally sprayed coatings containing a required level of porosity can be minimized using an appropriate bonding agent (foil rather than liquid). For further instructions, please refer to 6.5.3. This tensile test is inappropriate for determining the adhesive strength of fused spray coatings deposited using self-fluxing alloys due to their inherent high adhesion strength values.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 7500-1, *Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Calibration and verification of the force-measuring system*

ISO 14917, *Thermal spraying — Terminology, classification*

EN 13507, *Thermal spraying — Pre-treatment of surfaces of metallic parts and components for thermal spraying*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— IEC Electropedia: available at http://www.electropedia.org/

— ISO Online browsing platform: available at http://www.iso.org/obp

© ISO 2017 – All rights reserved

3.1
adhesive strength
R_H
tensile strength measured in the tension test, which is calculated from the quotient of the maximum load F_{max} and the cross-section area of the fractured face

3.2
adhesive failure
fracture, which runs along the interface between coating and substrate

Note 1 to entry: The coating will be totally separated away from the substrate.

Note 2 to entry: The inter-particle bonding (cohesive strength) is higher than the adhesive strength of the coating.

3.3
cohesive failure
fracture, which takes place within the coating

Note 1 to entry: The inter-particle bonding (cohesive strength) is lower than the adhesion strength of the coating.

3.4
adhesive-cohesive failure
fracture, which is partially located in the interface of the coating to the substrate and partially within the coating

3.5
internal adhesive strength
adhesive strength between the layers of a coating system, e.g. between a bond and top coat

3.6
test disc
test specimen formed like a disc coated on one side

Note 1 to entry: This is to be positioned and glued between two loading blocks when preparing the tensile test specimen.

3.7
reference specimen
specimen for determination of the strength of bonding agent

Note 1 to entry: This consists of two uncoated loading blocks glued together using the same joining procedure as for all other tested specimens.

4 Principles

The test methods listed in this document are recommended for quality control or characterization of coatings and/or coating systems in order to improve thermal spray processes or to develop coatings with increased adhesive and cohesive strength as well as with improved microstructure.

Thermally sprayed coatings exhibit as a thumb of rule — inherent to the characteristics of the process — a porous microstructure. Due to the requirements of their targeted application areas, they may contain a high level of porosity. Due to the possibility of infiltration of the coating by the bonding agent, the porous character of a coating can be unfavourable. The development of incorrect types or quantities of bonding agents can lead to significant changes in the coating properties so that the measurement results can be invalid.

Furthermore, only loads normal to the coating surface, which are free of bending or torsion moments, shall be applied during tensile loading. Therefore, adequate clamping and centring devices shall be used during the entire manufacturing process of the test specimens and during the testing.

© ISO 2017 – All rights reserved