INTERNATIONAL STANDARD

ISO 15314

Second edition
2018-08

Plastics — Methods for marine exposure

Plastiques — Méthodes d'exposition aux intempéries marines

Reference number
ISO 15314:2018(E)

© ISO 2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

 © ISO 2018 – All rights reserved

Contents

Page

Foreword ..... **iv**
Introduction ..... **v**
1 Scope **1**
2 Normative references **1**
3 Terms and definitions **1**
4 Principle **2**
4.1 General 2
4.2 Significance 2
5 Requirements for apparatus **3**
5.1 General requirements 3
5.2 Requirements for method A, floating exposure 3
5.3 Requirements for method B, partial-immersion exposure 4
5.4 Requirements for method C, shallow-immersion exposure 5
6 Test specimens **5**
6.1 Form and preparation 5
6.2 Number of test specimens 7
6.3 Storage and conditioning 8
7 Procedure **8**
7.1 General 8
7.2 Specific procedure for method A, marine floating exposure 9
7.3 Specific procedure for method B, partial-immersion exposure 9
7.4 Specific procedure for method C, shallow-immersion exposure 9
7.5 Evaluation of specimens after exposure 9
8 Test report **10**
Bibliography **12**

© ISO 2018 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 6, *Ageing, chemical and environmental resistance*.

This second edition cancels and replaces the first edition (ISO 15314:2004), which has been technically revised.

The main changes compared to the previous edition are as follows.

— The term “sunlight” has been replaced by “solar radiation” or “global solar radiation”.

— ISO 293, ISO 294-1, ISO 294-2, ISO 294-3, ISO 295 and ISO 3167 have been moved to the bibliography.

— In Clause 2, the withdrawn International Standard ISO 877 has been replaced by ISO 877-1, ISO 877-2, and ISO 877-3.

Any feedback or questions on this document should be directed to the user’s national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2018 – All rights reserved

Introduction

Plastics are often used in outdoor applications where they are immersed or partially immersed in water. In some cases, materials made from plastic are designed to float on water. In others, plastic articles that are discarded end up as floating debris. In addition to the effects of global solar radiation and heat, plastic polymers or products exposed in marine environments may be subjected to hydrolysis, water absorption, extraction of stabilizers, erosion by wave action, corrosion by salts and/or attack by seaborne microorganisms. These stresses are not simulated in typical weathering exposures conducted in accordance with ISO 877-1, ISO 877-2 and ISO 877-3. Therefore, it is necessary to define procedures that realistically and consistently stress plastic materials in the same way that they would be in products used or discarded in marine environments. This document describes three procedures for the exposure of plastic materials in the same way as they could be when used in marine environments.

There are four primary reasons why the rate of degradation of plastics exposed at sea can be different from that for the same plastic exposed on land:

a) exposure in moist conditions is known to accelerate degradation of some polymers — small amounts of absorbed water can act as a plasticizer, increasing accessibility of the matrix to oxygen, or can leach out stabilizing additives;

b) differences in heat build-up between plastics exposed in water or on the surface compared to plastics exposed on land;

c) the action of microorganisms that can shield the plastic from UV radiation or can enhance biodegradation processes;

d) the action of macroorganism settlements that can produce disfigurement of surfaces.

It is essential to establish appropriate exposure procedures in order to properly assess the performance of plastics used in marine environments, and to evaluate how long plastics discarded as litter will persist in marine environments.

© ISO 2018 – All rights reserved

Plastics — Methods for marine exposure

1 Scope

This document describes three methods for the exposure of plastics in a marine environment. Method A covers exposures where specimens float on the surface, method B covers exposures where specimens are partially immersed method C covers exposures where specimens are completely immersed. Although intended for marine (salt water) exposure, the methodology can be used with outdoor brackish water and fresh-water exposures as well. Direct weathering of plastics on land is described in ISO 877-1, ISO 877-2 and ISO 877-3.

Method A is particularly applicable to enhanced-degradability plastics where the environmental degradation under marine floating exposure is expected to be accelerated relative to that of regular plastic materials.

This document specifies the general requirements for the apparatus, and procedures for using the test methods described.

It lists properties that can be used to evaluate changes in plastics subjected to marine exposure. More specific information about methods for determining the changes in properties of plastics on exposure and reporting these results is given in ISO 4582.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 877-1, *Plastics — Methods of exposure to solar radiation — Part 1: General guidance*

ISO 877-2, *Plastics — Methods of exposure to solar radiation — Part 2: Direct weathering and exposure behind window glass*

ISO 877-3, *Plastics — Methods of exposure to solar radiation — Part 3: Intensified weathering using concentrated solar radiation*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 4582, *Plastics — Determination of changes in colour and variations in properties after exposure to glass-filtered solar radiation, natural weathering or laboratory radiation sources*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

© ISO 2018 – All rights reserved

3.1
control
<weathering> material which is of similar composition and construction to the test material, and which is exposed at the same time for comparison with the test material

Note 1 to entry: An example of the use of a control material would be when a formulation different from one currently being used is being evaluated. In that case, the control would be the plastic made with the original formulation.

3.2
file specimen
portion of the material to be tested which is stored under conditions in which it is stable, and is used for comparison between the exposed state and the original state

4 Principle

4.1 General

Replicate specimens of the appropriate size and shape are exposed floating on the surface of water, partially immersed in water or completely immersed in water. After the prescribed exposure interval, the specimens are removed from the water and tested/examined for changes in chemical, physical and/or appearance properties. In addition, the specimens may be tested for the type and severity of microbial growth or biofouling. Unless otherwise specified, test specimens are exposed in an unstrained state.

The exposure intervals at which the specimens are tested/examined are typically defined in terms of a given length of time. In some cases, however, the exposure interval may be expressed in terms of the total solar or solar ultraviolet radiant exposure. The climatic conditions are monitored during the exposure and reported with the other conditions of exposure.

4.2 Significance

The relative durability of materials in marine exposures can vary depending on the location of the exposure because of differences in ultraviolet radiation, ambient air temperature, water temperature, microorganisms, tidal action and contaminants in the water. Therefore, it cannot be assumed that results from one exposure in a particular location will be useful in determining the relative durability in another location. Exposures in several locations which represent a broad range of anticipated service conditions are recommended.

Exposure of the same material for the same length of time at different marine sites is not expected to result in identical degrees of degradation. This is also true for exposures at the same site, but during different seasons or in different years. Thus, the length of exposure is only a general indication of the extent of exposure and should always be considered in relation to the characteristics of the exposure site. Because of year-to-year climatic variations, results from a single exposure test cannot be used to predict the absolute rate at which a material degrades in marine exposures. Several years of repeat exposures are needed to get an “average” test result for a given location.

It is strongly recommended that at least one control material be part of any marine exposure evaluation. It is preferable to use two control materials, one with relatively good durability and one with relatively poor durability.

This document covers plastic materials in film, sheet, laminate, monofilament, fibre, rope or netting form. This includes, but is not limited to, packaging films, fishing gear, monofilament fibres and ropes.

When filaments, fibres, ropes or netting are exposed, it may be appropriate to apply a stress or use weights during exposure to give a more realistic estimate of performance in actual service.

When marine exposures are used to evaluate enhanced-degradability plastic material, a comparable material not formulated for enhanced degradability might be used for comparison. The test results can then be used to obtain the rate of breakdown of the enhanced-degradability material relative to the other

© ISO 2018 – All rights reserved