INTERNATIONAL STANDARD

ISO 15901-1

Second edition
2016-04-01

Evaluation of pore size distribution and porosity of solid materials by mercury porosimetry and gas adsorption —

Part 1: Mercury porosimetry

Evaluation de la distribution de taille des pores et la porosité des matériaux solides par porosimétrie à mercure et l'adsorption des gaz —

Partie 1: Porosimétrie à mercure

Reference number
ISO 15901-1:2016(E)

© ISO 2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword ... **iv**
Introduction ... **v**
1 Scope ... **1**
2 Normative references ... **1**
3 Terms and definitions ... **1**
4 Symbols and abbreviated terms ... **4**
5 Principles ... **5**
6 Apparatus and material ... **6**
6.1 Sample holder ... 6
6.2 Porosimeter ... 7
6.3 Mercury ... 7
7 Procedures for calibration and performance ... **7**
7.1 General ... 7
7.2 Pressure signal calibration ... 7
7.3 Volume signal calibration ... 7
7.4 Vacuum transducer calibration ... 7
7.5 Verification of porosimeter performance ... 8
8 Procedures ... **8**
8.1 Sampling ... 8
8.1.1 Obtaining a test sample ... 8
8.1.2 Quantity of sample ... 8
8.2 Method ... 9
8.2.1 Sample pre-treatment ... 9
8.2.2 Filling of the sample holder and evacuation ... 9
8.2.3 Filling the sample holder with mercury ... 9
8.2.4 Measurement ... 10
8.2.5 Completion of test ... 10
8.2.6 Blank and sample compression correction ... 10
9 Evaluation ... **11**
9.1 Determination of the pore size distribution ... 11
9.2 Determination of the specific pore volume ... 11
9.3 Determination of the specific surface area ... 12
9.4 Determination of the bulk and skeleton densities ... 12
9.5 Determination of the porosity ... 13
10 Reporting ... **13**
Annex A (informative) **Mercury porosimetry analysis results** ... **14**
Annex B (informative) **Recommendations for the safe handling of mercury** ... **17**
Bibliography ... **19**

© ISO 2016 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 24, *Particle characterization including sieving*, Subcommittee SC 4, *Particle characterization*.

This second edition cancels and replaces the first edition (ISO 15901-1:2005), which has been technically revised. It also incorporates the Corrigendum ISO 15901-1:2005/Cor 1:2007.

ISO 15901 consists of the following parts, under the general title *Evaluation of pore size distribution and porosity of solid materials by mercury porosimetry and gas adsorption*:

— *Part 1: Mercury porosimetry*

— *Part 2: Analysis of mesopores and macropores by gas adsorption*

— *Part 3: Analysis of micropores by gas adsorption*

© ISO 2016 – All rights reserved

Introduction

In general, different pores (micro-, meso-, and macropores) may be pictured as either apertures, channels or cavities within a solid body or as space (i.e. interstices or voids) between solid particles in a bed, compact or aggregate. Porosity is a term which is often used to indicate the porous nature of solid material and in this International Standard is more precisely defined as the ratio of the total pore volume of the accessible pores and voids to the volume of the particulate agglomerate. In addition to the accessible pores, a solid may contain closed pores which are isolated from the external surface and into which fluids are not able to penetrate. The characterization of closed pores is not covered in this International Standard.

Porous materials may take the form of fine or coarse powders, compacts, extrudates, sheets or monoliths. Their characterization usually involves the determination of the pore size distribution as well as the total accessible pore volume or porosity. For some purposes it is also necessary to study the pore shape and interconnectivity and to determine the internal and external specific surface area.

Porous materials have great technological importance, for example in the context of the following:

— controlled drug release;

— catalysis;

— gas separation;

— filtration including sterilization;

— materials technology;

— environmental protection and pollution control;

— natural reservoir rocks;

— building materials;

— polymers and ceramic.

It is well established that the performance of a porous solid (e.g. its strength, reactivity, permeability) is dependent on its pore structure. Many different methods have been developed for the characterization of pore structure. In view of the complexity of most porous solids, it is not surprising that the results obtained are not always in agreement and that no single technique can be relied upon to provide a complete picture of the pore structure. The choice of the most appropriate method depends on the application of the porous solid, its chemical and physical nature and the range of pore size.

The most commonly used methods are as follows:

a) Mercury porosimetry, where the pores are filled with mercury under pressure. This method is suitable for many materials with pores in the approximate diameter range of 0,004 µm to 400 µm.

b) Meso- and macropore analysis by gas adsorption, where the pores are characterized by adsorbing a gas, such as nitrogen at liquid nitrogen temperature. The method is used for pores in the approximate diameter range of 0,002 µm to 0,1 µm (2 nm to 100 nm).

c) Micropore analysis by gas adsorption, where the pores are characterized by adsorbing a gas, such as nitrogen at liquid nitrogen temperature. The method is used for pores in the approximate diameter range of 0,4 nm to 2 nm.

© ISO 2016 – All rights reserved

Evaluation of pore size distribution and porosity of solid materials by mercury porosimetry and gas adsorption —

Part 1: Mercury porosimetry

WARNING — The use of this International Standard may involve hazardous materials, operations and equipment. This International Standard does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this International Standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This International Standard describes a method for the evaluation of the pore size distribution and the specific surface area of pores in solids by mercury porosimetry according to the method of Ritter and Drake[1][2]. It is a comparative test, usually destructive due to mercury contamination, in which the volume of mercury penetrating a pore or void is determined as a function of an applied hydrostatic pressure, which can be related to a pore diameter.

Practical considerations presently limit the maximum applied absolute pressure to about 400 MPa (60 000 psi) corresponding to a minimum equivalent pore diameter of approximately 4 nm. The maximum diameter is limited for samples having a significant depth due to the difference in hydrostatic head of mercury from the top to the bottom of the sample. For the most purposes, this limit can be regarded as 400 µm. The measurements cover inter-particle and intra-particle porosity. In general, without additional information from other methods it is difficult to distinguish between these porosities where they co-exist. The method is suitable for the study of most porous materials non-wettable by mercury. Samples that amalgamate with mercury, such as certain metals, e.g. gold, aluminium, copper, nickel and silver, can be unsuitable with this technique or can require a preliminary passivation. Under the applied pressure some materials are deformed, compacted or destroyed, whereby open pores may be collapsed and closed pores opened. In some cases it may be possible to apply sample compressibility corrections and useful comparative data may still be obtainable. For these reasons, the mercury porosimetry technique is considered to be comparative.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3165, *Sampling of chemical products for industrial use — Safety in sampling*

ISO 14488, *Particulate materials* — Sampling and sample splitting for the determination of particulate properties

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1
porosimeter
instrument for measuring pore volume and pore size distribution

© ISO 2016 – All rights reserved

3.2
porosimetry
methods for the estimation of pore volume, pore size distribution, and porosity

3.3
porous solid
solid with cavities or channels which are deeper than they are wide

3.4
powder
porous or nonporous solid composed of discrete particles with maximum dimension less than about 1 mm, powders with a particle size below about 1 μm are often referred to as fine powders

3.5
pore
cavity or channel which is deeper than it is wide, otherwise it is part of the material's roughness

3.6
void
interstice
space between particles, i.e. interparticle pore

3.7
macropore
pore of internal width greater than 50 nm

3.8
mesopore
pore of internal width between 2 nm and 50 nm

3.9
micropore
pore of internal width less than 2 nm

3.10
closed pore
pore totally enclosed by its walls and hence not interconnecting with other pores and not accessible to fluids

3.11
open pore
pore not totally enclosed by its walls and open to the surface either directly or by interconnecting with other pores and therefore accessible to fluid

3.12
ink bottle pore
narrow necked open pore

3.13
pore size
internal pore width (for example, the diameter of a cylindrical pore or the distance between the opposite walls of a slit) which is a representative value of various sizes of vacant space inside a porous material

3.14
pore volume
volume of open pores unless otherwise stated

© ISO 2016 – All rights reserved

3.15
pore diameter
diameter of a pore in a model in which the pores typically are assumed to be cylindrical in shape and which is calculated from data obtained by a specified procedure

3.16
median pore diameter
diameter that corresponds to the 50th percentile of pore volume, i.e. the diameter for which one half of the pore volume is found to be in larger pores and one half is found to be in smaller pores

3.17
modal pore diameter
mode
pore diameter of the maximum in a differential pore size distribution curve

3.18
hydraulic pore diameter
average pore diameter, calculated as the ratio of pore volume multiplied by four to pore area.

3.19
bulk volume
volume of powder or solids, including all pores (open and closed) and interstitial spaces between particles.

3.20
bulk density
ratio of sample mass to bulk volume

3.21
skeleton volume
volume of the sample including the volume of closed pores (if present) but excluding the volumes of open pores as well as that of void spaces between particles within the bulk sample

[SOURCE: ISO 12154]

3.22
skeleton density
ratio of sample mass to skeleton volume

3.23
apparent volume
total volume of the solid constituents of the sample including closed pores and pores inaccessible or not detectable by the stated method;

3.24
apparent density
ratio of sample mass to apparent volume

3.25
envelope volume
total volume of the particle, including closed and open pores, but excluding void space between the individual particles

3.26
envelope density
ratio of sample mass to envelope volume

3.27
porosity
ratio of the volume of the accessible pores and voids to the bulk volume occupied by an amount of the solid

© ISO 2016 – All rights reserved

3.28
interparticle porosity
ratio of the volume of void space between the individual particles to the bulk volume of the particles or powder

3.29
intraparticle porosity
ratio of the volume of open pores inside the individual particles of a particulate or divided solid sample to the bulk volume occupied by the sample

3.30
surface area
extent of accessible surface area as determined by a given method under stated conditions

3.31
surface tension
work required to increase a surface area divided by that area.

3.32
contact angle
angle at which a liquid/vapour interface meets the surface of a solid material

4 Symbols and abbreviated terms

For the purposes of this document, the following symbols apply.

Symbol	Term	SI unit	Derived and obsolete units	Conversion factors
P	pressure	Pa	MPa, psia, Torr, mmHg	1 MPa = 10^6 Pa 1 psi = 1 lb in^{-2} = 6 895 Pa 1 Torr = 1 mmHg = 133,32 Pa
d_p	pore diameter	m	nm, µm, Å	1nm = 10^{-9} m, 1µm = 10^{-6} m, 1 Å = 10^{-10} m
t	time	s	h	1 h = 3 600 s
S	specific surface area	$m^2 \cdot kg^{-1}$	$m^2 \cdot g^{-1}$	
V_{Hg}	intruded volume of mercury	m^3	cm^3, mm^3	10^3 mm^3 = 1 cm^3 = 10^{-6} m^3
$V_{Hg,0}$	initial intruded volume of mercury	m^3	cm^3, mm^3	
$V_{Hg,max}$	total intruded volume of mercury	m^3	cm^3, mm^3	
V_p	specific pore volume	$m^3 \cdot kg^{-1}$	$mm^3 \cdot g^{-1}$ $cm^3 \cdot g^{-1}$	
γ	surface tension of mercury	$N \cdot m^{-1}$	$dyne \cdot cm^{-1}$	1 $dyne \cdot cm^{-1}$ = 10^{-3} $N \cdot m^{-1}$
ρ_{Hg}	density of mercury	$kg \cdot m^{-3}$	$g \cdot cm^{-3}$	1 $g \cdot cm^{-3}$ = 10^3 $kg \cdot m^{-3}$
Θ	contact angle of mercury at the sample	rad	°	1° = (π/180) rad
m_S	mass of the test sample	kg	g	
m_{SH}	mass of empty sample holder	kg	g	
m_{SH+S}	mass of sample holder with sample	kg	g	
$m_{SH+S+Hg}$	mass of sample holder with sample and filled with mercury	kg	g	

© ISO 2016 – All rights reserved