INTERNATIONAL STANDARD

ISO 16148

Second edition
2016-04-15

Gas cylinders — Refillable seamless steel gas cylinders and tubes — Acoustic emission examination (AT) and follow-up ultrasonic examination (UT) for periodic inspection and testing

Bouteilles à gaz — Bouteilles à gaz rechargeables en acier sans soudure et tubes — Essais d'émission acoustique et examen ultrasonique complémentaire pour l'inspection périodique et l'essai

Reference number
ISO 16148:2016(E)

© ISO 2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword ... **iv**
Introduction ... **v**
1 Scope ... **1**
2 Normative references ... **1**
3 Terms and definitions ... **1**
4 Operational principles ... **3**
5 Personnel qualification ... **3**
6 Special considerations to ensure valid tests ... **4**
6.1 General ... 4
6.2 Acoustic emission examination methods ... 4
6.3 Pressurization ... 4
6.4 Safety precautions ... 5
7 Acoustic emission examination equipment ... **5**
8 Acoustic emission examination calibration and equipment verification ... **7**
8.1 Calibration ... 7
8.2 Equipment verification ... 7
9 Overall procedure ... **7**
10 Real-time evaluation criteria ... **8**
11 AT test report ... **9**
12 Follow-up ultrasonic examination ... **10**
Annex A (normative) **Ultrasonic examination (UT) follow-up to acoustic emission examination (AT)** ... **11**
Annex B (normative) **AT equipment specifications** ... **17**
Annex C (normative) **Example instrument settings, examination methods and rejection criteria for MAE** ... **19**
Annex D (informative) **Alternative method for source location** ... **22**
Annex E (informative) **Distance amplitude correction procedures** ... **24**
Bibliography ... **27**

© ISO 2016 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 58, *Gas cylinders*, Subcommittee SC 4, *Operational requirements for gas cylinders*.

This second edition cancels and replaces the first edition (ISO 16148:2006), which has been technically revised. The changes include

a) expansion of the scope to include tubes of water capacity up to 3 000 l used for compressed and liquefied gases, and

b) addition of procedures for ultrasonic examination (UT) follow-up during periodic inspection, as described in the new Annex A.

© ISO 2016 – All rights reserved

Introduction

In recent years, new non-destructive examination (NDE) techniques have been successfully introduced as an alternative to the conventional testing procedures of gas cylinders, tubes and other cylinders at the time of periodic inspection and testing.

One of the alternative NDE methods for certain applications is acoustic emission examination (AT), which has proved to be an acceptable test method applied during periodic inspection and testing in some countries.

The test method requires pressurization to a level greater than the normal filling pressure.

The pressurization medium can be either gas or liquid.

Acoustic emission (AE) measurements are used to detect and locate emission sources. Other NDE methods are needed to evaluate the significance of AE detected sources. One of the alternative NDE methods used as a follow-up to AT is ultrasonic examination (UT), which has proved to be an acceptable testing method applied during periodic inspection and testing. The purpose of this International Standard is to provide a procedure for locating, detecting and evaluating the relevance of AE indications such as those from longitudinally oriented crack-like discontinuities. The shear wave (angle beam) UT method is intended to be used immediately following AT to evaluate the significance of AE indications.

This International Standard describes two methods of AT, defined as Method A and Method B, and a method of follow-up UT.

With the agreement of the testing and certifying body approved by the competent authority of the country of approval, the hydraulic pressure test of cylinders and tubes can be replaced by an equivalent AT/UT Method A or B.

This International Standard is intended to be used under a variety of national regulatory regimes, but has been written so that it is suitable for the application of Reference.[1] Attention is drawn to requirements in the specified relevant national regulations of the country (countries) where the cylinders are intended to be used that might override the requirements given in this International Standard. Where there is any conflict between this International Standard and any applicable regulation, the regulation always takes precedence.

© ISO 2016 – All rights reserved

Gas cylinders — Refillable seamless steel gas cylinders and tubes — Acoustic emission examination (AT) and follow-up ultrasonic examination (UT) for periodic inspection and testing

1 Scope

This International Standard gives procedures for the use of acoustic emission examination (AT) and ultrasonic examination (UT) follow-up during the periodic inspection and testing of seamless steel cylinders and tubes with a water capacity of up to 3 000 l used for compressed and liquefied gases. This examination provides acoustic emission (AE) indications and locations that are evaluated by a secondary examination using UT for a possible flaw in the cylinder or tube. Methods other than UT for the secondary examination are not covered by this International Standard.

This International Standard does not cover composite cylinders.

CAUTION — Some of the tests specified in this International Standard involve the use of processes which could lead to a hazardous situation.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for is application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5577, *Non-destructive testing — Ultrasonic inspection — Vocabulary*

ISO 6406, *Gas cylinders — Seamless steel gas cylinders — Periodic inspection and testing*

ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel*

ISO 12716, *Non-destructive testing — Acoustic emission inspection — Vocabulary*

ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories*

EN 13477-1, *Non-destructive testing — Acoustic emission — Equipment characterisation — Part 1: Equipment description*

EN 13477-2, *Non-destructive testing — Acoustic emission — Equipment characterisation — Part 2: Verification of operating characteristic*

ASTM E1419, *Standard Practice for Examination of Seamless, Gas-Filled, Pressure Vessels using Acoustic Emission*

ASNT SNT-TC-1A, *Recommended Practice for Personnel Qualification and Certification in Nondestructive Testing*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 5577, ISO 12716 and the following apply.

© ISO 2016 – All rights reserved

3.1
critical flaw
imperfection or damage that is large enough to exhibit unstable crack growth under certain service conditions

3.2
working pressure
settled pressure of a compressed gas at a uniform reference temperature of 15 °C in a full gas cylinder

Note 1 to entry: In North America service pressure is often used to indicate a similar condition, usually at 21,1 °C (70 °F).

Note 2 to entry: In East Asia, service pressure is often used to indicate a similar condition, usually at 35 °C.

[SOURCE: ISO 10286:2015, definition 736]

3.3
normal filling pressure
level to which a cylinder or tube is pressurized during filling

Note 1 to entry: This is usually greater than the marked working pressure due to the heat of compression.

3.4
acoustic emission test pressure
AT pressure
maximum pressure at which acoustic emission testing is performed

3.5
acoustic emission pressure test range
range of pressure during which acoustic emission is monitored

3.6
Method A
acoustic emission testing performed using pneumatic pressurization to at least 110 % of the normal filling pressure

Note 1 to entry: Normally performed on an assembly of cylinders (e.g. bundle) or tubes (e.g. tube trailer).

3.7
Method B
acoustic emission testing performed during the hydrostatic proof pressurization to the re-test pressure on each cylinder or tube

3.8
secondary AE sources
emissions not generated by actual crack propagation and plastic deformation

Note 1 to entry: Contact between the surfaces of a discontinuity as the cylinder expands, fracture or rubbing of mill scale within a discontinuity as the cylinder expands are examples of secondary AE sources.

3.9
calibration ring
section cut from similar cylinder material used for the calibration of the follow-up UT

3.10
distance amplitude correction curve
DAC curve
curve generated during the standardization process that accounts for the loss of amplitude of the returning signal as a result of signal travel distance

© ISO 2016 – All rights reserved

3.11
shear wave ultrasonic search unit
block of material that conforms to the curvature of the surface of the test object and orients the ultrasonic transducer at an angle which transmits and receives shear waves

3.12
ultrasonic couplant
fluid medium that forms a thin, bubble-free layer between the search unit and the test object

3.13
skip distance
in angle beam (shear wave) examination, distance along the test surface from the sound entry point to the point at which the sound returns to the same surface

Note 1 to entry: It can be considered the top surface distance of a complete wave path of sound in the test material.

3.14
modal acoustic emission
MAE
branch of AE (acoustic emission) focused on the detection and analysis of the actual sound waves produced at fracture sites from crack growths or surface rubbing

4 Operational principles

When cylinders or tubes containing discontinuities are pressurized, sound waves (AE) can be produced by several different sources (e.g. secondary sources or actual propagation of cracks). These sources can produce AE indications at pressures less than, equal to or greater than working pressure. The sound waves travel throughout the structure.

Piezoelectric sensors mounted on a cylinder or tube surface respond to sound waves. They are connected to a signal processor, which records the signal parameters associated with the passage of the waves under the sensor. Sound waves travel at assumed constant speeds. With at least two sensors, one mounted at each end of a cylinder or tube, the approximate location of event sources is derived from the measured arrival time of sound waves at the sensors.

If measured emissions exceed the specified levels over a linear distance on the cylinder, then such locations shall undergo a secondary inspection (e.g. by UT) in order to verify the presence of discontinuities and to measure their dimensions. From this secondary inspection, if the depth of the discontinuity exceeds the specified limit (that is, a limit based on a number of factors, i.e. cylinder material, wall thickness, fatigue crack growth rate estimates, fracture critical size calculations and any practical experience), then the cylinder shall be removed from service.

If, after the examination, a recalibration of the AT equipment proves negative, the relevant cylinder shall be re-examined by a non-destructive examination (NDE) method other than AT Method A.

5 Personnel qualification

The AT and UT equipment shall be operated, and its operation supervised, by competent personnel who meet the requirements of ISO 9712 or an equivalent standard (e.g., ASNT SNT TC 1A) as authorized by the Level III operator. The operator shall meet the requirements for Level I and shall be supervised by a Level II person. The testing organization shall retain a Level III operator (company employee or a third party) to oversee the entire AT and UT programme.

© ISO 2016 – All rights reserved