INTERNATIONAL STANDARD

ISO 16293-4

First edition
2016-12-01

Glass in building — Basic soda lime silicate glass products —

Part 4: Wired patterned glass

Verre dans la construction — Produits de base: verre de silicate sodo-calcique —

Partie 4: Verre armé

Reference number
ISO 16293-4:2016(E)

© ISO 2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword ... **iv**

1 Scope ... **1**

2 Normative references ... **1**

3 Terms and definitions ... **1**

4 Dimensional requirements ... **3**
4.1 Thickness ... 3
4.1.1 General ... 3
4.1.2 Tolerances ... 3
4.2 Length, width and squareness ... 3
4.3 Wire mesh ... 4

5 Quality requirements ... **4**
5.1 General ... 4
5.2 Methods of observation and measurement ... 4
5.2.1 Visual faults ... 4
5.2.2 Edge defects for final cut sizes ... 5
5.3 Acceptance levels ... 6
5.3.1 Spot faults ... 6
5.3.2 Linear/extended faults ... 7
5.3.3 Pattern faults ... 7
5.3.4 Wire faults ... 7
5.3.5 Edge defects for final cut sizes ... 8

6 Designation ... **8**

Bibliography ... **9**

© ISO 2016 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 160, *Glass in Building*, Subcommittee SC 1, *Product considerations*.

A list of all parts in the ISO 16293 series can be found on the ISO website.

© ISO 2016 – All rights reserved

Glass in building — Basic soda lime silicate glass products —

Part 4: Wired patterned glass

1 Scope

This document specifies dimensional and minimum quality requirements (in respect of visual, pattern and wire faults) for wired patterned glass, as defined in ISO 16293-1, for use in building.

This document applies only to wired patterned glass supplied in rectangular panes, in stock sizes and in final cut sizes.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 16293-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:


— IEC Electropedia: available at http://www.electropedia.org/

— ISO Online browsing platform: available at http://www.iso.org/obp

3.1
length
H
dimension of the straight edge of the glass parallel to the direction of draw of the glass ribbon

Note 1 to entry: See Figure 1.

[SOURCE: ISO 11485-1:2011, 2.26, modified]



Key

l direction of draw
H length
B width

Figure 1 — Relationship between length, width and direction of draw

© ISO 2016 – All rights reserved

3.2
width
B
dimension of the edge of the glass perpendicular to the direction of the glass ribbon

Note 1 to entry: See Figure 1.

3.3
stock size
glass sizes that are intended to be re-cut to obtain *final cut sizes* (3.4)

3.4
final cut size
pane of glass that has been cut down to the dimensions being required either for installation or processing into a final product, e.g. insulating glass units of those dimensions

Note 1 to entry: The minimum final cut size shall have dimensions *H* or *B* not less than 100 mm and a minimum surface area of not less than 0,05m^2.

3.5
visual fault
fault which alters the visual quality of the glass

Note 1 to entry: They include spot faults, linear/extended faults, pattern faults and wire faults.

3.6
spot fault
fault which can be in or on the glass in the form of gaseous inclusion, solid inclusion, mark or deposit of small size

3.7
linear/extended fault
faults which can be on or in the glass, in the form of deposits, marks or scratches which occupy an extended length or area

3.8
pattern fault
deviation of the pattern (3.9) relative to a reference, e.g. line or straight edge

3.9
deviation of the pattern
deviation, *u*, *v* or *w*, of the pattern

3.10
wire fault
deviation of the wire (3.11), penetration of the glass surface by the wire or break in the wire in the body of the glass

3.11
deviation of the wire
deviation, *x*, *y*, *z* of the wire relative to a reference, e.g. line or straight edge

3.12
edge defect
defect which can occur on the edge of a glass sheet in the form of entrant and emergent faults and/or bevels

© ISO 2016 – All rights reserved