INTERNATIONAL STANDARD

ISO 16478

First edition
2023-11

Thermal insulation products — Vacuum insulation panels (VIPs) — Specification

Reference number
ISO 16478:2023(E)

© ISO 2023



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

© ISO 2023 – All rights reserved

Contents

Page

Foreword ... **iv**

1 Scope ... **1**

2 Normative references ... **1**

3 Terms, definitions, symbols and units ... **2**
3.1 Terms and definitions ... 2
3.2 Symbols and units ... 6

4 Requirements ... **10**
4.1 General ... 10
4.2 Thermal resistance and thermal conductivity ... 10
4.2.1 General ... 10
4.2.2 Initial COP thermal properties ... 10
4.2.3 Size dependent value ... 10
4.3 Length, width, squareness and flatness ... 11
4.4 Thickness ... 12
4.5 Dimensional stability ... 12

5 Sampling ... **12**

6 Test methods ... **12**
6.1 General ... 12
6.2 Thermal resistance and thermal conductivity ... 13
6.2.1 General ... 13
6.2.2 Initial COP thermal properties ... 13
6.2.3 Linear thermal transmittance ... 13
6.2.4 Aged thermal properties (25 years) ... 13
6.3 Length, width, squareness and flatness ... 14
6.3.1 General ... 14
6.3.2 Length and width ... 14
6.3.3 Squareness on length and width ... 14
6.3.4 Flatness ... 14
6.4 Thickness ... 14
6.5 Dimensional stability ... 15

7 Conformity control ... **15**

8 Marking and labelling ... **15**

Annex A (normative) **Determination of linear thermal transmittance** ... **16**

Annex B (normative) **Determination of aged value for silica core VIP** ... **22**

Annex C (normative) **Determination of the aged values for glass fibre core VIP** ... **28**

Annex D (normative) **Relationship between $\lambda(p)$ and the inner pressure** ... **34**

Annex E (normative) **Product type determination (PTD) and factory production control (FPC)** ... **36**

Annex F (informative) **Additional properties** ... **37**

Annex G (informative) **Measurement of inner pressure** ... **41**

Annex H (informative) **Mounting and fixing procedure for reaction to fire tests** ... **47**

Bibliography ... **52**

© ISO 2023 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 163, *Thermal performance and energy use in the built environment*, Subcommittee SC 3, *Thermal insulation products, components and systems*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2023 – All rights reserved

Thermal insulation products — Vacuum insulation panels (VIPs) — Specification

1 Scope

This document:

— defines requirements for vacuum insulation panels (VIPs) with silica or glass fibre core, which are used for thermal insulation of buildings;

— outlines required product properties, their performance, test methods and rules for conformity evaluations, identification and labelling;

— provides a test method to determine ageing factors and the influence of the linear thermal bridges at the edges.

This document is applicable to all types of silica and glass fibre core VIPs, independent of the type of envelope. In the case of a glass fibre core VIP, it is only applicable to VIPs with desiccants whose service life is ≥ 25 years.

This document is not applicable to:

— any specific installation and application requirements;

— products intended to be used for the insulation of building equipment and industrial installations.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1182, *Reaction to fire tests for products — Non-combustibility test*

ISO 1716, *Reaction to fire tests for products — Determination of the gross heat of combustion (calorific value)*

ISO 3529-1, *Vacuum technology — Vocabulary — Part 1: General terms*

ISO 3529-2, *Vacuum technology — Vocabulary — Part 2: Vacuum pumps and related terms*

ISO 3529-3, *Vacuum technology — Vocabulary — Part 3: Total and partial pressure vacuum gauges*

ISO 8301, *Thermal insulation — Determination of steady-state thermal resistance and related properties — Heat flow meter apparatus*

ISO 8302, *Thermal insulation — Determination of steady-state thermal resistance and related properties — Guarded hot plate apparatus*

ISO 8990, *Thermal insulation — Determination of steady-state thermal transmission properties — Calibrated and guarded hot box*

ISO 10211, *Thermal bridges in building construction — Heat flows and surface temperatures — Detailed calculations*

ISO 10456, *Building materials and products — Hygrothermal properties — Tabulated design values and procedures for determining declared and design thermal values*

© ISO 2023 – All rights reserved

ISO 11925-2, *Reaction to fire tests — Ignitability of products subjected to direct impingement of flame — Part 2: Single-flame source test*

ISO 12136, *Reaction to fire tests — Measurement of material properties using a fire propagation apparatus*

ISO 12567-1, *Thermal performance of windows and doors — Determination of thermal transmittance by the hot-box method — Part 1: Complete windows and doors*

ISO 12576-1:2001, *Thermal insulation — Insulating materials and products for buildings — Conformity control systems — Part 1: Factory-made products*

ISO 29465, *Thermal insulating products for building applications — Determination of length and width*

ISO 29466, *Thermal insulating products for building applications — Determination of thickness*

ISO 29467, *Thermal insulating products for building applications — Determination of squareness*

ISO 29468, *Thermal insulating products for building applications — Determination of flatness*

ISO 29472, *Thermal insulating products for building applications — Determination of dimensional stability under specified temperature and humidity conditions*

EN 13501-1, *Fire classification (Euroclasses) of construction products and building elements — Classification using test data from reaction to fire tests*

EN 13823, *Reaction to fire tests for building products — Building products excluding floorings exposed to the thermal attack by a single burning item*

3 Terms, definitions, symbols and units

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp


— IEC Electropedia: available at https://www.electropedia.org/

3.1 Terms and definitions

3.1.1
vacuum insulation panel
VIP
insulation element containing open porous *core material* (3.1.4) and an *adsorbent* (3.1.8) within an *envelope* (3.1.5), where the *inner pressure* (3.1.10) inside the envelope is significantly lower, close to the vacuum (i.e. zero pressure), than the ambient air pressure

Note 1 to entry: A schematic view of a VIP is shown in Figure 1.

© ISO 2023 – All rights reserved



Key

1 core material
2 envelope
3 adsorbent
d thickness (3.1.17)
l_w working length (3.1.11)

Figure 1 — Schematic view of VIP

3.1.2
silica core VIP
vacuum insulation panel (VIP) (3.1.1) using fumed silica or other comparable silica powders as *core material* (3.1.4)

3.1.3
glass fibre core VIP
vacuum insulation panel (VIP) (3.1.1) using glass fibre as *core material* (3.1.4), and generally containing an *adsorbent* (3.1.8)

3.1.4
core material
open porous insulation material constituting the main component inside the *vacuum insulation panel (VIP)* (3.1.1) *envelope* (3.1.5)

3.1.5
envelope
barrier layer(s) of the *vacuum insulation panel (VIP)* (3.1.1) resisting gas or vapour permeation into and securing the vacuum inside the VIP

3.1.6
metallized film
MF
laminated film containing a high barrier performance metallic thin layer produced by chemical/physical deposition

3.1.7
aluminium foil laminated film
AF
laminated film containing aluminium foil as a gas barrier layer

3.1.8
adsorbent
material adsorbing either water vapour or dry air, or both, physically or chemically

3.1.9
desiccant
material added inside the *envelope* (3.1.5) for the purpose of adsorbing water vapour

EXAMPLE CaO.

© ISO 2023 – All rights reserved

3.1.10
inner pressure
total gas pressure within the *vacuum insulation panel (VIP)* (3.1.1)

3.1.11
working length
l_w
longer linear dimension of the major surface of the test specimen

Note 1 to entry: See Figure 2.

3.1.12
working width
w_w
shorter linear dimension of the major surface of the test specimen, measured at right angles to the *working length* (3.1.11)

Note 1 to entry: See Figure 2.

3.1.13
core length
l_c
longer linear dimension of the *core material* (3.1.4) of the test specimen

Note 1 to entry: See Figure 2.

3.1.14
core width
w_c
shorter linear dimension of the *core material* (3.1.4) of the test specimen, measured at right angles to the *core length* (3.1.13)

3.1.15
length of edge seal
l_2
longer linear dimension of the edge seal of the test specimen

Note 1 to entry: See Figure 2.

3.1.16
width of edge seal
w_2
shorter linear dimension of the edge seal of the test specimen, measured at right angles to the *edge seal length* (3.1.19)

Note 1 to entry: See Figure 2.

3.1.17
thickness
d
linear dimension measured perpendicularly to the length and width plane

3.1.18
surface area
A_{sur}
area of gas permeation plane of the test specimen

Note 1 to entry A_{sur} shall be determined by Formulae (1) or (2).

metallized film (MF) (3.1.6) on both sides:

$$A_{sur} = l_2 \times w_2 \times 2 \quad (1)$$

© ISO 2023 – All rights reserved


MF on single side:

$$A_{sur} = l_2 \times w_2 \quad (2)$$


3.1.19
edge seal length
l_{es}
total length of the edge seal of the test specimen

Note 1 to entry: l_{es} shall be determined by Formula (3).


$$l_{es} = l_2 \times 2 + w_2 \times 2 \quad (3)$$




a)



b)



c)



d)

© ISO 2023 – All rights reserved

Key

1 core material (3.1.4)
2 envelope (3.1.5)
3 adsorbent or desiccant
4 edge seal
l_c core length (3.1.13)
l_w working length (3.1.11)
l_2 length of edge seal (3.1.15)
w_w working width (3.1.12)
w_2 width of edge seal (3.1.16)

Figure 2 — Dimensions of a VIP

3.1.20
centre of panel
COP
area of the *vacuum insulation panel (VIP)* (3.1.1) not affected by the *edge effect* (3.1.21)

3.1.21
edge effect
thermal bridging along the edge due to higher thermal conductivity of the outer *envelope* (3.1.5) compared to the *core material* (3.1.4)

3.1.22
aged value
expected mean thermal conductivity value at 25 years in specified laboratory conditions

3.2 Symbols and units

A	surface area of the VIP	m^2
A_m	metering area of the GHP or HFM apparatus used for measurement	m^2
A_N	nominal surface area of the VIP	m^2
A_{sp}	area of the specimen measured by hot box method	m^2
A_{sur}	surface area of gas permeation plane of the product	m^2
$A_{sur,sp}$	surface area of gas permeation plane of the specimen	m^2
C_{des}	capacity of the desiccant	g/g
$C_{des,20\ \%}$	capacity of the desiccant including a safety margin of 20 %	g/g
d	thickness	m
$d_{ambient}$	thickness of the ventilated VIP	m
d_N	nominal thickness of the product	m
d_{VIP}	thickness of the VIP	m
f_{air}	acceleration factor for dry air of the envelope	-

© ISO 2023 – All rights reserved

f_v	acceleration factor for water vapour of the VIP envelope	-
k	factor related to the number of test results available	-
l	length	m
l_c	core length	m
l_2	length of edge seal	m
l_w	working length	m
l_ψ	length of the joints within the metering area	m
m_1	initial water amount of core material	g
m_2	amount of adsorbed water vapour	g
m_{25a}	water vapour amount adsorbed over 25 years	g
m_{des}	mass of desiccant	g
$m_{des,1a}$	mass of the desiccant after test	g
$m_{des,1d}$	sufficient amount of desiccant	g
$m_{des,2a}$	mass of the desiccant before acceleration test	g
$m_{des,2c}$	mass of the desiccant after acceleration test	g
$m_{des,0}$	mass of the fully dried desiccant	g
$m_{des,sat}$	mass of the saturated desiccant	g
$m'_{t,air,\ 23/50}$	inner dry air mass increase rate at 23 °C, 50 % relative humidity (RH)	g/day
$m'_{t,v,\ 23/50}$	water vapour mass increase rate at 23 °C, 50 % RH	g/day
N	number of test results	-
P_{air}	air permeability of the VIP envelope	$m^3 \cdot Pa/(m^2 \cdot s)$
$P_{air,total,23/50}$	air permeability of the VIP envelope of the product at 23 °C, 50 % RH	g/(day·Pa)
$P_{air,total,sp,23/50}$	air permeability of the VIP envelope of the specimen at 23 °C, 50 % RH	g/(day·Pa)
$P_{air,A,23/50}$	air permeability of the film surface at 23 °C, 50 % RH	$g/(m^2 \cdot day \cdot Pa)$
$P_{air,l,23/50}$	air permeability of the edge seal at 23 °C, 50 % RH	g/(m·day·Pa)
P_v	water intake rate of the VIP envelope	$kg/(m^2 \cdot s)$
p_{air}	air pressure inside the VIP	Pa
$p_{air,atm}$	atmospheric pressure	Pa
p_{lim}	maximum value of the inner pressure measured at least 24 hours after production	Pa

© ISO 2023 – All rights reserved

p_v	water vapour pressure inside the VIP	Pa
$p_{v,out}$	atmospheric water vapour pressure	Pa
p_0	initial value of the inner pressure	Pa
$p_{1/2}$	inner pressure of VIP, where λ increases by 1/2 of the thermal conductivity of still air	Pa
$p'_{t,air,23/50}$	inner pressure increase rate at 23 °C, 50 % RH	Pa/day
$p'_{t,air,40}$	inner pressure increase rate at 40 °C	Pa/day
$p'_{t,air,60}$	inner pressure increase rate at 60 °C	Pa/day
$p'_{t,air,80}$	inner pressure increase rate at 80 °C	Pa/day
R_{aux}	thermal resistance of the auxiliary material	$m^2 \cdot K/W$
R_D	declared thermal resistance	$m^2 \cdot K/W$
R_{eq}	thermal resistance obtained by assuming the entire surface to be homogeneous calculated by the thermal transmittance	$m^2 \cdot K/W$
$R_{s,t}$	total surface thermal resistance	$m^2 \cdot K/W$
R_{mean}	mean thermal resistance	$m^2 \cdot K/W$
R_{tot}	thermal resistance of VIP plus auxiliary material	$m^2 \cdot K/W$
$R_{90/90}$	90 % fractile with a confidence level of 90 % for the thermal resistance	$m^2 \cdot K/W$
S	top surface area (working length x working width) of the VIP	m^2
S_b	deviation from squareness on width or length	mm/m
S_{MAX}	deviation from flatness	mm
S_N	nominal perimeter of the product	m
s_λ	estimate of the standard deviation of the thermal conductivity	$W/(m \cdot K)$
T	temperature	K
t	time	s
t_{des}	lifetime of desiccant	a
U	thermal transmittance	$W/(m^2 \cdot K)$
V	core volume of the product	m^3
V_{sp}	core volume of the specimen	m^3
V_{void}	void volume of core	m^3
w	width	m
w_c	core width	m
w_2	width of edge seal	

© ISO 2023 – All rights reserved

w_w	working width	m
X	water content inside the VIP	mass-%
λ_{air}	thermal conductivity of still air	W/(m·K)
$\lambda_{ambient}$	thermal conductivity of a ventilated VIP at centre of the panel	W/(m·K)
λ_{cop}	thermal conductivity for centre of panel	W/(m·K)
$\lambda_{cop,mean}$(25 years)	average value of thermal conductivity over 25 years in use at centre of panel	W/(m·K)
$\lambda_{cop,90/90,aged}$	$\lambda_{90/90}$ at centre of panel plus ageing	W/(m·K)
λ_D	declared thermal conductivity	W/(m·K)
λ_{eq}	thermal conductivity including edge effect	W/(m·K)
$\lambda_{eq,ja}$	equivalent thermal conductivity including edge effect	W/(m·K)
λ_{mean}	mean value of thermal conductivity	W/(m·K)
λ_i	one test result of thermal conductivity	W/(m·K)
λ_0	thermal conductivity in the evacuated state	W/(m·K)
λ'_p	change of thermal conductivity with pressure	W/(m·K·Pa)
λ'_t	change of thermal conductivity with time	W/(m·K·s)
λ_{VIP}	thermal conductivity of the VIP	W/(m·K)
λ'_X	change of thermal conductivity with humidity	W/(m·K)/mass-%
$\lambda_{90/90}$	90 % fractile with a confidence level of 90 % of thermal conductivity	W/(m·K)
$\lambda'_{t,23/50}$	change of thermal conductivity with time at 23 °C 50 % RH	W/(m·K·s)
$\lambda'_{t,50/70}$	change of thermal conductivity with time at 50 °C 70 % RH	W/(m·K·s)
$\lambda_{cop}(t)$	time-dependent thermal conductivity value	W/(m·K)
$\lambda(t)_{,23/50}$	time-dependent value of thermal conductivity at 23 °C 50 % RH	W/(m·K·s)
$\lambda(t)_{,50/70}$	time-dependent value of thermal conductivity at 50 °C 70 % RH	W/(m·K·s)
$\lambda^*(t = 0)$	interpolated initial thermal conductivity	W/(m·K)
σ_{mt}	tensile strength perpendicular to faces	kPa
σ_{10}	compressive stress at 10 % deformation	kPa
φ	RH inside the VIP	%
φ'_x	change of RH inside the VIP as function of water content	(rel. humidity-%) /(mass-%)
Φ_{in}	quantity of heat generated in the hot box	W

© ISO 2023 – All rights reserved

Φ_l	quantity of heat loss from the hot box	W
Φ_{sur}	quantity of heat flow through the surround panel	W
ψ	linear thermal transmittance	W/(m·K)
ψ_m	linear thermal transmittance for the joints in the metering area	W/(m·K)
$\Delta\theta_n$	environmental temperature difference between both sides of the specimen	K

4 Requirements

4.1 General

Products shall be assessed in accordance with Clause 6 and meet the requirements as outlined in Clause 4.

All characteristics defined in Clause 4, if declared, shall be subject to product type determination (PTD) in accordance with Annex E. The minimum frequencies of tests in the factory production control (FPC) shall be in accordance with Annex E.

NOTE The manufacturer can choose to give information for additional properties (see Annex F).

4.2 Thermal resistance and thermal conductivity

4.2.1 General

Requirements of thermal resistance and thermal conductivity are given in Table 1.

Table 1 — Thermal resistance and thermal conductivity

Property	Thermal resistance R $m^{2+}K/W$	Thermal conductivity λ W/(m·K)
Initial value of centre of panel (COP) ($\lambda_{cop,90/90}$, $R_{cop,90/90}$)	> 1,6	< 0,005
Initial value including thermal bridging (λ_D)	–	Declare
Aged value of COP ($\lambda_{cop,90/90,aged}$, $R_{cop,90/90,aged}$)	> 0,8	< 0,010
Aged value including thermal bridging ($\lambda_{90/90,aged}$)	–	Declare

4.2.2 Initial COP thermal properties

The initial value of COP, $R_{cop,90/90}$ and $\lambda_{cop,90/90}$ shall be determined by using Formulae (4) and (5) and shall not exceed the limits given in Table 1.

$$\lambda_{cop,90/90} = \lambda_{mean} + k \times s_\lambda \tag{4}$$

$$R_{cop,90/90} = \frac{d_N}{\lambda_{cop,90/90}} \tag{5}$$

4.2.3 Size dependent value

4.2.3.1 General

Edge effect and ageing effect depends on the size of VIP.

© ISO 2023 – All rights reserved