INTERNATIONAL STANDARD

ISO 185

Fourth edition
2020-05

Grey cast irons — Classification

Fontes à graphite lamellaire — Classification

Reference number
ISO 185:2020(E)

© ISO 2020



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

© ISO 2020 – All rights reserved

Contents

Page

Foreword ... **iv**
Introduction ... **v**
1 Scope ... **1**
2 Normative references ... **1**
3 Terms and definitions ... **1**
4 Designation ... **2**
5 Order information ... **2**
6 Manufacture ... **2**
7 Requirements ... **3**
7.1 Mechanical properties ... 3
7.2 Tensile properties ... 3
7.2.1 General ... 3
7.2.2 Test pieces machined from cast samples ... 3
7.2.3 Test pieces cut from a casting ... 3
7.3 Hardness properties ... 6
7.4 Graphite structure ... 7
8 Sampling ... **7**
8.1 General ... 7
8.2 Types of samples ... 7
8.3 Samples for tensile test ... 8
8.3.1 Size of cast samples ... 8
8.3.2 Frequency and number of test samples ... 8
8.3.3 Separately cast samples ... 8
8.3.4 Side-by-side cast samples ... 8
8.3.5 Cast-on samples ... 9
8.3.6 Samples cut from a casting ... 11
8.4 Samples for hardness test ... 12
9 Test methods ... **12**
9.1 Tensile test ... 12
9.2 Brinell hardness test ... 14
9.3 Graphite structure ... 14
9.4 Alternative test procedures ... 14
10 Retests ... **14**
10.1 Need for retests ... 14
10.2 Test validity ... 14
10.3 Nonconforming test results ... 15
10.4 Heat treatment of samples and castings ... 15
Annex A (informative) **Information on mechanical and physical properties in addition to that given in Tables 1 and 2** ... **16**
Annex B (informative) **Additional information on the relationship between hardness and tensile strength of grey cast irons** ... **18**
Annex C (informative) **Additional information on the relationship between tensile strength, hardness and wall thickness of grey iron castings** ... **21**
Annex D (informative) **Cross-references of ISO 185 grade designations to other standard grades of grey cast irons** ... **25**
Bibliography ... **27**

© ISO 2020 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 25, *Cast irons and pig irons*.

This fourth edition cancels and replaces the third edition (ISO 185:2019), of which it constitutes a minor revision. The changes to the previous edition are as follows:

— Correction to typographical error for relevant wall thickness of ISO 185/JL/HBW235 in Table 2; corrected from “4” to “40”. As a result of this change, the year of publication of ISO 185 in Annex D, Table D.1, column 1, updated from 2019 to 2020 to conform with this new edition.

— Symbols for Brinell hardness and relative hardness updated to H_B and H_R, respectively, in B.2 and Figure B.1.

Any feedback or questions on this document should be directed to the user’s national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2020 – All rights reserved

Introduction

This document deals with the classification of grey cast irons, subdivided into two groups:

— materials specified by their tensile strength;

— materials specified by their hardness.

It is also possible to specify grey cast irons by a combination of tensile strength and hardness.

NOTE This document does not cover technical delivery conditions for grey iron castings.

The properties of grey cast iron depend on the form and distribution of the graphite and on the structure of the matrix.

For many applications, tensile strength and hardness are not the only properties of interest to casting designers. Other mechanical or physical properties can be decisive for the use of grey iron. For example:

— the thermal capacity and the thermal diffusivity for disc brakes;

— the damping capacity for engine blocks or machine beds;

— the thermocycle fatigue for exhaust manifolds or ingot moulds.

Therefore, Annex A provides additional information of interest to casting designers.

Furthermore:

— Annex B contains additional information on the relationship between hardness and tensile strength;

— Annex C contains additional information on the relationship between tensile strength, hardness and wall thickness of grey iron castings;

— Annex D provides cross-references of ISO 185 grade designations to other standard grades of grey cast irons.

© ISO 2020 – All rights reserved

Grey cast irons — Classification

1 Scope

This document specifies the properties of unalloyed and low-alloyed grey cast irons used for castings that have been manufactured in sand moulds or in moulds with comparable thermal behaviour.

This document specifies the characterizing properties of grey cast irons by any of the following:

a) the tensile strength of cast samples;

b) if agreed by the manufacturer and the purchaser, the tensile strength of samples cut from a casting;

c) if agreed between the manufacturer and the purchaser, the hardness of the material determined on castings or on a cast-on knob.

If agreed by the manufacturer and the purchaser, the combination of tensile strength from option a) or option b) and plus hardness from option c) can be specified. Information on specifying a combination of tensile strength and hardness is given in Annex B.

This document specifies eight grades of grey cast iron according to tensile strength (see Table 1) and six grades of grey cast iron according to Brinell hardness (see Table 2).

This document does not apply to grey cast irons used for pipes and pipe fittings and continuous cast products.

This document does not cover technical delivery conditions for grey iron castings.

NOTE General information on the engineering properties of grey cast irons is provided in ISO/TR 10809-1.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 945-1, *Microstructure of cast irons — Part 1: Graphite classification by visual analysis*

ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

© ISO 2020 – All rights reserved

3.1
grey cast iron
cast material, iron and carbon based, carbon being present mainly in the form of flake (lamellar) graphite particles

Note 1 to entry: Grey cast iron is also known as "flake graphite cast iron" and, less commonly, as "lamellar graphite cast iron".

Note 2 to entry: Graphite form, distribution and size are specified in ISO 945-1.

3.2
relevant wall thickness
section of the casting, agreed between the manufacturer and the purchaser, to which the determined mechanical properties apply

3.3
separately cast sample
sample cast in a separate sand mould under representative manufacturing conditions and material

3.4
side-by-side cast sample
sample cast in the mould alongside the casting, with a connected but separate running system

3.5
cast-on sample
sample attached directly to the casting

4 Designation

The material shall be designated as given in either Table 1 or Table 2. The designation system is given in ISO/TR 15931.

The number in position 3 of the designation in Table 1 is the minimum tensile strength of the grade as determined by test pieces machined from standardized 30 mm test bars or from cast samples of corresponding relevant wall thickness.

The number in position 3 of the designation in Table 2 is the maximum Brinell hardness value of the grade for relevant wall thickness > 40 mm to ≤ 80 mm.

5 Order information

The following information shall be supplied by the purchaser:

a) the complete designation of the material;

b) any special requirements that have to be agreed between the manufacturer and the purchaser.

All agreements between the manufacturer and the purchaser shall be made by the time of acceptance of the order.

6 Manufacture

Unless otherwise specified by the purchaser, the method of manufacture of grey cast irons, including their chemical composition, to obtain the specified mechanical properties shall be left to the discretion of the manufacturer.

The manufacturer shall ensure that the requirements of this document are met for the material grade specified in the order.

© ISO 2020 – All rights reserved