INTERNATIONAL STANDARD

ISO 18797-1

First edition
2016-09-01

Petroleum, petrochemical and natural gas industries — External corrosion protection of risers by coatings and linings —

Part 1: Elastomeric coating systems-polychloroprene or EPDM

Industries du pétrole, de la pétrochimie et du gaz naturel — Protection de la corrosion externe des risers par revêtements et doublures —

Partie 1: Systèmes de revêtement élastomère-polychloroprène ou EPDM

Reference number
ISO 18797-1:2016(E)

© ISO 2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword ..... **v**
Introduction ..... **vi**
1 Scope **1**
2 Normative references **1**
3 Terms and definitions **3**
4 Abbreviated terms **5**
5 Pre-work requirements **6**
5.1 General 6
5.2 Health, safety and environmental (HSE) 6
5.3 Qualification of coating/lining application and inspection personnel 6
6 Materials **7**
6.1 General requirements 7
6.2 Material requirements 8
6.3 Materials packing, handling and storage 9
6.4 Coating materials 9
7 Bare pipes transportation, handling and storage **10**
7.1 Transportation and handling of pipes 10
7.2 Storage of pipes 10
8 Surface preparation **10**
8.1 General 10
8.2 Pipe imperfections/damages removal 11
8.3 Contaminants removal 11
8.4 Abrasive blast cleaning 11
9 Coating application for risers **13**
9.1 General 13
9.2 Priming and coating on abrasive blast-cleaned surface 13
9.3 Polychloroprene or EPDM application and vulcanization 14
9.4 Manual coating application on clamps, guides, bolt holes, inner sections of flanges and pipe section used for modifications at worksites 15
9.5 Coating application of field joints 16
9.6 Coating repair 16
10 Inspection and testing **17**
10.1 General 17
10.2 Testing of elastomer properties 17
10.2.1 General 17
10.2.2 Cure and hardness 17
10.2.3 Specific gravity 17
10.2.4 Rheological properties 17
10.2.5 Tensile strength, tear strength and elongation at break 17
10.2.6 Compression set 18
10.2.7 Abrasion resistance 18
10.2.8 Ozone resistance 18
10.2.9 Adhesion 18
10.2.10 Resistance to seawater 18
10.2.11 Thermal conductivity 18
10.2.12 Vulcanization characteristics (rotorless curemeters) 18
10.2.13 Cathodic disbondment 19
10.2.14 Volume resistivity 19
10.3 Inspection/testing of coated pipes 19
10.3.1 Visual inspection 19

© ISO 2016 – All rights reserved

10.3.2 Holiday detection 19
10.3.3 Thickness test 20
10.3.4 Adhesion (bond) test 20
10.3.5 Hardness testing 20
10.3.6 Ultrasonic inspection 20
10.3.7 Sound testing 20
10.3.8 Rejection 20
10.4 Inspection and testing of field joint coating 21
10.5 Test reports and certificate of compliance 21
11 Coating damage/defect repair 21
11.1 Defect acceptance criteria 21
11.2 Repair procedures 21
12 Handling and stacking of coated pipes 22
13 Quality requirements 22
14 Documentation 23
Annex A (informative) **Contents in a batch certificate 24**
Annex B (normative) **Physical properties of polychloroprene or EPDM elastomer 25**
Annex C (normative) **Riser pipe external coating progress chart 26**
Bibliography 28

 © ISO 2016 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*.

A list of all parts in the ISO 18797 series can be found on the ISO website.

© ISO 2016 – All rights reserved

Introduction

This document is based on GSO 2273. This document defines the minimum technical requirements for the external corrosion protection of risers by coatings and linings based on elastomeric coating systems-polychloroprene, EPDM or equivalent elastomeric coatings that are employed in the oil and gas industry and provides technical guidance for developing local standards and specifications in order to ensure compliance in coating and lining material selection and performance with contract requirements.

Users of this document need to be aware that further or differing requirements can be needed for individual applications. This document is not limiting the contractor and/or manufacturer from proposing or company from accepting alternative engineering solutions for the individual application. This can be particularly applicable where there is innovative or developing technology. Where an alternative is proposed, the specification issuer needs to identify any deviations from this document and provide details.

This document does not incorporate any form of passive fireproofing requirements or any related compatibility issues. Any requirements with regards to passive fireproofing are to be addressed separately.

© ISO 2016 – All rights reserved

Petroleum, petrochemical and natural gas industries — External corrosion protection of risers by coatings and linings —

Part 1: Elastomeric coating systems-polychloroprene or EPDM

1 Scope

This document specifies the minimum requirements for materials selection, surface preparation, application, inspection, testing, qualification and acceptance criteria of external coating for steel risers pipes used in the splash zone, their field joints and clamps/guides, using an elastomeric protective coating based on polychloroprene, EPDM or equivalent. This is applicable for new construction and repair of applied pipes before installation. Maintenance requirements and field repairs are covered in ISO 18797-2.

This document also specifies the requirements for transportation, handling and storage of riser pipes before and after surface preparation and coating application.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 34 (all parts), *Rubber, vulcanized or thermoplastic — Determination of tear strength*

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 48, *Rubber, vulcanized or thermoplastic — Determination of hardness (hardness between 10 IRHD and 100 IRHD)*

ISO 813, *Rubber, vulcanized or thermoplastic — Determination of adhesion to rigid substrate — 90 degree peel method* [alternative to ISO 814]

ISO 814, *Rubber, vulcanized or thermoplastic — Determination of adhesion to metal — Two-plate method* [alternative to ISO 813]

ISO 815-1, *Rubber, vulcanized or thermoplastic — Determination of compression set — Part 1: At ambient or elevated temperatures*

ISO 815-2, *Rubber, vulcanized or thermoplastic — Determination of compression set — Part 2: At low temperatures*

ISO 1431-1, *Rubber, vulcanized or thermoplastic — Resistance to ozone cracking — Part 1: Static and dynamic strain testing*

ISO 1817, *Rubber, vulcanized or thermoplastic — Determination of the effect of liquids*

ISO 2781, *Rubber, vulcanized or thermoplastic — Determination of density*

ISO 2812-2, *Paints and varnishes — Determination of resistance to liquids — Part 2: Water immersion method*

© ISO 2016 – All rights reserved

ISO 4649, *Rubber, vulcanized or thermoplastic — Determination of abrasion resistance using a rotating cylindrical drum device*

ISO 6502, *Rubber — Guide to the use of curemeters*

ISO 7619-1, *Rubber, vulcanized or thermoplastic — Determination of indentation hardness — Part 1: Durometer method (Shore hardness)*

ISO 8501-1:2007,[1)] *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 1: Rust grades and preparation grades of uncoated steel substrates and of steel substrates after overall removal of previous coatings*

ISO 8502-2, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 2: Laboratory determination of chloride on cleaned surfaces*

ISO 8502-3, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 3: Assessment of dust on steel surfaces prepared for painting (pressure-sensitive tape method)*

ISO 8502-4, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 4: Guidance on the estimation of the probability of condensation prior to paint application*

ISO 8502-5, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 5: Measurement of chloride on steel surfaces prepared for painting (ion detection tube method)*

ISO 8502-6, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 6: Extraction of soluble contaminants for analysis — The Bresle method*

ISO 8502-9, *Preparation of steel substrate before application of paints and related products — Tests for the assessment of surface cleanliness — Part 9: Field method for the conductometric determination of water-soluble salts*

ISO 8503-2, *Preparation of steel substrates before application of paints and related products — Surface roughness characteristics of blast-cleaned steel substrates — Part 2: Method for the grading of surface profile of abrasive blast-cleaned steel — Comparator procedure*

ISO 8503-4, *Preparation of steel substrates before application of paints and related products — Surface roughness characteristics of blast-cleaned steel substrates — Part 4: Method for the calibration of ISO surface profile comparators and for the determination of surface profile — Stylus instrument procedure* [alternative to ISO 8503-5]

ISO 8503-5, *Preparation of steel substrates before application of paints and related products — Surface roughness characteristics of blast-cleaned steel substrates — Part 5: Replica tape method for the determination of the surface profile* [alternative to ISO 8503-4]

ISO 10474:2013, *Steel and steel products — Inspection documents*

ISO 11126 (all parts), *Preparation of steel substrates before application of paints and related products — Specifications for non-metallic blast-cleaning abrasives*

ISO 21457, *Petroleum, petrochemical and natural gas industries — Materials selection and corrosion control for oil and gas production systems*

ISO 21809-3, *Petroleum and natural gas industries — External coatings for buried or submerged pipelines used in pipeline transportation systems — Part 3: Field joint coatings*

---

1) SSPC SP10 is equivalent to ISO 8501-1.

© ISO 2016 – All rights reserved

ISO 29601, *Paints and varnishes — Corrosion protection by protective paint systems — Assessment of porosity in a dry film* [alternative to ASTM D5162]

EN 10204:2004, *Metallic products — Types of inspection documents*

EN 12664, *Thermal performance of building materials and products — Determination of thermal resistance by means of guarded hot plate and heat flow meter methods — Dry and moist products of medium and low thermal resistance* [alternative to ISO 29601]

EN 14879-4:2007, *Organic coating systems and linings of protection of industrial apparatus and plants against corrosion caused by aggressive media — Part 4: Linings on metallic components*

API RP 5LW, *Recommended Practice for Transportation of Line Pipe on Barges and Marine Vessels* [alternative to API RP 5L1]

API RP 5L1, *Recommended Practice for Railroad Transportation of Line Pipe* [alternative to API RP 5LW]

ASTM D2084, *Standard Test Method for Rubber Property — Vulcanization Using Oscillating Disc Cure Meter*

ASTM D4285, *Standard Test Method for Indicating Oil or Water in Compressed Air*

ASTM D5162, *Standard Practice for Discontinuity (Holiday) Testing of Nonconductive Protective Coating on Metallic Substrates* [alternative to ISO 29601]

ASTM D5894, *Standard Practice for Cyclic Salt Fog/UV Exposure of Painted Metal, (Alternating Exposures in a Fog/Dry Cabinet and a UV/Condensation Cabinet)*

SSPC-AB 2, *Cleanliness of Recycled Ferrous Metallic Abrasive*

SSPC-PA 2, *Procedure for Determining Conformance to Dry Coating Thickness Requirements*

SSPC-SP 1, *Solvent Cleaning*

3 Terms and definitions

For the purpose of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at http://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

3.1
atmospheric zone
areas of offshore structures and riser pipes that extend upward from the *splash zone* (3.18) up to top decks of the *platform* (3.12) which are exposed to sun, wind, sprays and rains

3.2
applicator
organization appointed by *contractor* (3.3)/*client* (3.4) to perform application of coatings/linings on riser pipes as per project procedures prepared in accordance with this document

3.3
contractor
organization appointed by the *client* (3.4) to perform the *works* (3.21) in accordance with this document

3.4
client
organization for which professional services are rendered or person that receives a product

© ISO 2016 – All rights reserved

3.5
dew point
temperature at which moisture in air will condense out on to a solid surface, like blast-cleaned metal surface or newly coated surfaces

3.6
dust
loose fine particulate matter present on a steel surface prepared for rubber lining, arising from blast cleaning or other grinding activities or from worksite environments

3.7
elastomeric coatings
flexible skins, permanently bonded to *risers* (3.15) and structures

Note 1 to entry: Elastomeric coatings are designed and developed to withstand aggressive environment or conditions affecting platform structures and risers in marine splash zones. These provide add on durability to designed life to structures and risers in offshore environment, while providing resistance to seawater ingression, ozone oxidation, erosion and abrasion.

3.8
ethylene propylene diene monomer
EPDM
elastomeric compound or synthetic rubber applied as a protective coating on riser pipes in *splash zones* (3.18) to withstand erosion of riser pipe material caused by continuous exposure to seawater and wave actions

Note 1 to entry: EPDM provides resistance to outdoor and high temperature services in the range of -35 °C to 120 °C.

3.9
flash rusting
slight rust formation on a freshly blast-cleaned carbon steel surfaces due to humidity in air and if not painted within 4 h from start of blasting

3.10
holiday
discontinuity in a protective coating (cracks, pinholes, voids, etc.) that exhibits electrical conductivity when exposed to specific voltage

Note 1 to entry: Holiday also means a small defect in the lining that would permit corrosion of substrate under service conditions for which lining is designed. The term can be considered synonymous with cracks or mechanical damages occurring in rubber lining, while in services.

3.11
manufacturer
organization responsible for the manufacture of coating material(s)

3.12
platform
offshore structure used to accommodate oil and gas wells related production equipment, pipelines and living quarters

3.13
production batch
one loading capacity of the internal mixer used for preparing the mixed rubber prior to forming strip of sheet

3.14
polychloroprene
light yellow synthetic rubber compound obtained by polymerization of chloroprene

Note 1 to entry: Polychloroprene is commonly known as polychloroprene compound.

© ISO 2016 – All rights reserved

Note 2 to entry: Polychloroprene is applied as a protective coating on riser pipes in *splash zones* (3.18) and below to withstand erosion of riser pipe material caused by continuous exposure to seawater and wave actions. It provides resistance to outdoor and services temperature in the range of −35 °C to 90 °C.

3.15
riser
section of pipeline carrying crude/gas between ocean floor and upper decks of *platform* (3.12) on offshore structures

3.16
shore hardness
methods for determining the hardness of materials by means of durometer

3.17
site
lands and waters and other places on, under, in or through which the *works* (3.21) are to be carried out and any other lands, waters or places provided by the *client* (3.4) for the purposes of the contract together with any other places designated in the contract

3.18
splash zone
external surfaces of an offshore structure or pipeline that are, periodically wet and dry by the influence of the astronomical tides, winds and waves, the limits are as defined by the contract specifications

3.19
surface profile
micro-roughness of surface generally expressed as an average of height of highest peaks relative to lowest valleys sometime referred to as amplitude

3.20
vulcanization
curing of elastomeric materials by chemical reaction under heat and pressure to improve strength and elasticity of applied rubber lining

3.21
works
activities to be executed in accordance with the contract, as defined in the specified conditions and including both permanent and temporary activities

4 Abbreviated terms

µm	micrometer (microns)
ASTM	American Society for Testing and Materials
BS	British Standard
DFT	dry film thickness
HSE	health, safety and environment
GSO	Gulf Standardization Organization ITP
MS	method statement
MSDS	material safety data sheet
NACE	National Association of Corrosion Engineers
NPS	nominal pipe size

© ISO 2016 – All rights reserved