INTERNATIONAL STANDARD

ISO 19604

First edition
2018-05

Fine ceramics (advanced ceramics, advanced technical ceramics) — Mechanical properties of ceramic composites at high temperature — Determination of stress-rupture time diagram under constant tensile loading

Céramiques techniques (céramiques avancées, céramiques techniques avancées) — Propriétés mécaniques des composites à matrice céramique à température élevée sous air et à pression atmosphérique — Détermination du diagramme contrainte temps de rupture sous chargement constant en traction

Reference number
ISO 19604:2018(E)

© ISO 2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword ..... **v**

1 Scope **1**

2 Normative references **1**

3 Terms, definitions and symbols **1**

4 Principle **3**

5 Significance and use **3**

6 Apparatus **3**
6.1 Test machine 3
6.2 Gripping devices 4
6.2.1 General 4
6.2.2 Active gripping devices 4
6.2.3 Passive gripping devices 4
6.3 Test chamber 4
6.4 Load indicator 4
6.5 Extensometer 6
6.5.1 General 6
6.5.2 Mechanical extensometer 7
6.5.3 Electronic optical extensometer 7
6.6 Heating apparatus 7
6.7 Temperature measurement devices 7
6.8 Data recording system 8
6.9 Micrometers 8

7 Test specimens **8**
7.1 Test specimen geometry 8
7.2 End tabs of specimen 9
7.3 Test specimen preparation 10
7.4 Number of test specimens 11

8 Test preparation **11**
8.1 Alignment adjustment in tensile axis direction 11
8.2 Adjustment of heating apparatus and temperature measuring device 11
8.3 Measurement of test specimen dimension 11

9 Test procedures **12**
9.1 Testing technique 12
9.1.1 Test specimen mounting 12
9.1.2 Setting of extensometers 12
9.1.3 Setting of inert atmosphere 12
9.1.4 Heating the test specimen 12
9.1.5 Monitoring of temperature and elongation 13
9.1.6 Applying load 13
9.2 Post-testing treatment 13
9.3 Test validity 13
9.4 Stress levels in tests 14
9.5 Accidental interruption of the test 14

10 Calculation of results **14**
10.1 Tensile applied stress 14
10.2 Tensile strain 15
10.3 Drawing of tensile strain curve 15
10.4 Drawing of stress-rupture diagram 15

11 Test report **15**

© ISO 2018 – All rights reserved

Annex A (informative) **Measurement procedure of bending ratio in the adjustment of a tensile axis** **17**

 © ISO 2018 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 206, *Fine ceramics*.

© ISO 2018 – All rights reserved

Fine ceramics (advanced ceramics, advanced technical ceramics) — Mechanical properties of ceramic composites at high temperature — Determination of stress-rupture time diagram under constant tensile loading

1 Scope

This document specifies the conditions for determination of the stress-rupture time diagram of continuous fibre-reinforced ceramic matrix composites (including carbon fibre-reinforced carbon matrix composite) at high temperature in air, vacuum and inert gas atmospheres under constant tensile loading.

This document applies to all ceramic matrix composites with continuous fibre reinforcement: unidirectional (1D), bidirectional (2D) and tridirectional (xD, with $2 < x \leq 3$), loaded along one principal axis of reinforcement.

NOTE 1 In most cases, ceramic matrix composites to be used at high temperature in air are coated with an antioxidation coating.

NOTE 2 Since the main purpose of the test is to obtain the stress-rupture time data, the deformation measurement is not mandatory.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3611, *Geometrical product specifications (GPS) — Dimensional measuring equipment: Micrometers for external measurements — Design and metrological characteristics*

ISO 7500-1, *Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Calibration and verification of the force-measuring system*

ISO 17161, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Ceramic composites — Determination of the degree of misalignment in uniaxial mechanical tests*

ISO 20507, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Vocabulary*

IEC 60584-1, *Thermocouples — Part 1: Reference tables*

IEC 60584-2, *Thermocouples — Part 2: Tolerances*

3 Terms, definitions and symbols

For the purposes of this document, the terms and definitions given in ISO 20507 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

© ISO 2018 – All rights reserved

3.1
test temperature
T
temperature measured at the centre of the test specimen gauge section

3.2
calibrated length
l
part of the test specimen that has uniform and minimum cross-sectional area

3.3
gauge length
L_0
initial distance between reference points on the test specimen in the calibrated length

3.4
controlled temperature zone
part of the *calibrated length* (3.2) including the *gauge length* (3.3) where the temperature is within 20 °C for the test temperature of <500 °C, and within 50 °C for the test temperature of ≥500 °C

3.5
initial cross-section area
S_0
total area of the cross-section of the test specimen within the *calibrated length* (3.2) at room temperature

3.6
apparent cross-section area
$S_{0\,app}$
total area of the cross-section of the test specimen with an antioxidative protection

3.7
effective cross-section area
$S_{0\,eff}$
total area corrected by a factor, to account for the presence of an antioxidative protection

3.8
applied tensile force
F
constant tensile force loaded to the test specimen

3.9
applied tensile stress
σ
applied tensile force (3.8) supported by the test specimen at any time in the test divided by the initial cross-section area

3.10
apparent tensile stress
σ_{app}
applied tensile force supported by the test specimen at any time in the test divided by the *apparent cross-section area* (3.6)

3.11
effective tensile stress
σ_{eff}
applied tensile force (3.8) supported by the test specimen at any time in the test divided by the *effective cross-section area* (3.7)

© ISO 2018 – All rights reserved

3.12
longitudinal deformation
A
increase in the *gauge length* (3.3) between reference points under a constant tensile force

3.13
tensile strain
ε
relative change in the *gauge length* (3.3) defined as the ratio A/L_0 under a constant tensile force

3.14
tensile strain rate
$\dot{\varepsilon}$
change in tensile strain per unit time under a constant tensile force

3.15
rupture time
t_r
time required for the test specimen to fracture under a constant tensile force

3.16
rupture strain
ε_f
accumulated tensile strain to rupture under a constant tensile force

4 Principle

A constant uniaxial tensile force is applied to a test specimen of specified dimensions at high temperature in ambient air, vacuum or inert gas atmospheres. By continuing the test until rupture or a certain period, tensile strains and rupture time are determined.

5 Significance and use

Several mechanisms may be responsible for time-dependent deformation and rupture time of continuous fibre-reinforced ceramic matrix composites at high temperature under a constant tensile force. These may be creep of the fibre and/or the matrix, or may be caused by the composite nature of the material (e.g. matrix micro-cracking, fibre-matrix interface sliding, oxidation-activated slow crack growth, degradation of fibres). Creep behaviour is characterized by the total time-dependent increase of the gauge length and the rupture time, starting from the time when the specified force level is reached, whatever mechanism is responsible.

6 Apparatus

6.1 Test machine

The test machine shall conform to the following requirements.

a) The test machine shall meet the requirements of grade 1 or better of ISO 7500-1.

b) The forces loaded by the tensile testing machines shall be accurate to ±0,5 % at any force within the force capacity range of 5 % to 100 %.

c) The test machine shall be installed so as not to be influenced by external vibration and shock.

d) The test machine shall be equipped with features to maintain alignment and transmit force to a test specimen smoothly. A direct load or lever arm load test machine is desirable.

© ISO 2018 – All rights reserved