INTERNATIONAL STANDARD

ISO 20921

First edition
2019-02

Textiles — Determination of stable nitrogen isotope ratio in cotton fibres

Textiles — Détermination du rapport isotopique stable de l'azote dans les fibres de coton

Reference number
ISO 20921:2019(E)

© ISO 2019



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

 © ISO 2019 – All rights reserved

Contents

Page

Foreword ..... **iv**
Introduction ..... **v**
1 Scope **1**
2 Normative references **1**
3 Terms and definitions **1**
4 Principle **2**
5 Reagent **2**
6 Apparatus **2**
7 Preparation **3**
7.1 Sampling of test specimen 3
7.2 Pre-treatment of test specimen 3
8 Test procedure **3**
8.1 Weighing of aliquot 3
8.1.1 Determination of weighing amount needed 3
8.1.2 General weighing procedure 3
8.2 Natural ^{15}N abundance analysis 4
8.2.1 Instrumentation 4
8.2.2 General analytical procedure 4
9 Precision **5**
10 Test report **5**
Annex A (normative) **Identification procedure of organic raw cotton fibres by using stable nitrogen isotope ratios** **6**
Annex B (informative) **Analytical results of cotton fibres of various origin and process stage** **8**
Bibliography **10**

© ISO 2019 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2019 – All rights reserved

Introduction

Nitrogen (N) is the most essential element for cotton fibre production, since cotton crops require large amounts of N to sustain their growth and productivity. For this purpose, considerable amounts of nitrogen are applied to the soil as chemical fertilizers (e.g. urea) or organic fertilizers (e.g. composted manure).

The nitrogen applied in the form of a chemical fertilizer or a composted manure is absorbed from the soil to cotton crops through their root systems during cultivation, leaving a fertilizer-specific nitrogen isotopic signature in cotton tissues (particularly in cotton fibres). The inerasable nitrogen isotopic fingerprint engraved in cotton fibres remains unchanged during manufacturing of yarns, textiles and fabrics.

This document employs the principle of nitrogen isotope discrimination that fractionates against ^{15}N (heavier nitrogen isotope), resulting in ^{15}N-enriched reactants and ^{15}N-depleted products. In general, composted manure has a much higher $\delta^{15}N$ (natural ^{15}N abundance, defined hereinafter) than chemical fertilizer due to faster NH_3 (ammonia) volatilization of the lighter nitrogen isotope (^{14}N) than ^{15}N during the composting process. In contrast, chemical fertilizers (e.g. urea) are produced from the atmospheric N_2 via the Haber-Bosch process, resulting in low $\delta^{15}N$ values close to atmospheric N_2, which means that similar isotopic nitrogen compositions of chemical fertilizers to the atmospheric N_2.

Organic farming strictly bans the use of genetically modified crops (GMO), synthetic pesticides, and chemical fertilizers. Therefore, the use of chemical fertilizer during organic cotton production can be detected by determining $\delta^{15}N$ of cotton fibres, since the difference in $\delta^{15}N$ values between the two isotopically different nitrogen inputs (chemical vs. organic fertilizers) leaves a fertilizer-specific isotopic fingerprint in cotton fibres that can thereafter provide a forensic evidence for organic cotton fibre production.

© ISO 2019 – All rights reserved

Textiles — Determination of stable nitrogen isotope ratio in cotton fibres

1 Scope

This document specifies the determination of the ratio of nitrogen isotopes in cotton fibres that are used for textile production. It applies not only to cotton textiles but also to raw cotton taken from cotton fields.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

3.1
stable isotope
atom whose nucleus contains the same number of protons but a different number of neutrons

Note 1 to entry: Stable isotopes do not decay into other elements, while radioactive isotopes are unstable and will decay into other elements.

3.2
isotope-ratio mass spectrometry
IRSM
specialization of mass spectrometry, in which mass spectrometric methods are used to measure the relative abundance of isotopes in given sample

Note 1 to entry: The analysis of isotopes is normally related to measuring isotopic variations caused by mass-dependent isotopic fractionation in natural systems.

3.3
isotopic fractionation
isotopic discrimination
process that affect the relative abundance of isotopes

Note 1 to entry: Normally, the focus is on *stable isotopes* (3.1) of the same element. Isotopic fractionation in the natural environment can be measured by isotope analysis, using isotope-ratio mass spectrometry, to separate different element isotopes on the basis of their mass-to-charge ratios.

Note 2 to entry: Both heavy and light stable isotopes participate freely in biochemical reactions and in geochemical processes, but the rate at which heavy and light stable isotopes react differs. As a result, the lighter isotopes react faster than the heavier isotopes leading to isotopic fractionation between reactant and product in the reactions.

© ISO 2019 – All rights reserved

3.4
natural ^{15}N abundance
relative amount of the isotopes of nitrogen, as it occurs in nature

Note 1 to entry: Natural ^{15}N abundance is expressed in parts per thousand (‰, per mil) deviations from the atmospheric N_2 (a standard).

4 Principle

Isotope-ratio mass spectrometry (IRMS) measures the relative abundance of stable isotopes (e.g. ^{14}N and ^{15}N for nitrogen) in a cotton fibre sample. The abundance of stable isotopes varies according to physical, physiological and biochemical isotopic fractionation processes. Consequently, variations in the isotopic ratio of nitrogen (i.e. $^{15}N/^{14}N$) can be used both as fingerprints of the nitrogen source and to track the fate and transformation of nitrogen-containing compounds.

Nitrogen (N) is the most essential element that can increase the production of cotton fibres that are used to manufacture cotton yarns, textiles and fabrics. To ensure cotton fibre production, sufficient amount of nitrogen should be supplied as fertilizers (chemical or organic fertilizers) to the soil to meet the nitrogen demand for the growth and productivity of cotton crops.

Since most of fertilizer-nitrogen released into the soil is absorbed through root systems, translocated, and stored in the cotton fibres during cultivation, the isotopic nitrogen composition of the cotton fibre, expressed as $\delta^{15}N$, reflects the type of fertilizer from which it originated. In general, $\delta^{15}N$ of chemical fertilizers is close to 0 ‰, ranging from −3,9 ‰ to +0,5 ‰, while that of composted manure is much higher, ranging between +15,4 ‰ and +19,4 ‰. Cotton fibres harvested are processed to produce cotton yarns, textiles, and fabrics. Therefore, it is believed that $\delta^{15}N$ of a cotton fibre that contains information about the type of nitrogen fertilizers can serve as an isotopic fingerprint to identify authenticity and trace origin of cotton products, such as yarns, textiles and fabrics.

An accurate measurement of $\delta^{15}N$ of an aliquot of the dried cotton fibres can be obtained by using a continuous-flow type isotope ratio mass spectrometer linked to an elemental analyser (EA-IRMS). An aliquot of the test sample is washed, dried, ground to very fine powders using a ball-mill, weighed in a tin capsule on a microbalance, and then analysed for cotton-$\delta^{15}N$.

In particular, the use of chemical fertilizers can be attested by simultaneous measurements of stable nitrogen isotope ratio ($\delta^{15}N$) of cotton fibre and soil samples at harvest by using the determination process specified herein, and the determination procedure is specified in Annex A. Annex B shows some main outcomes of feasibility testing performed on cotton fabrics from organic certified textiles (see Table B.1) and raw cotton fibres obtained from several countries (see Table B.2).

5 Reagent

5.1 Reference material, **nitrogen isotopes in ammonium sulfate (IAEA-N2)** provided by the International Atomic Energy Agency (IAEA), necessary to check the accuracy and precision of $\delta^{15}N$ analysis, and available as NIST RM8548.

The $\delta^{15}N$ of NIST RM8548 is +20,3 ‰, and the accuracy and reproducibility of $\delta^{15}N$ analysis checked periodically with this standard should be lower than 0,4 ‰ and 0,2 ‰, respectively.

6 Apparatus

6.1 Drying oven, capable of heating up to around 80 °C.

6.2 Ball-mill, capable of grinding to final size smaller than 5 μm, and vibrational frequency ranging 3 Hz to 30 Hz (180 ~1 800) r/min are at least required.

© ISO 2019 – All rights reserved