TECHNICAL REPORT

ISO/TR 10400

Second edition
2018-08

Petroleum and natural gas industries — Formulae and calculations for the properties of casing, tubing, drill pipe and line pipe used as casing or tubing

Industries du pétrole et du gaz naturel — Formules et calculs relatifs aux propriétés des tubes de cuvelage, des tubes de production, des tiges de forage et des tubes de conduites utilisés comme tubes de cuvelage et tubes de production

Reference number
ISO/TR 10400:2018(E)

© ISO 2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

© ISO 2018 – All rights reserved

Contents

Page

Foreword ..... **vi**
Introduction ..... **vii**
1 Scope **1**
2 Normative references **2**
3 Terms and definitions **2**
4 Symbols **4**
5 Conformance **13**
5.1 References 13
5.2 Units of measurement 13
6 Triaxial yield of pipe body **13**
6.1 General 13
6.2 Assumptions and limitations 13
6.2.1 General 13
6.2.2 Concentric, circular cross-sectional geometry 14
6.2.3 Isotropic yield 14
6.2.4 No residual stress 14
6.2.5 Cross-sectional instability (collapse) and axial instability (column buckling) 14
6.3 Data requirements 14
6.4 Design formula for triaxial yield of pipe body 14
6.5 Application of design formula for triaxial yield of pipe body to line pipe 16
6.6 Example calculations 16
6.6.1 Initial yield of pipe body, Lamé formula for pipe when external pressure, bending and torsion are zero 16
6.6.2 Yield design formula, special case for thin wall pipe with internal pressure only and zero axial load 18
6.6.3 Pipe body yield strength 18
6.6.4 Yield in the absence of bending and torsion 19
7 Ductile rupture of the pipe body **20**
7.1 General 20
7.2 Assumptions and limitations 20
7.3 Data requirements 21
7.3.1 General 21
7.3.2 Determination of the hardening index 21
7.3.3 Determination of the burst strength factor, k_a 22
7.4 Design formula for capped-end ductile rupture 23
7.5 Adjustment for the effect of axial force and external pressure 24
7.5.1 General 24
7.5.2 Design formula for ductile rupture under combined loads 25
7.5.3 Design formula for ductile necking under combined loads 26
7.5.4 Boundary between rupture and necking 27
7.5.5 Axisymmetric wrinkling under combined loads 27
7.6 Example calculations 28
7.6.1 Ductile rupture of an end-capped pipe 28
7.6.2 Ductile rupture for a given true axial load 28
8 External pressure resistance **29**
8.1 General 29
8.2 Assumptions and limitations 29
8.3 Data requirements 29
8.4 Design formula for collapse of pipe body 30
8.4.1 General 30
8.4.2 Yield strength collapse pressure formula 30

© ISO 2018 – All rights reserved

8.4.3 Plastic collapse pressure formula 31
8.4.4 Transition collapse pressure formula 33
8.4.5 Elastic collapse pressure formula 34
8.4.6 Collapse pressure under axial tensile stress 35
8.4.7 Collapse pressure under axial stress and internal pressure 35
8.5 Formulae for empirical constants 35
8.5.1 General 35
8.5.2 SI units 36
8.5.3 USC units 36
8.6 Application of collapse pressure formulae to line pipe 37
8.7 Example calculations 37

9 Joint strength 37
9.1 General 37
9.2 API casing connection tensile joint strength 37
9.2.1 General 37
9.2.2 Round thread casing joint strength 38
9.2.3 Buttress thread casing joint strength 40
9.3 API tubing connection tensile joint strength 42
9.3.1 General 42
9.3.2 Non-upset tubing joint strength 42
9.3.3 Upset tubing joint strength 43
9.4 Line pipe connection joint strength 44

10 Pressure performance for couplings 44
10.1 General 44
10.2 Internal yield pressure of round thread and buttress couplings 44
10.3 Internal pressure leak resistance of round thread or buttress couplings 45

11 Calculated masses 48
11.1 General 48
11.2 Nominal linear masses 48
11.3 Calculated plain-end mass 48
11.4 Calculated finished-end mass 49
11.5 Calculated threaded and coupled mass 49
11.5.1 General 49
11.5.2 Direct calculation of e_m, threaded and coupled pipe 50
11.6 Calculated upset and threaded mass for integral joint tubing 50
11.6.1 General 50
11.6.2 Direct calculation of e_m, upset and threaded pipe 51
11.7 Calculated upset mass 51
11.7.1 General 51
11.7.2 Direct calculation of e_m, upset pipe 52
11.8 Calculated coupling mass 52
11.8.1 General 52
11.8.2 Calculated coupling mass for line pipe and round thread casing and tubing 52
11.8.3 Calculated coupling mass for buttress thread casing 55
11.9 Calculated mass removed during threading 56
11.9.1 General 56
11.9.2 Calculated mass removed during threading pipe or pin ends 56
11.9.3 Calculated mass removed during threading integral joint tubing box ends 58
11.10 Calculated mass of upsets 59
11.10.1 General 59
11.10.2 Calculated mass of external upsets 59
11.10.3 Calculated mass of internal upsets 60
11.10.4 Calculated mass of external-internal upsets 61

12 Elongation 61

13 Flattening tests 62
13.1 Flattening tests for casing and tubing 62

 © ISO 2018 – All rights reserved

13.2 Flattening tests for line pipe 62
14 Hydrostatic test pressures 63
14.1 Hydrostatic test pressures for plain-end pipe and integral joint tubing 63
14.2 Hydrostatic test pressure for threaded and coupled pipe 64
15 Make-up torque for round thread casing and tubing 64
16 Guided bend tests for submerged arc-welded line pipe 65
16.1 General 65
16.2 Background 67
16.2.1 Values of ε_{eng} 67
16.2.2 Values of A_{gbtj} 67
17 Determination of minimum impact specimen size for API couplings and pipe 67
17.1 Critical thickness 67
17.2 Calculated coupling blank thickness 68
17.3 Calculated wall thickness for transverse specimens 71
17.4 Calculated wall thickness for longitudinal specimens 71
17.5 Minimum specimen size for API couplings 71
17.6 Impact specimen size for pipe 73
17.7 Larger size specimens 73
17.8 Reference information 74
Annex A (informative) **Discussion of formulae for triaxial yield of pipe body 75**
Annex B (informative) **Discussion of formulae for ductile rupture 88**
Annex C (informative) **Rupture test procedure 126**
Annex D (informative) **Discussion of formulae for fracture 128**
Annex E (informative) **Discussion of historical collapse formulae 135**
Annex F (informative) **Development of probabilistic collapse performance properties 149**
Annex G (informative) **Calculation of design collapse strength from collapse test data 188**
Annex H (informative) **Calculation of design collapse strengths from production quality data 191**
Annex I (informative) **Collapse test procedure 205**
Annex J (informative) **Discussion of formulae for joint strength 211**
Annex K (informative) **Tables of calculated performance properties in SI units 219**
Annex L (informative) **Tables of calculated performance properties in USC units 221**
Bibliography 223

© ISO 2018 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, Subcommittee SC 5, *Casing, tubing and drill pipe*.

This second edition cancels and replaces the first edition (ISO/TR 10400:2007), which has been technically revised.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2018 – All rights reserved

Introduction

Performance design of tubulars for the petroleum and natural gas industries, whether it is formulated by deterministic or probabilistic calculations, compares anticipated loads to which the tubular can be subjected to the anticipated resistance of the tubular to each load. Either or both of the load and resistance can be modified by a design factor.

Both deterministic and probabilistic approaches to performance properties are addressed in this document. The deterministic approach uses specific geometric and material property values to calculate a single performance property value. The probabilistic method treats the same variables as random and thus arrives at a statistical distribution of a performance property. A performance distribution in combination with a defined lower percentile determines the final design formula.

Both the well design process itself and the definition of anticipated loads are currently outside the scope of standardization for the petroleum and natural gas industries. Neither of these aspects is addressed in this document. Rather, it serves to identify useful formulae for obtaining the resistance of a tubular to specified loads, independent of their origin. It provides limit state formulae (see annexes) which are useful for determining the resistance of an individual sample whose geometric and material properties are given, and design formulae which are useful for well design based on conservative geometric and material parameters.

Whenever possible, decisions on specific constants to use in a design formula are left to the discretion of the reader.

© ISO 2018 – All rights reserved

Petroleum and natural gas industries — Formulae and calculations for the properties of casing, tubing, drill pipe and line pipe used as casing or tubing

1 Scope

This document illustrates the formulae and templates necessary to calculate the various pipe properties given in International Standards, including

— pipe performance properties, such as axial strength, internal pressure resistance and collapse resistance,

— minimum physical properties,

— product assembly force (torque),

— product test pressures,

— critical product dimensions related to testing criteria,

— critical dimensions of testing equipment, and

— critical dimensions of test samples.

For formulae related to performance properties, extensive background information is also provided regarding their development and use.

Formulae presented here are intended for use with pipe manufactured in accordance with ISO 11960 or API 5CT, ISO 11961 or API 5D, and ISO 3183 or API 5L, as applicable. These formulae and templates can be extended to other pipe with due caution. Pipe cold-worked during production is included in the scope of this document (e.g. cold rotary straightened pipe). Pipe modified by cold working after production, such as expandable tubulars and coiled tubing, is beyond the scope of this document.

Application of performance property formulae in this document to line pipe and other pipe is restricted to their use as casing/tubing in a well or laboratory test, and requires due caution to match the heat-treat process, straightening process, yield strength, etc., with the closest appropriate casing/tubing product. Similar caution is exercised when using the performance formulae for drill pipe.

This document and the formulae contained herein relate the input pipe manufacturing parameters in ISO 11960 or API 5CT, ISO 11961 or API 5D, and ISO 3183 or API 5L to expected pipe performance. The design formulae in this document are not to be understood as a manufacturing warranty. Manufacturers are typically licensed to produce tubular products in accordance with manufacturing specifications which control the dimensions and physical properties of their product. Design formulae, on the other hand, are a reference point for users to characterize tubular performance and begin their own well design or research of pipe input properties.

This document is not a design code. It only provides formulae and templates for calculating the properties of tubulars intended for use in downhole applications. This document does not provide any guidance about loads that can be encountered by tubulars or about safety margins needed for acceptable design. Users are responsible for defining appropriate design loads and selecting adequate safety factors to develop safe and efficient designs. The design loads and safety factors will likely be selected based on historical practice, local regulatory requirements, and specific well conditions.

All formulae and listed values for performance properties in this document assume a benign environment and material properties conforming to ISO 11960 or API 5CT, ISO 11961 or API 5D and

© ISO 2018 – All rights reserved

ISO 3183 or API 5L. Other environments can require additional analyses, such as that outlined in Annex D.

Pipe performance properties under dynamic loads and pipe connection sealing resistance are excluded from the scope of this document.

Throughout this document tensile stresses are positive.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

3.1
Cauchy stress
true stress
force applied to the surface of a body divided by the current area of that surface

3.2
coefficient of variance
dimensionless measure of the dispersion of a random variable, calculated by dividing the standard deviation by the mean

3.3
design formula
formula which, based on production measurements or specifications, provides a performance property useful in design calculations

Note 1 to entry: A design formula can be defined by applying reasonable extremes to the variables in a limit state formula to arrive at a conservative value of expected performance. When statistically derived, the design formula corresponds to a defined lower percentile of the resistance probability distribution curve.

3.4
deterministic
approach which assumes all variables controlling a performance property are known with certainty

Note 1 to entry: Pipe performance properties generally depend on one or more controlling parameters. A deterministic formula uses specific geometric and material property values to calculate a single performance property value. For design formulations, this value is the expected minimum.

3.5
ductile rupture
failure of a tube due to internal pressure and/or axial force in the plastic deformation range

3.6
e
Euler's constant
2,718 281 828

© ISO 2018 – All rights reserved

3.7
effective axial force
material axial force (pipe wall axial stress times cross-sectional area) adjusted for the effect of internal and external pressure

Note 1 to entry: When a tubular is bent laterally into a circular arc, the pressures apply a lateral uniform distributed load (UDL) of $(p_i A_i - p_o A_o)/R$. For small deflections, the curvature is defined as $1/R \cong d^2y/dx^2$, thus, this term can be grouped with the tension term $F\, d^2y/dx^2$ in the governing differential formula. For bending and buckling, the tubular therefore acts as if it were loaded by the *effective axial force* $F_{eff} = F_a - p_i A_i + p_o A_o$[141]. It should be seen as a convenient grouping of terms, which determines the structural response: it does not exist as a physical axial force.

3.8
engineering strain
dimensionless measure of the stretch of a deforming line element, defined as the change in length of the line element divided by its original length

3.9
engineering stress
force applied to the surface of a body divided by the original area of that surface

3.10
fracture pressure
internal pressure at which a tube fails due to propagation of an imperfection

3.11
inspection threshold
maximum size of a crack-like imperfection which is defined to be acceptable by the inspection system

3.12
J-integral
measure of the intensity of the stress-strain field near the tip of a crack

3.13
label 1
dimensionless designation for the size or specified outside diameter that may be used when ordering pipe

3.14
label 2
dimensionless designation for the mass per unit length or wall thickness that may be used when ordering pipe

3.15
limit state formula
formula which, when used with the measured geometry and material properties of a sample, produces an estimate of the failure value of that sample

Note 1 to entry: A limit state formula describes the performance of an individual sample as closely as possible, without regard for the tolerances to which the sample was built.

3.16
logarithmic strain
dimensionless measure of the stretch of a deforming line element, defined as the natural logarithm of the ratio of the current length of the line element to its original length

Note 1 to entry: Alternatively, the logarithmic strain can be estimated as the natural logarithm of one plus the engineering strain.

3.17
mass
label used to represent wall thickness of tube cross section for a given pipe size

© ISO 2018 – All rights reserved

3.18
pipe body yield
stress state necessary to initiate yield at any location in the pipe body

3.19
principal stress
stress on a principal plane for which the shear stress is zero

Note 1 to entry: For any general state of stress at any point, there exist three mutually perpendicular planes at that point on which shearing stresses are zero. The remaining normal stress components on these three planes are principal stresses. The largest of these three stresses is called the maximum principal stress.

3.20
probabilistic method
approach which uses distributions of geometric and material property values to calculate a distribution of performance property values

3.21
synthesis method
probability approach which addresses the uncertainty and likely values of pipe performance properties by using distributions of geometric and material property values

Note 1 to entry: These distributions are combined with a limit state formula to determine the statistical distribution of a performance property. The performance distribution in combination with a defined lower percentile determines the final design formula.

3.22
template
procedural guide consisting of formulae, test methods and measurements for establishing design performance properties

3.23
TPI
threads per inch

Note 1 to entry: 1 thread per inch = 0,039 4 threads per millimetre; 1 thread per millimetre = 25,4 threads per inch.

3.24
true stress-strain curve
plot of Cauchy stress (ordinate) versus logarithmic strain (abscissa)

3.25
yield
permanent, inelastic deformation

3.26
yield stress bias
ratio of actual yield stress to specified minimum yield stress

4 Symbols

A	hand-tight standoff, turns
A_c	empirical constant in historical API collapse formula
A_{crit}	area of the weaker connection component at the critical cross section
A_{gbtj}	critical dimension on guided bend test jig, denoted as dimension A in ISO 3183 or API 5L
A_i	area to pipe inside diameter; $A_i = \pi d^2/4$

© ISO 2018 – All rights reserved