TECHNICAL REPORT

ISO/TR 18228-4

First edition
2022-03

Design using geosynthetics —

Part 4: Drainage

Design pour géosynthétiques —

Partie 4: Drainage

Reference number
ISO/TR 18228-4:2022(E)

© ISO 2022



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

© ISO 2022 – All rights reserved

Contents

Page

Foreword ... **iv**
Introduction ... **v**
1 Scope ... **1**
2 Normative references ... **1**
3 Terms, definitions and symbols ... **1**
3.1 Symbols and abbreviations ... 1
4 Concepts ... **6**
5 Applications ... **8**
6 Materials ... **9**
6.1 Components of draining geocomposites ... 9
6.2 Filter Component of draining geocomposites ... 9
6.3 Drainage cores ... 10
6.4 Definitions and acronyms for the various products ... 10
7 Properties relevant to design ... **10**
8 Darcy's law ... **10**
9 Subsurface drainage structures ... **11**
10 Geosynthetic properties ... **11**
11 Geotextile filter performance and filter criteria ... **12**
12 Geocomposite drainage systems design ... **12**
12.1 General ... 12
12.2 Calculation of input flow rate ... 13
12.2.1 General ... 13
12.2.2 Rainfall on sloping surface ... 13
12.2.3 Filtration from soil or rock ... 16
12.3 Calculation of available flow rate ... 17
12.3.1 Hydraulic gradient ... 17
12.3.2 Discharge capacity ... 19
12.3.3 Pressure applied to the geocomposite ... 19
12.3.4 Materials in contact with the faces of the drainage geocomposite ... 21
12.3.5 Compressive behaviour of geocomposites ... 22
12.3.6 Factors influencing the available flow rate ... 24
12.3.7 Laboratory tests for water flow capacity of geocomposites ... 25
12.3.8 Specific situations ... 27
12.3.9 Flow rate versus hydraulic gradient ... 29
12.3.10 Flow rate versus viscosity ... 31
12.3.11 General procedure for evaluating the available flow rate of the geocomposites ... 33
12.4 Selection of the geocomposite ... 34
12.5 Equivalence with a granular drainage layer ... 34
12.5.1 General ... 34
12.5.2 Equivalence for water flow on slopes ... 34
12.5.3 Equivalence for vertical water flow ... 39
Annex A (informative) **The movement of water in the ground** ... **41**
Annex B (informative) **Reduction factors** ... **53**
Bibliography ... **60**

© ISO 2022 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 221, *Geosynthetics*.

A list of all parts in the ISO 18228 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2022 – All rights reserved

Introduction

The ISO 18228 series provides guidance for designs using geosynthetics for soils and below ground structures in contact with natural soils, fills and asphalt. The series contains 10 parts which cover designs using geosynthetics, including guidance for characterization of the materials to be used and other factors affecting the design and performance of the systems which are particular to each part, with ISO/TR 18228-1 providing general guidance relevant to the subsequent parts of the series.

The series is generally written in a limit state format and guidelines are provided in terms of partial material factors and load factors for various applications and design lives, where appropriate.

This document includes information relating to the drainage function. Details of design methodology adopted in a number of regions are provided.

Parts of this document have been adapted from *Comité français des géosynthétiques*, 2014[10].

© ISO 2022 – All rights reserved

Design using geosynthetics —

Part 4:
Drainage

1 Scope

This document outlines the criteria for evaluating the available and the required flow rate of geosynthetics in various situations, provides a summary of the available laboratory testing, and lists the safety factors and reduction factors that can be applied to the parameters when designing using geosynthetics for drainage systems.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10318-1, *Geosynthetics — Part 1: Terms and definitions*

3 Terms, definitions and symbols

For the purposes of this document, the terms and definitions given in ISO 10318-1 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at https://www.electropedia.org/

3.1 Symbols and abbreviations

O_{90}	characteristic opening size of a geosynthetic (µm)
k_n	coefficient of permeability normal to the plane(m/s)
q_n	flux(l/m^2·s)
v-index	velocity index(mm/s)
ψ	permittivity(s^{-1})
ϑ	transmissivity (m^3/s/m or l/s/m)
GCD	acronym used for draining geocomposites
dQ/dt	volumetric flow rate of water through the soil (m^3/s or l/s)
A	bulk cross-sectional area through which the flow occurs (m^2)
h	hydraulic head (m)

© ISO 2022 – All rights reserved

l	distance travelled by the bulk water flow (m)
dh/dl	hydraulic gradient (dimensionless)
K	hydraulic conductivity or permeability of the soil (m/s)
q	equal to (dQ/dt), volumetric flow rate (m^3/s or l/s)
i	equal to (dh/dl), hydraulic gradient (dimensionless)
q_p	in-plane flow capacity, equal to the volumetric flow rate of water and/or other liquids per unit width of specimen, at defined gradients in the plane of a product (l/s·m).
k_p	coefficient of permeability in the plane, equal to the ratio between in-plane flow capacity q_p and the product of thickness d and hydraulic gradient i (m/s)
q_r	rainfall per unit horizontal area (m^3/s/m^2)
P	rainfall flow rate (m^3/s)
A_h	horizontal area (m^2)
q_s	rainfall per unit sloping area (m^3/s/m^2)
β	slope angle (deg or °)
q_D	rainfall per unit area entering the drainage system (m^3/s/m^2)
f	coefficient of infiltration (dimensionless)
Q_R	input flow rate due to rainfall (m^3/s/m or l/s/m)
L	length of the slope (m)
L_h	horizontal length of the slope (m)
h_r	height of rainfall (mm)
t	duration of the rainfall (h)
j	rainfall intensity (mm/h)
a	parameter of the pluviometric curve (mm h^{-n})
n	exponent of the pluviometric curve (-)
$F_{S,Q}$	Factor of Safety on input flow rate (dimensionless)
Q_S	input flow rate due to additional surficial flow (m^3/s/m or l/s/m)
Q_D	design input flow rate in the geocomposite (m^3/s/m or l/s/m)
Q_F	total rainfall flow on the catchment zone (m^3/s or l/s)
A_c	horizontal area of the catchment zone (m^2)
B_g	running width of the geocomposite drain (m)
h_{max}	maximum thickness of liquid in the granular liquid collection layer

© ISO 2022 – All rights reserved

Q	Specific flow rate = discharge per unit width in the geocomposite, under a specified hydraulic gradient ($m^3/s/m$ or l/s/m)
B	width of geocomposite specimen in the flow rate test (m)
q_m	measured flow rate for a geocomposite specimen of width B (l/s or m^3/s)
p	applied pressure (kPa)
γ	saturated unit weight of the soil or material placed on the geocomposite (kN/m^3)
H	thickness of the soil or the material placed on the geocomposite (m)
w_s	distributed surcharge on the ground surface (kPa)
H_l	depth of the lowest point of the geocomposite below the ground surface (m)
K_a	coefficient of active pressure of the soil (dimensionless)
φ	friction angle of the soil (deg or °)
t, t_{GCD}	geocomposite thickness (m)
L_{sp}	distance between geotextile support points (m)
Q_{i1}	specific flow rate for the i_1 gradient (l/s/m or m^2/s)
Q_{i0}	specific flow rate for the i_0 gradient (l/s/m or m^2/s)
i_1	hydraulic gradient on the diagram, immediately higher than the actual hydraulic gradient (dimensionless)
i_0	actual hydraulic gradient (dimensionless)
Q_v	discharge or volumetric flow rate (m^3/s)
A_g	cross-sectional area of the geocomposite (m^2)
χ	parameter depending on the roughness of the flow surface ($m^{1/2}$ / s)
R	hydraulic radius of the flow conduit (m)
C	parameter as a function of geometry and roughness of the flow surface
σ_n	pressure applied in lab tests (kPa)
i_1, i_2	hydraulic gradients applied in lab tests (dimensionless)
i_o	actual hydraulic gradient (dimensionless)
$Q(\sigma_n, i)$	flow rate evaluated for the values σ_n, i (l/s/m or m^2/s)
$Q_{i0}(\sigma_n, i_0)$	flow rate evaluated for the values σ_n, i_0 (l/s/m or m^2/s)
Q_{20}, Q_T	specific flow rates at 20 °C and T °C
μ_{20}, μ_T	viscosity of water at 20 °C and T °C
T	actual temperature of water (°C)
C_T	correction factor for temperature and viscosity (dimensionless)

© ISO 2022 – All rights reserved

Q_a	available long term flow rate for the geocomposite (l/s/m or m^2/s)
Q_L	short term flow rate obtained from laboratory tests with the appropriate boundary conditions (l/s/m or m^2/s)
$R_{F,in}$	Reduction Factor for the intrusion of filter geotextiles into the draining core due to tensile creep of the geotextile, occurring after the short term flow rate test (dimensionless)
$R_{F,cr\text{-}Q}$	Reduction Factor for the compressive creep of the geocomposite (dimensionless)
$R_{F,cc}$	Reduction Factor for chemical clogging of the draining core (dimensionless)
$R_{F,bc}$	Reduction Factor for biological clogging of the draining core (dimensionless)
$R_{F,L}$	Reduction Factor for overall uncertainties on laboratory data and field conditions (dimensionless)
q_h	flow rate of liquid supply ($m^3/s/m^2$)
j	factor of the Giroud theory (dimensionless)
$t_{prescribed}$	prescribed thickness of the granular layer (m)
$F_{S,E}$	Factor of Safety on equivalency (dimensionless)
E	equivalency coefficient (dimensionless)
Q_{GCD}	minimum short term input flow rate for the geocomposite in order to be considered equivalent to the granular layer having thickness larger than h_{max} ($m^3/s/m$ or l/s/m)
Q_{Darcy}	flow rate in the granular soil layer according to Darcy's law ($m^3/s/m$)
K_{lt}	long term permeability of the granular soil layer evaluated in situ at the end of its design life (m/s)
q_h^*	equivalent flow rate of liquid supply in the granular soil layer at equilibrium ($m^3/s/m^2$)
j^*	factor of the Giroud theory related to Q_{Darcy} (dimensionless)
E^*	equivalency coefficient for the thickness $t_{prescribed}$ (dimensionless)
Q_{GCD}^*	short term input flow rate for the geocomposite in order to be considered equivalent to the granular layer having thickness $t_{prescribed}$ ($m^3/s/m$)
Q_{GL}	flow rate afforded by the granular drainage layer ($m^3/s/m$ or l/s/m)
U	Darcy's velocity (m/s)
z	vertical distance in the soil (m)
k	intrinsic permeability of the soil, which depends only on properties of the solid matrix (m^2)
ρ	density of the fluid ($N\ s^2/m^4$ or kg/m^3)
μ	dynamic viscosity of the fluid ($N / m^2\ s$)
C	Hazen's empirical coefficient for intrinsic permeability (dimensionless)
C^*	Hazen's empirical coefficient for permeability ($m^{-1}\ s^{-1}$)

© ISO 2022 – All rights reserved

C_U	coefficient of uniformity of the soil = D_{60} / D_{10} (dimensionless)
D_{10}, D_{60}	diameter of soil particles for 10 % and 60 % cumulative passing (m)
g	acceleration due to gravity = 9,81 m/s^2
γ_w	unit weight of water for the given temperature (kN/m^3)
n	soil porosity = void volume / total volume (dimensionless)
$R_{F,in(R/R)\ short\ term}$	Reduction Factor for the intrusion of filter geotextiles into the draining core for Rigid / Rigid boundaries at short term (dimensionless)
$R_{F,in(R/S)\ short\ term}$	Reduction Factor for the intrusion of filter geotextiles into the draining core for Soft / Soft boundaries at short term (dimensionless)
$R_{F,in(S/S)\ short\ term}$	Reduction Factor for the intrusion of filter geotextiles into the draining core for Rigid / Soft boundaries at short term (dimensionless)
$R_{F,in(R/R)\ long\ term}$	Reduction Factor for the intrusion of filter geotextiles into the draining core for Rigid / Rigid boundaries at long term (dimensionless)
$R_{F,in(R/S)\ long\ term}$	Reduction Factor for the intrusion of filter geotextiles into the draining core for Soft / Soft boundaries at long term (dimensionless)
$R_{F,in(S/S)\ long\ term}$	Reduction Factor for the intrusion of filter geotextiles into the draining core for Rigid / Soft boundaries at long term (dimensionless)
$Q_{L\ (R/R)\ short\ term}$	Specific flow rate for Rigid / Rigid boundaries at short term (m^3/s/m or l/s/m)
$Q_{L\ (R/S)\ short\ term}$	Specific flow rate for Rigid / Soft boundaries at short term (m^3/s/m or l/s/m)
$Q_{L\ (S/S)\ short\ term}$	Specific flow rate for Soft / Soft boundaries at short term (m^3/s/m or l/s/m)
$Q_{L\ (R/R)\ long\ term}$	Specific flow rate for Rigid / Rigid boundaries at long term (m^3/s/m or l/s/m)
$Q_{L\ (R/S)\ long\ term}$	Specific flow rate for Rigid / Soft boundaries at long term (m^3/s/m or l/s/m)
$Q_{L\ (S/S)\ long\ term}$	Specific flow rate for Soft / Soft boundaries at long term (m^3/s/m or l/s/m)
$R_{F,cr,th}$	Reduction Factor for thickness (dimensionless)
t_{virgin}	thickness of the geocomposite core before load application (m);
t_{cr}	thickness measured at long term (1 year, 10 years, … 100 years) in compressive creep tests (m)
$q(\sigma_n, i,$ long term)	long term available flow rate for applied pressure σ_n and hydraulic gradient i (m^3/s/m or l/s/m);
$q(\sigma_n, i)$	short term available flow rate for applied pressure σ_n and hydraulic gradient i (m^3/s/m or l/s/m);
$x(\sigma_n, 0)$	short term thickness of geocomposite for applied pressure σ_n (m);
$x(\sigma_n, t)$	long term thickness of geocomposite for applied pressure σ_n (m);
F	Reduction Factor for thickness (dimensionless)
α	Reduction Factor for the long term effect of compressive creep and geotextile intrusion (dimensionless)

© ISO 2022 – All rights reserved